

25 June 2025

EXPLORATION TARGET REVEALS LARGE SCALE AT WHUNDO COPPER

Highlights

- **Copper-Zinc Exploration Target supports potential larger scale mineral system across the Whundo project**
- **The Exploration Target is a crucial part of the Company's strategic pathway to assessing a potential near-term mining operation**
- **Fast tracking assessment of gold contribution to previously reported Mineral Resource^{1,2}**
- **Shallow mineralisation of immediate interest to identify and evaluate near-term production opportunities**
- **Conceptual mining studies are progressing which include potential operations immediately below previously mined historic open cut pits at Whundo East and Whundo West and the unmined deposits at Ayshia and Yannery**
- **Radio Hill processing plant located 12km away will be evaluated as a potential processing option**

GreenTech Metals Ltd (ASX: GRE), ('GreenTech' or 'the Company') is pleased to announce it has taken significant steps to evaluate the viability of near-term production from the Whundo Project. This evaluation is focused on shallow defined resources at Whundo (East & West) and Ayshia as well as known shallow mineralisation at Yannery. The deeper Cu/Zn mineralisation associated with each of the plunging mineralised shoots are not sufficiently defined by drilling at this stage to be incorporated into the current assessment of near-term production opportunities.

Whundo Project - Exploration Target

The Whundo Project Exploration Target encompasses multiple mineralised shoots comprising Ayshia, Yannery, Whundo East, Whundo West, Austin & Shelby (**Figure 1**) and does not include any of the previously reported Mineral Resource Estimate tonnes. Tonnes, Grade and Metal content estimated range is **15 to 23 million tonnes with a target grade of 0.9% to 1.4% Copper and 0.2% to 0.4% Zinc, and metal content of 264,800 to 176,500 tonnes Copper and 46,000 to 69,000 tonnes Zinc** (refer **Tables 1 & 2**).

The Whundo Project Exploration Target are conceptual in nature. There has been insufficient exploration to estimate a Mineral Resource under the Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserve, the JORC code (JORC2012). It is uncertain if further exploration will result in the estimation of a Mineral Resource.

GreenTech's Executive Director, Tom Reddicliffe, commented: "We are very pleased with the potential of the Whundo Project. Importantly our work to date has highlighted both shallow and deep mineralised areas for further drill testing. The shallow mineralisation is of immediate interest as the company looks to identify and evaluate near-term production opportunities. We are also fast tracking our assessment of our previously reported Mineral Resource Estimates given the significant gold

¹ Refer to ASX:GRE Announcement 11th May 2022

² Refer to ASX:GRE Announcement 12th April 2023

contribution which we believe will potentially enhance inground value and subsequently have a positive effect on modelling project economics.”




Figure 1: Exploration Target Estimate Domains associated with the Whundo Cu-Zn Mineralisation

Table 1: Summary Whundo Project Exploration Target - Potential Tonnes and Grade Ranges

Tonnes Range	Metal	Grade Range	Metal Content Range
15-23Mt	Copper	0.9 - 1.4%	176,000 - 265,000 tonnes
	Zinc	0.2 - 0.4%	46,000 - 69,000 tonnes

Table 2: Whundo Project Exploration Target - Potential Tonnes, Grade and Metal Content Ranges

Mineralised Shoot	Tonnage (Mt)		Cu (%)		Zn (%)		Cu Metal (t)*		Zn (t)*	
	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max
Whundo East	0.06	0.09	0.7	1.0	0.10	0.15	500	700	70	100
Whundo West	0.1	0.2	1.0	1.5	0.2	0.3	1,400	2,100	300	400
Austin	3.9	5.8	0.8	1.3	0.2	0.4	40,500	60,700	11,500	17,300
Ayshia	2.7	4.1	0.7	1.1	0.3	0.5	24,800	37,200	10,300	15,400
Yannery	0.4	0.7	0.9	1.4	0.3	0.4	5,100	7,700	1,500	2,200
Shelby	8.1	12.1	1.0	1.6	0.2	0.3	104,300	156,400	22,500	33,800
Total*	15	23	0.9	1.4	0.2	0.4	176,000	265,000	46,000	69,000

*Numbers and totals are subject to rounding errors

The Whundo Project Exploration Target is conceptual in nature. There has been insufficient exploration to estimate a Mineral Resource under the Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserve, the JORC code (JORC2012). It is uncertain if further exploration will result in the estimation of a Mineral Resource.

The estimated tonnes, grade and metal content has been reported using a cut-off grade of 0.5% copper (Tables 1 & 2). Areas previously subject to Mineral Resource Estimates^{3,4}, comprise the Ayshia and Whundo deposits which have been excluded from the current estimate. Inverse Distance methodology has been used in the block model to assess the Whundo cluster of mineralised Cu-Zn Shoots and to define the Exploration Target domains (Figure 1).

The current mineral resource estimates (MRE) for Ayshia and Whundo are summarised in Table 3 and shown in Figure 1. The Mineral Resource Estimates are not included as part of the Exploration Target.

Table 3: Mineral Resource Estimate for Whundo Project^{5,6}

Deposit	Cutoff	Category	Mt	Cu (%)	Au	Zn (%)	Ag	Cu Metal (t)	Zn Metal (t)
Ayshia	>0.5	Inferred	0.9	1.3	Not reported	2.3	Not reported	12,000	21,000
Whundo	>0.2	Indicated	4.4	1.03	Not reported	0.89	Not reported	45,000	39,000
	>0.2	Inferred	0.9	1.4	Not reported	0.5	Not reported	12,000	4,000
Total		Ind & Inf	6.2	1.12	Not reported	1.04	Not reported	69,000	64,000




Figure 2: Exploration Target Estimate block model using Inverse Distance methodology

³ Refer to ASX:GRE Announcement 12th April 2023

⁴ Refer to ASX:GRE Announcement 11th May 2022

⁵ Refer to ASX:GRE Announcement 12th April 2023

⁶ Refer to ASX:GRE Announcement 11th May 2022

Gold and silver have not been included in the current Mineral Resource Estimate. However, as disclosed in the ASX announcement dated 5 June 2025⁷, high-grade gold intercepts have been reported in association with copper mineralisation. As a result, the Mineral Resource Estimate (**MRE**) for the Whundo Project is currently under review. If the updated MRE confirms a material contribution from gold and silver, it may inform a future update to the Exploration Target and enhance the potential for future mining operations.

Method of Assessment

The companies entire drill hole data base has been utilised to inform the potential size of the exploration target beyond the current Whundo Mineral Resource Statement^{8,9}. The drilling data base comprising a total of 1,135 drill holes for a total of 83,298.30m. Of this total 42 drillholes, for a total of 5,916.8m, sit within the exploration target area (refer **Table 4**).

Table 4: Summary of Drillholes within the Exploration Target area*

	Exploration Target Estimate	Drill Hole Total (minus exploration target drill holes)
No of Holes	42	1,135
Total Meters drilled (m)	5,916.8	83,298.3

*The Whundo Exploration Target has been developed using Leapfrog Geo and Leapfrog EDGE workflows

A total of fourteen (14) hard-boundary domains have been defined to inform the estimate, based on modelling broad mineralised trends (>0.1% copper) observed in the drill dataset. The domain geometries and orientations have been further refined through integration of limited exploration drilling data and geophysical modelling (**Figure 3**). In this case, surface FLTEM data and modelled downhole EM conductor plates were used. Notably, recent drilling targeting these conductor plates has correlated strongly with the presence of copper, gold, zinc, and silver mineralisation¹⁰ (refer to ASX announcement dated 16th April 2025).

The combined geological, geochemical, and geophysical datasets provide a reasonable basis to extend mineralised domains beyond the limits of current drilling.

Grade interpolation was carried out using the Inverse Distance (ID) method, incorporating declustering. One metre (1 m) composites of copper and zinc assay intervals were used, with residual intervals (≥ 0.25 m) included in the preceding composite. Composites were constrained within hard boundaries for each domain. Interpolation parameters were informed by drillhole spacing, sample density, and the geometry of mineralised envelopes. Typically, 2–3 passes using expanding search ellipsoids were applied. A uniform bulk density value of 3.4 g/cm³ was applied, representing a mid-range estimate for this style of mineralisation.

To support estimation in areas lacking drill coverage, pseudo-drillholes were introduced. These were based on grade composites from drilled intervals and guided by interpreted continuity of mineralisation and geometry. A rotated block model (rotated 40 degrees to align with the mineralisation trend) was constructed using parent blocks of 20 m x 20 m x 5 m, with sub-blocks refined to 4 m x 4 m x 2 m.

The Exploration Target range was derived by applying a $\pm 20\%$ variation to tonnes and grade values, with corresponding metal endowment estimates calculated accordingly. QAQC review of the Company and historic drill data set has been validated & deemed suitable for this work.

⁷ Refer to ASX:GRE Announcement 5th May 2025

⁸ Refer to ASX:GRE Announcement 12th April 2023

⁹ Refer to ASX:GRE Announcement 11th May 2022

¹⁰ Refer to ASX:GRE Announcement 16th April 2025




Figure 3: FLTEM & DHTEM geophysical conductor anomalies have been used to assist with definition of domain trends which inform the Exploration Target Estimate

Mining Studies

A mining industry consultancy (Burnt Shirt Pty Ltd) has been engaged to evaluate various mining/processing scenarios to identifying a viable near-term mining operation and to ultimately complete a scoping study.

Historic Mining at Whundo

The Whundo Project is on a granted mining lease and has a previous history of open pit mining in more recent times at Whundo (East and West) ore shoots and limited historic underground mining. Details as follows;

- Following a feasibility study in 1975, open pit mining of Whundo (East) by Whim Creek Consolidated NL in 1976 yielded **6,200 tonnes** of supergene oxide ore at **26.98% Cu** during its one year of operation.
- Open-pit mining was undertaken by Fox Resources during 2006 and 2007, focused on the West Whundo deposit with **148,310 tonnes** of ore processed at Radio Hill processing plant and producing **25,812 tonnes** of copper concentrate at a grade of **20.86%**.
- In 2017, Artemis Resources (ASX: ARV) generated revenue through the sale of at surface mined ore which was heap leached at Whim Creek.
- There are historic records of intermittent underground production from mining leases at Yannery in the period 1920-1958 of **1,132 tonnes** of copper ore averaging **21% Cu**. Also, in the period 1951-1968 with a further **1,911.8 tonnes** of cupreous ore averaging **12.87% Cu** reported from the oxidised and supergene zone.

Next Steps

To target a significant expansion of the existing Whundo/Ayshia Mineral Resource¹¹ and where possible quantifying new resources as part of the next phase of drilling. Given the strong copper and gold prices the company is evaluating near-term opportunities for potential copper production from the Whundo project.

Drilling

Planning of the next drill program is underway which will focus on testing:

- For continuity of mineralisation between Austin and Shelby (EIS Co-funded)¹²
- Down plunge extent of the Ashyia shoot
- Shallow high grade oxide mineralisation at Yannery

The company will provide further details on drilling when plans are completed.

Conceptual Mine Study

- Completion of Mineral Resource Estimates for Whundo, Ayshia and Yannery incorporating gold
- Completion of Whittle optimisation for Whundo, Ayshia and Yannery
- Evaluating the economics of near-term production opportunities
- Further evaluation of the Radio Hill Processing site (**Figure 4**) as a processing option for Whundo

Mining Compliance

- Commence the application process for a mining permit




Figure 4: Regional Location of GreenTech's Whundo Copper Project and location of two processing sites at Radio Hill (Artemis) and Whim Creek (Anax)

This ASX announcement has been approved for release by the Board of GreenTech Metals Limited.

¹¹ Refer to GRE ASX Announcement 9 May 2024

¹² Government Sponsored Exploration Incentive Scheme

ENDS

For Further Information:

Mr Thomas Reddicliffe
Executive Director
GreenTech Metals Limited
+61 8 6261 5463

Mr Guy Robinson
Company Secretary
GreenTech Metals Limited
Info@greentechmetals.com

About GreenTech Metals Limited

The Company is an exploration and development company primarily established to discover, develop and acquire Australian and overseas projects containing minerals and metals that are used in the battery storage and electric vehicle sectors. The Company's founding projects are focused on the lithium, copper, nickel and cobalt potential within the West Pilbara and Fraser Range Provinces.

The green energy transition that is currently underway will require a substantial increase in the metals supply of these minerals and metals for the electrification of the global vehicle fleet and for the massive investment in the electrical grid and renewable energy infrastructure and storage.

Caution regarding Forward Looking Information

This document contains forward looking statements concerning GreenTech Metals Limited. Forward looking statements are not statements of historical fact and actual events and results may differ materially from those described in the forward-looking statements as a result of a variety of risks, uncertainties and other factors. Forward looking statements in this document are based on GreenTech's beliefs, opinions and estimates as of the dates the forward-looking statements are made, and no obligation is assumed to update forward looking statements if these beliefs, opinions or estimates should change or to reflect other future developments.

Competent Person Statement

Thomas Reddicliffe, BSc (Hons), MSc, a Director and Shareholder of the Company, is a Fellow of the AUSIMM, and has sufficient experience which is relevant to the style of mineralisation and type of deposit under consideration to qualify as a Competent Person as defined in the 2012 edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Thomas Reddicliffe consents to the inclusion in the report of the information in the form and context in which it appears.

The information in this report that relates to Exploration Results and Exploration Target was prepared/compiled by Mr Adrian Hell BSc (Hons), a Competent Person who is a member of the Australasian Institute of Mining and Metallurgy (MAusIMM). Mr Hell is full time employee for GreenTech Metals. Mr Hell has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity being undertaken to qualify as a Competent Person as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Mr Hell consents to the inclusion in this report of the matters based on his information in the form and context in which it appears.

Philip Alan Jones BAppSc (App. Geol), MAIG, MAusIMM is an Independent Consultant and Competent Person as defined by the JORC Code 2012 Edition, having more than five years of experience that is relevant to the style of mineralisation and type of deposit described in the Report and accepts responsibility for the activities he has undertaken and described with Respect to Mineral Resource Estimates. He is a Member of both the Australasian Institute of Mining and Metallurgy and the Australian Institute of Geoscientists. Phil Jones consents to the inclusion in the report of the information prepared by him in the form and context in which it appears.

No New Information

To the extent that this announcement contains references to prior exploration results and Mineral Resource Estimates for the Whundo project which have been cross referenced to previous market announcements made by the Company, unless explicitly stated, no new information is contained. The Company confirms that it is not aware of any new information or data that materially affects the information included in the relevant market announcements and, in the case of estimates of Mineral Resources, that all material assumptions and technical

parameters underpinning the estimates in the relevant market announcements continue to apply and have not materially changed.

ASX Announcements referred to in this report:

- ¹ Review confirms Whundo Copper Resource Potential, 9 May 2024 (ASX:GRE)
- ² Whundo Copper-Zinc Project Increases Resource Tonnes by 72%, 12 April 2023 (ASX:GRE)
- ³ Drill campaign aims to expand Whundo Cu Resources, 13 June 2024 (ASX:GRE)
- ⁴ Whundo Copper Results Indicate Significant Growth, 19 September 2024 (ASX:GRE)
- ⁵ Maiden JORC 2012 MRE at Ayshia Cu-Zn Deposit, 11 May 2022 (ASX:GRE)
- ⁶ Significant Gold at Whundo Enhances Economic Potential, 5 May 2025 (ASX:GRE)

Appendices

Table 5: Drill Collar Table for Exploration Target Area

Data Set	Lease	Hole_ID	Type	NAT_East	NAT_North	NAT_RL	Length	Dip	TNAzi	Company	Year
Whundo	M47/9	23GTRC011A	RC	493024	7669778	149.04	96	-74.1	325	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC009B	RC	492979	7669754	166.72	32	-60.5	2	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC009C	RC	492985	7669745	124	102	-75.3	346	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC011	RC	493024	7669779	149.89	31	-55.4	345	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC010	RC	493063	7669795	135.82	135	-56.2	269	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC009	RC	492983	7669752	163.59	43	-55.6	358	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC009A	RC	492982	7669752	164.39	72	-55.6	353	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC004	RC	492993	7669724	141.57	30	-85.8	262	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC005	RC	492999	7669760	137.51	5	-90.0	0	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC006	RC	493024	7669784	149.28	60	-87.4	214	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC007	RC	493068	7669795	132.89	24	-86.4	230	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC008	RC	493067	7669820	131.72	24	-88.7	243	Green Tech Metals Ltd	2023
Whundo	M47/7	23GTRC001	RC	492280	7669325	82.07	277	-80.1	200	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC002	RC	492995	7669755	152.39	24	-55.5	359	Green Tech Metals Ltd	2023
Whundo	M47/9	23GTRC003	RC	492996	7669743	152.93	48	-86.6	278	Green Tech Metals Ltd	2023
Whundo	M47/7	22GTRC034	RC	492735	7669676	100.11	450	-79.7	184	Green Tech Metals Ltd	2022
Whundo	M47/7	AWRC087	RC	492909	7669867	108.5	100	-60.4	92	Green Tech Metals Ltd	2018
Whundo	M47/7	AWRC077	RC	492939	7669866	114.47	100	-60.4	90	Green Tech Metals Ltd	2018
Whundo	M47/7	AWRC075	RC	492899	7669829	108.08	114	-59.3	87	Green Tech Metals Ltd	2018
Whundo	M47/7	12AYDD105	DD	493231	7670647	100.11	423.6	-68.4	152	Green Tech Metals Ltd	2012
Whundo	M47/9	98WDRC014	RC	493073	7669800	126.58	80	-60.0	90	Straits (Whim Creek) P/L	1998
Whundo	M47/9	98WDRC015	RC	493057	7669780	135.26	51	-62.0	70	Straits (Whim Creek) P/L	1998
Whundo	M47/9	98WDRC016	RC	493019	7669775	141.28	51	-75.0	65	Straits (Whim Creek) P/L	1998
Whundo	M47/9	98WDRC017	RC	493003	7669762	138.5	80	-60.0	70	Straits (Whim Creek) P/L	1998
Whundo	M47/9	98WDRC018	RC	492969	7669754	145	86	-60.0	50	Straits (Whim Creek) P/L	1998
Whundo	M47/7	P6	PER	493558	7670176	107.82	30.48	-90.0	0		1972
Whundo	M47/7	P7	PER	493527	7670176	107.02	28.96	-90.0	0		1972
Whundo	M47/7	P74	PER	493028	7669601	120.68	36.58	-90.0	0		1972
Whundo	M47/7	P75	PER	493039	7669571	125.22	35.05	-90.0	0		1972
Whundo	M47/7	P76	PER	493043	7669651	123.38	35.05	-90.0	0		1972
Whundo	M47/7	P8	PER	493497	7670176	106.43	30.48	-90.0	0		1972
Whundo	M47/7	P80	PER	493074	7669545	130	59.44	-90.0	0		1972
Whundo	M47/9	P81	PER	492986	7669841	140.4	76.2	-90.0	0		1972
Whundo	M47/9	P82	PER	492952	7669837	135.02	60.96	-90.0	0		1972
Whundo	M47/9	P83	PER	493011	7669858	141.9	54.86	-90.0	0		1972
Whundo	M47/7	24GTRC001	RC	492280	7669325	100.95	372	-80.0	195	GreenTech Metals Ltd	2024
Whundo	M47/7	24GTRC002	RC	492670	7669655	102.19	153	-83.0	40	GreenTech Metals Ltd	2024
Whundo	M47/7	24GTRC003	RC	492670	7669665	102.19	192	-85.0	60	GreenTech Metals Ltd	2024
Whundo	M47/7	24GTRC004	RC	493360	7670505	116.53	378	-80.0	160	GreenTech Metals Ltd	2024
Whundo	M47/7	24GTRC005	RC	492691	7669753	102.1	648	-85.0	160	GreenTech Metals Ltd	2024
Whundo	M47/7	25GTDD001	DD	492622	7670007	107.03	815.7	-67.0	162	GreenTech Metals Ltd	2025
Whundo	M47/7	25GTDD002	DD	492192	7669413	99.89	371.4	-66.0	134	GreenTech Metals Ltd	2025

Table 6: Drill Hole Sample Assays – Cu, Zn, Au and Ag

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
12AYDD105	368.00	368.65	FXA19675	0.0100	0.0128	0.0005	0.250
12AYDD105	368.65	369.00	FXA19676	0.0035	0.0154	0.0005	0.250
12AYDD105	369.00	370.00	FXA19677	0.0100	0.0123	0.0005	0.250
12AYDD105	370.00	371.00	FXA19678	0.0061	0.0133	0.0005	0.250
12AYDD105	371.00	372.00	FXA19679	0.0060	0.0261	0.0005	0.250
12AYDD105	372.00	373.00	FXA19680	0.0100	0.0172	0.0005	0.250
12AYDD105	373.00	374.00	FXA19681	0.0062	0.0288	0.0005	0.500
12AYDD105	374.00	374.70	FXA19682	0.0200	0.0601	0.0005	0.250
12AYDD105	374.70	375.60	FXA19683	0.4400	0.0575	0.0600	3.400
12AYDD105	375.60	376.70	FXA19684	0.0400	0.0468	0.0700	0.250
12AYDD105	376.70	377.45	FXA19685	0.0100	0.1750	0.0005	0.250
12AYDD105	377.45	378.05	FXA19686	0.0100	0.1020	0.0005	0.250
12AYDD105	378.05	379.00	FXA19688	0.0500	0.0799	0.0005	0.250
12AYDD105	379.00	379.60	FXA19689	0.0200	0.0591	0.0005	0.250
12AYDD105	379.60	380.65	FXA19690	0.0100	0.0557	0.0005	0.250
12AYDD105	380.65	381.65	FXA19691	0.2900	0.0422	0.0200	1.500
12AYDD105	381.65	382.70	FXA19692	0.0600	0.0304	0.0100	0.250
12AYDD105	382.70	383.00	FXA19693	0.0100	0.0262	0.0005	0.250
12AYDD105	383.00	384.00	FXA19694	0.0039	0.0144	0.0005	0.250
12AYDD105	384.00	385.00	FXA19695	0.0300	0.0098	0.0100	0.250
12AYDD105	385.00	386.00	FXA19696	0.0100	0.0082	0.0005	0.250
12AYDD105	386.00	387.00	FXA19697	0.0026	0.0049	0.0005	0.250
12AYDD105	387.00	388.00	FXA19698	0.0019	0.0051	0.0100	0.250
12AYDD105	388.00	388.70	FXA19699	0.0200	0.0047	0.0005	0.250
12AYDD105	388.70	389.20	FXA19700	0.1870	0.0066	0.0100	0.250
12AYDD105	389.20	390.20	FXA19701	0.3700	0.0093	0.0100	0.700
12AYDD105	390.20	391.30	FXA19702	0.0100	0.0058	0.0005	0.250
12AYDD105	391.30	392.15	FXA19703	0.1200	0.0120	0.0005	0.250
12AYDD105	392.15	393.00	FXA19705	0.0700	0.0177	0.0005	0.250
12AYDD105	393.00	393.90	FXA19706	0.0400	0.0186	0.0005	0.250
12AYDD105	393.90	394.50	FXA19707	0.0100	0.0139	0.0005	0.250
12AYDD105	394.50	394.80	FXA19708	0.0100	0.0095	0.0005	0.250
12AYDD105	394.80	395.40	FXA19709	0.0200	0.0125	0.0005	0.250
12AYDD105	395.40	396.40	FXA19710	0.0011	0.0205	0.0005	0.250
12AYDD105	396.40	397.30	FXA19711	0.0043	0.0193	0.0005	0.250
12AYDD105	397.30	398.30	FXA19712	0.0020	0.0184	0.0005	0.250
12AYDD105	398.30	399.30	FXA19713	0.0200	0.0282	0.0005	0.250
12AYDD105	399.30	400.30	FXA19714	0.0200	0.0607	0.0100	0.250
12AYDD105	400.30	401.15	FXA19715	0.0100	0.0449	0.0005	0.250
12AYDD105	401.15	402.00	FXA19716	0.0051	0.0225	0.0005	0.250
12AYDD105	402.00	402.90	FXA19717	0.0027	0.0280	0.0005	0.250
12AYDD105	402.90	403.50	FXA19718	0.0041	0.0151	0.0005	0.250
12AYDD105	403.50	404.50	FXA19719	0.0100	0.0243	0.0005	0.250
12AYDD105	404.50	405.50	FXA19720	0.0023	0.0175	0.0005	0.250
12AYDD105	405.50	406.45	FXA19721	0.0011	0.0139	0.0005	0.250
12AYDD105	406.45	407.05	FXA19723	0.0200	0.0050	0.0300	1.400
12AYDD105	407.05	408.00	FXA19724	0.0031	0.0091	0.0005	0.250
12AYDD105	408.00	409.00	FXA19725	0.0100	0.0090	0.0005	0.250
12AYDD105	409.00	410.00	FXA19726	0.0020	0.0092	0.0005	0.250
22GTRC034	300.00	303.00	WHO1463	0.0011	0.0073	0.0100	0.250
22GTRC034	303.00	306.00	WHO1464	0.0027	0.0161	0.0100	0.250
22GTRC034	306.00	309.00	WHO1465	0.0034	0.0091	0.0100	0.250
22GTRC034	309.00	312.00	WHO1466	0.0008	0.0073	0.0100	0.250
22GTRC034	312.00	315.00	WHO1467	0.0039	0.0077	0.0100	0.250
22GTRC034	315.00	318.00	WHO1468	0.0026	0.0084	0.0100	0.250
22GTRC034	318.00	321.00	WHO1469	0.0055	0.0079	0.0100	0.250
22GTRC034	321.00	324.00	WHO1471	0.0024	0.0098	0.0100	0.250
22GTRC034	324.00	327.00	WHO1472	0.0075	0.0125	0.0100	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
22GTRC034	327.00	330.00	WHO1473	0.0042	0.0152	0.0100	0.250
22GTRC034	330.00	333.00	WHO1474	0.0028	0.0134	0.0100	0.250
22GTRC034	333.00	336.00	WHO1475	0.0011	0.0137	0.0100	0.250
22GTRC034	336.00	339.00	WHO1476	0.0012	0.0134	0.0100	0.250
22GTRC034	339.00	342.00	WHO1477	0.0031	0.0162	0.0100	0.250
22GTRC034	342.00	343.00	GTR7711	0.0004	0.0135	0.0100	0.250
22GTRC034	343.00	344.00	GTR7712	0.0136	0.0229	0.0100	0.250
22GTRC034	344.00	345.00	GTR7713	0.0252	0.1655	0.0100	0.250
22GTRC034	345.00	346.00	GTR7714	0.0123	0.3220	0.0100	0.250
22GTRC034	346.00	347.00	GTR7715	0.0169	0.1105	0.0100	0.250
22GTRC034	347.00	348.00	GTR7716	0.0089	0.0657	0.0100	0.250
22GTRC034	348.00	351.00	WHO1478	0.0120	0.0385	0.0100	0.250
22GTRC034	351.00	354.00	WHO1479	0.0003	0.0140	0.0100	0.250
22GTRC034	354.00	357.00	WHO1481	0.0016	0.0133	0.0100	0.250
22GTRC034	357.00	360.00	WHO1482	0.0007	0.0142	0.0100	0.250
22GTRC034	360.00	363.00	WHO1483	0.0001	0.0132	0.0100	0.250
22GTRC034	363.00	366.00	WHO1484	0.0024	0.0098	0.0100	0.250
22GTRC034	366.00	369.00	WHO1485	0.0082	0.0086	0.0100	0.250
22GTRC034	369.00	372.00	WHO1486	0.0062	0.0079	0.0100	0.250
22GTRC034	372.00	375.00	WHO1487	0.0030	0.0118	0.0100	0.250
22GTRC034	375.00	378.00	WHO1488	0.0202	0.0139	0.0100	0.250
22GTRC034	378.00	381.00	WHO1489	0.0097	0.0184	0.0100	0.250
22GTRC034	381.00	384.00	WHO1491	0.0151	0.0180	0.0100	0.250
22GTRC034	384.00	387.00	WHO1492	0.0074	0.0187	0.0100	0.250
22GTRC034	387.00	390.00	WHO1493	0.0011	0.0225	0.0100	0.250
22GTRC034	390.00	393.00	WHO1494	0.0001	0.0199	0.0100	0.250
22GTRC034	393.00	396.00	WHO1495	0.0001	0.0138	0.0100	0.250
22GTRC034	396.00	399.00	WHO1496	0.0001	0.0120	0.0100	0.250
22GTRC034	399.00	402.00	WHO1497	0.0001	0.0120	0.0100	0.250
22GTRC034	402.00	405.00	WHO1498	0.0001	0.0141	0.0100	0.250
22GTRC034	405.00	408.00	WHO1499	0.0001	0.0175	0.0100	0.250
22GTRC034	408.00	411.00	WHO1501	0.0003	0.0285	0.0100	0.250
22GTRC034	411.00	414.00	WHO1502	0.0001	0.0262	0.0100	0.250
22GTRC034	414.00	415.00	GTR7791	0.0004	0.0537	0.0100	0.250
22GTRC034	415.00	416.00	GTR7792	0.0003	0.0575	0.0100	0.250
22GTRC034	416.00	417.00	GTR7793	0.0004	0.1075	0.0100	0.250
22GTRC034	417.00	418.00	GTR7794	0.2230	0.2720	0.0100	0.250
22GTRC034	418.00	419.00	GTR7795	0.8280	0.1465	0.2200	2.200
22GTRC034	419.00	420.00	GTR7796	0.9020	0.1015	0.0500	1.500
22GTRC034	420.00	421.00	GTR7797	1.1200	0.2190	0.0300	2.100
22GTRC034	421.00	422.00	GTR7798	0.1075	0.1540	0.0100	0.250
22GTRC034	422.00	423.00	GTR7799	0.0384	0.0737	0.0100	0.250
22GTRC034	423.00	424.00	GTR7801	0.0374	0.0839	0.0200	0.250
22GTRC034	424.00	425.00	GTR7802	0.0266	0.0736	0.0100	0.250
22GTRC034	425.00	426.00	GTR7803	0.0241	0.0756	0.0100	0.250
22GTRC034	426.00	427.00	GTR7804	0.0038	0.0579	0.0100	0.250
22GTRC034	427.00	428.00	GTR7805	0.0020	0.0679	0.0100	0.250
22GTRC034	428.00	429.00	GTR7806	1.3500	0.1080	0.3900	3.200
22GTRC034	429.00	430.00	GTR7807	0.5500	0.0720	0.8900	1.400
22GTRC034	430.00	431.00	GTR7808	2.0000	0.1585	0.3500	3.700
22GTRC034	431.00	432.00	GTR7809	1.3550	0.1080	0.8800	4.100
22GTRC034	432.00	435.00	WHO1503	0.0027	0.0528	0.0100	0.250
22GTRC034	435.00	438.00	WHO1504	0.0014	0.0353	0.0100	0.250
22GTRC034	438.00	441.00	WHO1505	0.0006	0.0105	0.0100	0.250
22GTRC034	441.00	444.00	WHO1506	0.0004	0.0083	0.0100	0.250
22GTRC034	444.00	447.00	WHO1507	0.0010	0.0105	0.0100	0.250
22GTRC034	447.00	450.00	WHO1508	0.0003	0.0102	0.0100	0.250
23GTRC001	0.00	3.00	WHO1547	0.0030	0.0120	0.0100	0.250
23GTRC001	3.00	6.00	WHO1548	0.0027	0.0227	0.0100	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC001	6.00	9.00	WHO1549	0.0024	0.0228	0.0100	0.250
23GTRC001	9.00	12.00	WHO1551	0.0030	0.0195	0.0100	0.250
23GTRC001	12.00	15.00	WHO1552	0.0008	0.0145	0.0100	0.250
23GTRC001	15.00	18.00	WHO1553	0.0005	0.0156	0.0100	0.250
23GTRC001	18.00	21.00	WHO1554	0.0008	0.0213	0.0100	0.250
23GTRC001	21.00	24.00	WHO1555	0.0002	0.0151	0.0100	0.250
23GTRC001	24.00	27.00	WHO1556	0.0006	0.0206	0.0100	0.250
23GTRC001	27.00	30.00	WHO1557	0.0004	0.0166	0.0100	0.250
23GTRC001	30.00	33.00	WHO1558	0.0028	0.0401	0.0100	0.250
23GTRC001	33.00	34.00	GTM5822	0.0013	0.0262	0.0100	0.250
23GTRC001	34.00	35.00	GTM5823	0.0005	0.0240	0.0100	0.250
23GTRC001	35.00	36.00	GTM5824	0.0013	0.0445	0.0100	0.250
23GTRC001	36.00	37.00	GTM5825	0.0033	0.0465	0.0100	0.250
23GTRC001	37.00	38.00	GTM5826	0.0071	0.1435	0.0100	0.500
23GTRC001	38.00	39.00	GTM5827	0.0019	0.0349	0.0200	0.250
23GTRC001	39.00	40.00	GTM5828	0.0006	0.0255	0.0100	0.250
23GTRC001	40.00	41.00	GTM5829	0.0021	0.0412	0.0100	0.250
23GTRC001	41.00	42.00	GTM5831	0.0121	0.1195	0.0100	0.500
23GTRC001	42.00	43.00	GTM5832	0.0194	0.2090	0.0100	0.600
23GTRC001	43.00	44.00	GTM5833	0.0092	0.2650	0.0100	0.500
23GTRC001	44.00	45.00	GTM5834	0.0005	0.0308	0.0100	0.250
23GTRC001	45.00	46.00	GTM5835	0.0004	0.0364	0.0100	0.250
23GTRC001	46.00	47.00	GTM5836	0.0007	0.0297	0.0100	0.250
23GTRC001	47.00	48.00	GTM5837	0.0006	0.0410	0.0100	0.250
23GTRC001	48.00	49.00	GTM5838	0.0111	0.1330	0.0100	0.600
23GTRC001	49.00	50.00	GTM5839	0.0068	0.0628	0.0100	0.250
23GTRC001	50.00	51.00	GTM5841	0.0023	0.0262	0.0100	0.250
23GTRC001	51.00	53.00	WHO1559	0.0028	0.0459	0.0100	0.250
23GTRC001	53.00	54.00	GTM5844	0.0042	0.0551	0.0100	0.250
23GTRC001	54.00	55.00	GTM5845	0.0023	0.0500	0.0100	0.250
23GTRC001	55.00	56.00	GTM5846	0.0006	0.0988	0.0100	0.250
23GTRC001	56.00	57.00	GTM5847	0.0004	0.0443	0.0100	0.250
23GTRC001	57.00	58.00	GTM5848	0.0002	0.0218	0.0100	0.250
23GTRC001	58.00	61.00	WHO1561	0.0002	0.0170	0.0100	0.250
23GTRC001	61.00	64.00	WHO1562	0.0008	0.0155	0.0100	0.250
23GTRC001	64.00	67.00	WHO1563	0.0001	0.0119	0.0100	0.250
23GTRC001	67.00	70.00	WHO1564	0.0004	0.0127	0.0100	0.250
23GTRC001	70.00	73.00	WHO1565	0.0001	0.0086	0.0100	0.250
23GTRC001	73.00	76.00	WHO1566	0.0001	0.0093	0.0100	0.250
23GTRC001	76.00	79.00	WHO1567	0.0001	0.0133	0.0100	0.250
23GTRC001	79.00	82.00	WHO1568	0.0033	0.0307	0.0100	0.250
23GTRC001	82.00	85.00	WHO1569	0.0027	0.0262	0.0100	0.250
23GTRC001	85.00	88.00	WHO1571	0.0012	0.0286	0.0100	0.250
23GTRC001	88.00	91.00	WHO1572	0.0017	0.0212	0.0100	0.250
23GTRC001	91.00	94.00	WHO1573	0.0048	0.0162	0.0100	0.250
23GTRC001	94.00	97.00	WHO1574	0.0044	0.0206	0.0400	0.250
23GTRC001	97.00	100.00	WHO1575	0.0053	0.0204	0.0100	0.250
23GTRC001	100.00	103.00	WHO1576	0.0074	0.0198	0.0100	0.250
23GTRC001	103.00	106.00	WHO1577	0.0039	0.0195	0.0100	0.250
23GTRC001	106.00	109.00	WHO1578	0.0021	0.0082	0.0100	0.250
23GTRC001	109.00	112.00	WHO1579	0.0039	0.0126	0.0100	0.250
23GTRC001	112.00	115.00	WHO1581	0.0025	0.0137	0.0100	0.250
23GTRC001	115.00	118.00	WHO1582	0.0133	0.0194	0.0100	0.250
23GTRC001	118.00	121.00	WHO1583	0.0052	0.0213	0.0100	0.250
23GTRC001	121.00	124.00	WHO1584	0.0020	0.0220	0.0100	0.250
23GTRC001	124.00	127.00	WHO1585	0.0098	0.0168	0.0100	0.250
23GTRC001	127.00	130.00	WHO1586	0.0024	0.0124	0.0100	0.250
23GTRC001	130.00	133.00	WHO1587	0.0026	0.0132	0.0100	0.250
23GTRC001	133.00	136.00	WHO1588	0.0105	0.0167	0.0100	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC001	136.00	139.00	WHO1589	0.0038	0.0112	0.0100	0.250
23GTRC001	139.00	142.00	WHO1591	0.0027	0.0102	0.0100	0.250
23GTRC001	142.00	145.00	WHO1592	0.0107	0.0124	0.0100	0.250
23GTRC001	145.00	148.00	WHO1593	0.0140	0.0139	0.0100	0.250
23GTRC001	148.00	150.00	WHO1594	0.0181	0.0134	0.0100	0.250
23GTRC001	150.00	153.00	WHO1595	0.0091	0.0142	0.0100	0.250
23GTRC001	153.00	156.00	WHO1596	0.0032	0.0152	0.0100	0.250
23GTRC001	156.00	159.00	WHO1597	0.0051	0.0149	0.0100	0.250
23GTRC001	159.00	162.00	WHO1598	0.0010	0.0124	0.0100	0.250
23GTRC001	162.00	165.00	WHO1599	0.0076	0.0114	0.0100	0.250
23GTRC001	165.00	168.00	WHO1601	0.0201	0.0101	0.0100	0.250
23GTRC001	168.00	171.00	WHO1602	0.0102	0.0133	0.0100	0.250
23GTRC001	171.00	174.00	WHO1603	0.0044	0.0262	0.0100	0.250
23GTRC001	174.00	176.00	WHO1604	0.0062	0.1155	0.0100	0.250
23GTRC001	176.00	177.00	GTM5981	0.0024	0.0554	0.0100	0.250
23GTRC001	177.00	178.00	GTM5982	0.0268	0.0473	0.0100	0.250
23GTRC001	178.00	179.00	GTM5983	0.0542	0.0457	0.0100	0.600
23GTRC001	179.00	180.00	GTM5984	0.0905	0.0535	0.1300	2.100
23GTRC001	180.00	181.00	GTM5985	0.0362	0.0467	0.0200	0.250
23GTRC001	181.00	182.00	GTM5986	0.0083	0.0345	0.0100	0.250
23GTRC001	182.00	185.00	WHO1605	0.0106	0.0129	0.0100	0.250
23GTRC001	185.00	188.00	WHO1606	0.0025	0.0052	0.0100	0.250
23GTRC001	188.00	191.00	WHO1607	0.0045	0.0074	0.0100	0.250
23GTRC001	191.00	194.00	WHO1608	0.0015	0.0111	0.0100	0.250
23GTRC001	194.00	197.00	WHO1609	0.0068	0.0077	0.0100	0.250
23GTRC001	197.00	200.00	WHO1611	0.0073	0.0091	0.0100	0.250
23GTRC001	200.00	203.00	WHO1612	0.0015	0.0066	0.0100	0.250
23GTRC001	203.00	206.00	WHO1613	0.0026	0.0050	0.0100	0.250
23GTRC001	206.00	208.00	WHO1614	0.0039	0.0044	0.0100	0.250
23GTRC001	208.00	210.00	WHO1615	0.0098	0.0066	0.0100	0.250
23GTRC001	210.00	211.00	GTM6518	0.0130	0.0075	0.0100	0.250
23GTRC001	211.00	212.00	GTM6519	0.0028	0.0121	0.0100	0.250
23GTRC001	212.00	213.00	GTM6521	0.0028	0.0092	0.0100	0.250
23GTRC001	213.00	214.00	GTM6522	0.0046	0.0126	0.0100	0.250
23GTRC001	214.00	217.00	WHO1616	0.0049	0.0085	0.0100	0.250
23GTRC001	217.00	220.00	WHO1617	0.0016	0.0092	0.0100	0.250
23GTRC001	220.00	222.00	WHO1618	0.0002	0.0260	0.0100	0.250
23GTRC001	222.00	224.00	WHO1619	0.0055	0.0365	0.0100	0.250
23GTRC001	224.00	225.00	GTM6534	0.0099	0.0365	0.0100	0.250
23GTRC001	225.00	226.00	GTM6535	0.1175	0.0429	0.0100	0.250
23GTRC001	226.00	227.00	GTM6536	5.4000	0.5720	0.0700	10.000
23GTRC001	227.00	228.00	GTM6537	0.9000	0.1045	0.0500	1.400
23GTRC001	228.00	229.00	GTM6538	0.9290	0.0826	0.0300	0.900
23GTRC001	229.00	230.00	GTM6539	1.1000	0.2010	0.0200	0.900
23GTRC001	230.00	231.00	GTM6541	2.0000	0.9130	0.0300	2.300
23GTRC001	231.00	232.00	GTM6542	1.4050	0.2780	0.0200	1.200
23GTRC001	232.00	233.00	GTM6543	1.3600	0.1730	0.0800	1.500
23GTRC001	233.00	234.00	GTM6544	0.2770	0.1150	0.0200	0.250
23GTRC001	234.00	235.00	GTM6545	0.2580	0.1260	0.0100	0.250
23GTRC001	235.00	236.00	GTM6546	0.0442	0.0680	0.0100	0.250
23GTRC001	236.00	237.00	GTM6547	0.2800	0.0359	0.0400	0.500
23GTRC001	237.00	238.00	GTM6548	0.1460	0.0390	0.0200	0.250
23GTRC001	238.00	239.00	GTM6549	0.1680	0.0247	0.0100	0.250
23GTRC001	239.00	240.00	GTM6551	0.2040	0.0171	0.0200	0.250
23GTRC001	240.00	241.00	GTM6552	0.0820	0.0158	0.0100	0.250
23GTRC001	241.00	242.00	GTM6553	0.0518	0.0171	0.0100	0.250
23GTRC001	242.00	243.00	GTM6554	0.3920	0.0181	0.0200	0.800
23GTRC001	243.00	244.00	GTM6555	0.0210	0.0176	0.0100	0.250
23GTRC001	244.00	245.00	GTM6556	0.0074	0.0136	0.0100	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC001	245.00	248.00	WHO1621	0.0065	0.0100	0.0100	0.250
23GTRC001	248.00	251.00	WHO1622	0.0176	0.0091	0.0100	0.250
23GTRC001	251.00	254.00	WHO1623	0.0007	0.0116	0.0100	0.250
23GTRC001	254.00	257.00	WHO1624	0.0029	0.0124	0.0100	0.250
23GTRC001	257.00	260.00	WHO1625	0.0010	0.0085	0.0100	0.250
23GTRC001	260.00	263.00	WHO1626	0.0029	0.0082	0.0100	0.250
23GTRC001	263.00	266.00	WHO1627	0.0010	0.0112	0.0100	0.250
23GTRC001	266.00	269.00	WHO1628	0.0009	0.0094	0.0100	0.250
23GTRC001	270.00	272.00	WHO1629	0.0005	0.0072	0.0100	0.250
23GTRC001	272.00	275.00	WHO1631	0.0061	0.0067	0.0100	0.250
23GTRC001	275.00	277.00	WHO1632	0.0020	0.0103	0.0100	0.250
23GTRC002	0.00	1.00	GTM6593	0.5660	0.0962	0.0200	0.250
23GTRC002	1.00	2.00	GTM6594	0.9750	0.1955	0.0100	0.250
23GTRC002	2.00	3.00	GTM6595	1.4350	0.2490	0.0100	0.250
23GTRC002	3.00	4.00	GTM6596	1.4500	0.1725	0.0100	0.250
23GTRC002	4.00	5.00	GTM6597	0.9640	0.1145	0.0100	0.250
23GTRC002	5.00	6.00	GTM6598	0.8940	0.1160	0.0100	0.250
23GTRC002	6.00	7.00	GTM6599	0.7390	0.1985	0.0100	0.250
23GTRC002	7.00	8.00	GTM6601	0.4510	0.0894	0.0100	0.250
23GTRC002	8.00	9.00	GTM6602	0.0669	0.0536	0.0100	0.250
23GTRC002	9.00	10.00	GTM6603	0.1340	0.0378	0.0100	0.250
23GTRC002	10.00	11.00	GTM6604	0.0952	0.0379	0.0100	0.250
23GTRC002	11.00	12.00	GTM6605	0.8550	0.0827	0.0100	0.250
23GTRC002	12.00	13.00	GTM6606	0.5980	0.0610	0.0100	0.250
23GTRC002	13.00	14.00	GTM6607	0.2770	0.0150	0.0100	0.250
23GTRC002	14.00	15.00	GTM6608	0.3150	0.0069	0.0100	0.600
23GTRC002	15.00	16.00	GTM6609	0.2680	0.0036	0.0200	0.800
23GTRC002	16.00	17.00	GTM6611	0.1435	0.0024	0.0400	1.000
23GTRC002	17.00	18.00	GTM6612	0.1700	0.0028	0.0200	0.700
23GTRC002	18.00	19.00	GTM6613	0.2260	0.0054	0.1300	0.800
23GTRC002	19.00	20.00	GTM6614	0.0533	0.0027	0.0800	0.250
23GTRC002	20.00	21.00	GTM6615	0.1580	0.0054	0.0600	0.250
23GTRC002	21.00	22.00	GTM6616	0.0706	0.0040	0.1000	1.200
23GTRC002	22.00	23.00	GTM6617	0.0586	0.0051	0.0100	0.250
23GTRC003	0.00	1.00	GTM6619	0.0699	0.0039	0.0600	1.900
23GTRC003	1.00	2.00	GTM6621	0.0543	0.0073	0.0500	2.400
23GTRC003	2.00	3.00	GTM6622	0.0415	0.0053	0.0500	3.300
23GTRC003	3.00	4.00	GTM6623	0.1280	0.0208	0.2100	2.400
23GTRC003	4.00	5.00	GTM6624	0.2740	0.0600	0.0700	1.700
23GTRC003	5.00	6.00	GTM6625	0.2500	0.0728	0.0500	1.400
23GTRC003	6.00	7.00	GTM6626	0.1040	0.0620	0.0400	0.250
23GTRC003	7.00	8.00	GTM6627	0.0901	0.0425	0.0300	0.250
23GTRC003	8.00	9.00	GTM6628	0.0827	0.0436	0.0200	0.250
23GTRC003	9.00	10.00	GTM6629	0.0712	0.0391	0.0100	0.250
23GTRC003	10.00	11.00	GTM6631	0.3070	0.0314	0.0100	0.250
23GTRC003	11.00	12.00	GTM6632	0.5440	0.0315	0.0100	0.250
23GTRC003	12.00	13.00	GTM6633	0.0650	0.0203	0.0100	0.250
23GTRC003	13.00	14.00	GTM6634	0.0671	0.0167	0.0100	0.250
23GTRC003	14.00	15.00	GTM6635	0.1010	0.0205	0.0100	0.250
23GTRC003	15.00	16.00	GTM6636	0.1100	0.0186	0.0100	0.250
23GTRC003	16.00	17.00	GTM6637	0.1015	0.0190	0.0100	0.250
23GTRC003	17.00	18.00	GTM6638	0.0561	0.0150	0.0100	0.250
23GTRC003	18.00	19.00	GTM6639	0.0340	0.0121	0.0100	0.250
23GTRC003	19.00	21.00	WHO1633	0.0181	0.0097	0.0100	0.250
23GTRC003	21.00	23.00	WHO1634	0.0743	0.0204	0.0100	0.250
23GTRC003	23.00	24.00	GTM6645	0.0511	0.0213	0.0100	0.250
23GTRC003	24.00	25.00	GTM6646	0.0716	0.0272	0.0100	0.250
23GTRC003	25.00	26.00	GTM6647	0.2490	0.0510	0.0100	0.800
23GTRC003	26.00	27.00	GTM6648	0.0897	0.0646	0.0100	1.700

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC003	27.00	28.00	GTM6649	0.0219	0.0606	0.0100	0.800
23GTRC003	28.00	31.00	WHO1635	0.0147	0.0648	0.0100	0.600
23GTRC003	31.00	34.00	WHO1636	0.0076	0.0242	0.0100	0.250
23GTRC003	34.00	37.00	WHO1637	0.0065	0.0228	0.0100	0.250
23GTRC003	37.00	40.00	WHO1638	0.0031	0.0312	0.0100	0.250
23GTRC003	40.00	42.00	WHO1639	0.0055	0.0331	0.0100	0.250
23GTRC003	44.00	46.00	WHO1642	0.0022	0.0584	0.0100	0.250
23GTRC003	46.00	48.00	WHO1643	0.0042	0.0395	0.0100	0.500
23GTRC004	0.00	3.00	WHO1644	0.0116	0.0122	0.0100	0.250
23GTRC004	3.00	6.00	WHO1645	0.0164	0.0121	0.0100	0.250
23GTRC004	6.00	9.00	WHO1646	0.0254	0.0162	0.0100	0.250
23GTRC004	9.00	12.00	WHO1647	0.0209	0.0174	0.0100	0.250
23GTRC004	12.00	13.00	GTM6686	0.0206	0.0233	0.0100	0.250
23GTRC004	13.00	14.00	GTM6687	0.0265	0.0242	0.0100	0.250
23GTRC004	14.00	15.00	GTM6688	0.0473	0.0346	0.0100	0.250
23GTRC004	15.00	16.00	GTM6689	0.1090	0.0410	0.0100	0.250
23GTRC004	16.00	17.00	GTM6690	0.1210	0.0678	0.0100	0.250
23GTRC004	17.00	18.00	GTM6692	0.0487	0.0351	0.0100	0.250
23GTRC004	18.00	19.00	GTM6693	0.0342	0.0177	0.0100	0.250
23GTRC004	19.00	20.00	GTM6694	0.0802	0.0302	0.0100	0.250
23GTRC004	20.00	21.00	GTM6695	0.2000	0.0300	0.0100	0.250
23GTRC004	21.00	22.00	GTM6696	0.0053	0.0198	0.0100	0.250
23GTRC004	22.00	23.00	GTM6697	0.0044	0.0192	0.0100	0.250
23GTRC004	23.00	24.00	GTM6698	0.0075	0.0583	0.0100	0.250
23GTRC004	24.00	27.00	WHO1648	0.0047	0.0596	0.0100	0.250
23GTRC004	27.00	28.00	WHO1649	0.0073	0.0189	0.0100	0.250
23GTRC005	0.00	1.00	GTM6706	0.3260	0.0280	0.0300	0.250
23GTRC005	1.00	2.00	GTM6707	0.1475	0.0292	0.0200	0.250
23GTRC005	2.00	3.00	GTM6708	0.1785	0.0054	0.0100	0.500
23GTRC005	4.00	5.00	GTM6711	0.6980	0.0102	0.0100	0.800
23GTRC006	0.00	1.00	GTM6712	0.0893	0.0150	0.0100	0.250
23GTRC006	1.00	2.00	GTM6713	0.0209	0.0130	0.0100	0.250
23GTRC006	2.00	3.00	GTM6714	0.0185	0.0113	0.0100	0.250
23GTRC006	3.00	6.00	WHO1651	0.0066	0.0115	0.0100	0.250
23GTRC006	6.00	9.00	WHO1652	0.0383	0.0557	0.0100	0.250
23GTRC006	9.00	10.00	GTM6722	0.0352	0.0610	0.0100	0.250
23GTRC006	10.00	11.00	GTM6723	0.0560	0.0808	0.0100	0.250
23GTRC006	11.00	12.00	GTM6724	0.1475	0.0328	0.0500	0.900
23GTRC006	12.00	13.00	GTM6725	0.0914	0.0164	0.0500	2.800
23GTRC006	13.00	14.00	GTM6726	0.3010	0.0503	0.1700	4.800
23GTRC006	14.00	15.00	GTM6727	0.5160	0.0392	0.1700	6.400
23GTRC006	15.00	16.00	GTM6728	0.3880	0.0295	0.1300	8.800
23GTRC006	16.00	17.00	GTM6730	0.2280	0.0488	0.2300	5.000
23GTRC006	17.00	18.00	GTM6731	0.2700	0.0429	0.2000	4.400
23GTRC006	18.00	19.00	GTM6732	0.3940	0.0233	0.4400	11.300
23GTRC006	19.00	20.00	GTM6733	0.3310	0.0280	0.0900	0.900
23GTRC006	20.00	21.00	GTM6734	1.0550	0.0588	0.0200	0.800
23GTRC006	21.00	22.00	GTM6735	0.4420	0.0463	0.0100	0.700
23GTRC006	22.00	23.00	GTM6736	0.3930	0.0457	0.0100	0.500
23GTRC006	23.00	24.00	GTM6737	0.2210	0.0403	0.0200	0.600
23GTRC006	24.00	25.00	GTM6738	0.6750	0.0539	0.1400	3.400
23GTRC006	25.00	26.00	GTM6739	0.7050	0.0546	0.4000	3.200
23GTRC006	26.00	27.00	GTM6741	0.3310	0.0510	0.2800	6.400
23GTRC006	27.00	28.00	GTM6742	0.2460	0.0798	0.1900	1.600
23GTRC006	28.00	29.00	GTM6743	0.1985	0.0736	0.2000	2.200
23GTRC006	29.00	30.00	GTM6744	0.1830	0.0511	0.2900	3.200
23GTRC006	30.00	31.00	GTM6745	0.2800	0.0584	0.3600	2.400
23GTRC006	31.00	32.00	GTM6746	0.3030	0.0714	0.2500	2.300
23GTRC006	32.00	33.00	GTM6747	0.2260	0.0800	0.1600	1.000

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC006	33.00	34.00	GTM6748	0.4170	0.0763	0.1500	0.600
23GTRC006	34.00	35.00	GTM6749	0.3290	0.0566	0.0900	1.200
23GTRC006	35.00	36.00	GTM6751	0.2440	0.0644	0.0100	0.250
23GTRC006	36.00	37.00	GTM6752	0.2850	0.0308	0.0200	1.000
23GTRC006	37.00	38.00	GTM6753	0.3680	0.0138	0.0200	0.700
23GTRC006	38.00	39.00	GTM6754	0.3380	0.0117	0.0200	0.250
23GTRC006	39.00	40.00	GTM6755	0.4170	0.0160	0.0100	0.500
23GTRC006	40.00	41.00	GTM6756	1.0600	0.0329	0.0100	1.400
23GTRC006	41.00	42.00	GTM6757	0.7690	0.0125	0.0100	1.300
23GTRC006	42.00	43.00	GTM6758	1.4200	0.0222	0.0100	2.600
23GTRC006	43.00	44.00	GTM6759	1.4800	0.0267	0.0100	0.900
23GTRC006	44.00	45.00	GTM6761	1.1300	0.0236	0.0100	0.250
23GTRC006	45.00	46.00	GTM6762	0.2090	0.0187	0.0100	0.250
23GTRC006	46.00	47.00	GTM6763	0.0721	0.0104	0.0100	0.250
23GTRC006	47.00	48.00	GTM6764	0.0972	0.0100	0.0100	0.250
23GTRC006	48.00	49.00	GTM6765	0.1365	0.0095	0.0100	0.250
23GTRC006	49.00	50.00	GTM6766	0.0497	0.0048	0.0100	0.250
23GTRC006	50.00	51.00	GTM6767	0.0745	0.0056	0.0100	0.250
23GTRC006	51.00	52.00	GTM6768	0.0438	0.0058	0.0100	0.250
23GTRC006	52.00	53.00	GTM6769	0.2230	0.0082	0.0100	0.250
23GTRC006	53.00	54.00	GTM6771	0.0722	0.0064	0.0100	0.250
23GTRC006	54.00	55.00	GTM6772	0.2800	0.0103	0.0100	0.250
23GTRC006	55.00	56.00	GTM6773	0.0550	0.0058	0.0100	0.250
23GTRC006	56.00	57.00	GTM6774	0.1490	0.0073	0.0100	0.250
23GTRC006	57.00	58.00	GTM6775	0.0933	0.0083	0.0100	0.250
23GTRC006	58.00	59.00	GTM6776	0.1505	0.0093	0.0100	0.250
23GTRC006	59.00	60.00	GTM6777	0.0569	0.0097	0.0100	0.250
23GTRC007	0.00	1.00	GTM6778	0.1595	0.0768	0.0100	0.250
23GTRC007	1.00	2.00	GTM6779	0.0091	0.0119	0.0100	0.250
23GTRC007	2.00	3.00	GTM6781	0.0053	0.0084	0.0100	0.250
23GTRC007	3.00	6.00	WHO1653	0.0011	0.0182	0.0100	0.250
23GTRC007	6.00	9.00	WHO1654	0.0189	0.0289	0.0100	0.250
23GTRC007	9.00	12.00	WHO1655	0.0113	0.0229	0.0100	0.250
23GTRC007	12.00	15.00	WHO1656	0.0250	0.0270	0.0100	0.250
23GTRC007	15.00	16.00	GTM6795	0.0529	0.0304	0.0100	0.250
23GTRC007	16.00	17.00	GTM6796	0.2290	0.0324	0.0100	0.250
23GTRC007	17.00	18.00	GTM6797	0.2100	0.0306	0.0100	0.250
23GTRC007	18.00	19.00	GTM6798	0.0429	0.0318	0.0100	0.250
23GTRC007	19.00	20.00	GTM6799	0.0299	0.0276	0.0100	0.250
23GTRC007	20.00	22.00	WHO1657	0.0310	0.0304	0.0100	0.250
23GTRC007	22.00	24.00	WHO1658	0.0137	0.0255	0.0100	0.250
23GTRC008	0.00	3.00	WHO1659	0.0284	0.0252	0.0100	0.250
23GTRC008	3.00	4.00	GTM6808	0.0308	0.0235	0.0100	0.250
23GTRC008	4.00	5.00	GTM6809	0.0428	0.0286	0.0100	0.250
23GTRC008	5.00	6.00	GTM6811	0.1640	0.0188	0.0200	0.250
23GTRC008	6.00	7.00	GTM6812	0.0131	0.0102	0.0100	0.250
23GTRC008	7.00	8.00	GTM6813	0.0139	0.0103	0.0100	0.250
23GTRC008	8.00	11.00	WHO1661	0.0048	0.0079	0.0100	0.250
23GTRC008	11.00	14.00	WHO1662	0.0129	0.0132	0.0100	0.250
23GTRC008	14.00	17.00	WHO1663	0.0033	0.0121	0.0100	0.250
23GTRC008	17.00	20.00	WHO1664	0.0023	0.0139	0.0100	0.250
23GTRC008	20.00	22.00	WHO1665	0.0060	0.0116	0.0100	0.250
23GTRC008	22.00	24.00	WHO1666	0.0081	0.0156	0.0100	0.250
23GTRC009	0.00	3.00	WHO1667	0.0117	0.0053	0.0100	0.500
23GTRC009	3.00	6.00	WHO1668	0.0173	0.0018	0.0100	0.250
23GTRC009	6.00	7.00	GTM6838	0.0530	0.0054	0.0100	0.250
23GTRC009	7.00	8.00	GTM6839	0.0933	0.0087	0.0100	0.250
23GTRC009	8.00	9.00	GTM6841	0.1015	0.0108	0.0100	0.250
23GTRC009	9.00	10.00	GTM6842	0.1180	0.0168	0.0100	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC009	10.00	11.00	GTM6843	0.0700	0.0138	0.0100	0.250
23GTRC009	11.00	14.00	WHO1669	0.0283	0.0191	0.0100	0.250
23GTRC009	14.00	17.00	WHO1671	0.0513	0.0282	0.0100	0.250
23GTRC009	17.00	19.00	WHO1672	0.0336	0.0243	0.0100	0.250
23GTRC009	19.00	21.00	WHO1673	0.0090	0.0258	0.0100	0.250
23GTRC009	21.00	22.00	GTM6855	0.0125	0.0332	0.0100	0.250
23GTRC009	22.00	23.00	GTM6856	0.1785	0.0424	0.0100	0.250
23GTRC009	23.00	24.00	GTM6857	0.4370	0.0482	0.0100	0.250
23GTRC009	24.00	25.00	GTM6858	0.5530	0.0412	0.0100	0.250
23GTRC009	25.00	26.00	GTM6859	0.1975	0.0128	0.0100	0.250
23GTRC009	26.00	27.00	GTM6861	0.1100	0.0069	0.0100	0.250
23GTRC009	27.00	28.00	GTM6862	0.1060	0.0032	0.0100	0.250
23GTRC009	28.00	29.00	GTM6863	0.1210	0.0042	0.0100	0.250
23GTRC009	29.00	30.00	GTM6864	0.0711	0.0026	0.0100	0.250
23GTRC009	30.00	31.00	GTM6865	0.1365	0.0045	0.0500	0.250
23GTRC009	31.00	32.00	GTM6866	0.7210	0.0035	0.4000	0.900
23GTRC009	32.00	33.00	GTM6867	1.3450	0.0022	0.3500	0.900
23GTRC009	33.00	34.00	GTM6868	14.8500	0.0013	0.4900	1.000
23GTRC009	34.00	35.00	GTM6869	19.8500	0.0016	0.3800	34.200
23GTRC009	35.00	36.00	GTM6871	0.7210	0.0074	0.2600	4.600
23GTRC009	36.00	37.00	GTM6872	0.2480	0.0052	0.0900	1.500
23GTRC009	37.00	38.00	GTM6873	0.0789	0.0022	0.0100	0.250
23GTRC009	38.00	39.00	GTM6874	0.0777	0.0012	0.0100	0.250
23GTRC009	39.00	40.00	GTM6875	0.1005	0.0018	0.0100	0.600
23GTRC009	40.00	41.00	GTM6876	0.0829	0.0016	0.0200	0.500
23GTRC009	41.00	42.00	GTM6877	0.1400	0.0066	0.0100	0.500
23GTRC009	42.00	43.00	GTM6878	0.1445	0.0068	0.7500	8.100
23GTRC009A	0.00	1.00	GTM6879	0.0505	0.0026	0.1900	0.250
23GTRC009A	1.00	2.00	GTM6881	0.0104	0.0043	0.0400	0.250
23GTRC009A	2.00	3.00	GTM6882	0.0107	0.0040	0.0200	0.250
23GTRC009A	3.00	6.00	WHO1735	0.0103	0.0015	0.0100	0.250
23GTRC009A	6.00	9.00	WHO1723	0.0526	0.0048	0.0100	0.250
23GTRC009A	9.00	11.00	WHO1724	0.0586	0.0056	0.0100	0.250
23GTRC009A	11.00	12.00	GTM6892	0.0624	0.0081	0.0100	0.250
23GTRC009A	12.00	13.00	GTM6893	0.0746	0.0162	0.0100	0.250
23GTRC009A	13.00	14.00	GTM6894	0.0775	0.0202	0.0100	0.250
23GTRC009A	14.00	15.00	GTM6895	0.0262	0.0273	0.0100	0.250
23GTRC009A	15.00	16.00	GTM6896	0.0077	0.0227	0.0100	0.250
23GTRC009A	16.00	17.00	GTM6897	0.0076	0.0169	0.0100	0.250
23GTRC009A	17.00	18.00	GTM6898	0.0099	0.0194	0.0100	0.250
23GTRC009A	18.00	19.00	GTM6899	0.0086	0.0218	0.0100	0.250
23GTRC009A	19.00	22.00	WHO1725	0.0051	0.0185	0.0100	0.250
23GTRC009A	22.00	24.00	WHO1726	0.0066	0.0327	0.0100	0.250
23GTRC009A	24.00	25.00	GTM6906	0.0911	0.0421	0.0100	0.250
23GTRC009A	25.00	26.00	GTM6907	0.1835	0.0264	0.0100	0.250
23GTRC009A	26.00	27.00	GTM6908	0.2690	0.0212	0.0100	0.250
23GTRC009A	27.00	28.00	GTM6909	0.2490	0.0163	0.0100	0.500
23GTRC009A	28.00	29.00	GTM6911	0.1620	0.0102	0.0100	0.500
23GTRC009A	29.00	30.00	GTM6912	0.1185	0.0043	0.0100	0.250
23GTRC009A	30.00	31.00	GTM6913	0.1065	0.0045	0.0100	0.250
23GTRC009A	31.00	32.00	GTM6914	0.1400	0.0030	0.0100	0.250
23GTRC009A	32.00	33.00	GTM6915	0.0931	0.0014	0.0100	0.250
23GTRC009A	33.00	34.00	GTM6916	0.1355	0.0016	0.0100	0.250
23GTRC009A	34.00	35.00	GTM6917	0.0695	0.0009	0.0100	0.250
23GTRC009A	35.00	36.00	GTM6918	0.1145	0.0011	0.0100	0.250
23GTRC009A	36.00	37.00	GTM6919	0.1080	0.0044	0.0100	0.250
23GTRC009A	37.00	38.00	GTM6921	0.0444	0.0040	0.0100	0.250
23GTRC009A	38.00	41.00	WHO1727	0.0328	0.0012	0.0100	0.500
23GTRC009A	41.00	44.00	WHO1728	0.0328	0.0017	0.0100	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC009A	44.00	45.00	GTM6928	0.0505	0.0011	0.0100	0.800
23GTRC009A	45.00	46.00	GTM6929	0.1035	0.0010	0.0100	0.500
23GTRC009A	46.00	47.00	GTM6931	0.1070	0.0011	0.0100	0.800
23GTRC009A	47.00	48.00	GTM6932	0.6180	0.0024	0.0100	2.200
23GTRC009A	48.00	49.00	GTM6933	1.1100	0.0120	0.0100	0.900
23GTRC009A	49.00	50.00	GTM6934	0.5680	0.0099	0.0100	0.250
23GTRC009A	50.00	51.00	GTM6935	0.2250	0.0073	0.0100	0.250
23GTRC009A	51.00	52.00	GTM6936	0.1980	0.0077	0.0100	0.250
23GTRC009A	52.00	53.00	GTM6937	0.2360	0.0066	0.0100	0.250
23GTRC009A	53.00	54.00	GTM6938	0.1170	0.0105	0.0100	0.250
23GTRC009A	54.00	55.00	GTM6939	1.1050	0.0191	0.0100	1.800
23GTRC009A	55.00	56.00	GTM6941	0.0862	0.0162	0.0100	0.250
23GTRC009A	56.00	57.00	GTM6942	0.0714	0.0132	0.0100	0.250
23GTRC009A	57.00	58.00	GTM6943	0.0488	0.0141	0.0100	0.250
23GTRC009A	58.00	59.00	GTM6944	0.0261	0.0180	0.0100	0.250
23GTRC009A	59.00	62.00	WHO1729	0.0053	0.0148	0.0100	0.250
23GTRC009A	62.00	65.00	WHO1731	0.0030	0.0180	0.0100	0.250
23GTRC009A	65.00	68.00	WHO1732	0.0027	0.0247	0.0100	0.250
23GTRC009A	68.00	70.00	WHO1733	0.0046	0.0486	0.0600	0.250
23GTRC009A	70.00	72.00	WHO1734	0.0055	0.0392	0.0100	0.250
23GTRC009B	0.00	1.00	GTM7145	0.2420	0.0043	0.0400	0.250
23GTRC009B	1.00	2.00	GTM7146	0.1345	0.0041	0.0300	0.800
23GTRC009B	2.00	3.00	GTM7147	0.0221	0.0030	0.0100	0.250
23GTRC009B	3.00	6.00	WHO1736	0.0112	0.0023	0.0100	0.250
23GTRC009B	6.00	7.00	GTM7152	0.0302	0.0015	0.0100	0.250
23GTRC009B	7.00	8.00	GTM7153	0.0400	0.0032	0.0100	0.500
23GTRC009B	8.00	9.00	GTM7154	0.0667	0.0060	0.0100	0.250
23GTRC009B	9.00	10.00	GTM7155	0.0887	0.0082	0.0100	0.500
23GTRC009B	10.00	11.00	GTM7156	0.0537	0.0065	0.0100	0.250
23GTRC009B	11.00	13.00	WHO1737	0.0477	0.0117	0.0100	0.250
23GTRC009B	13.00	15.00	WHO1738	0.0112	0.0201	0.0100	0.250
23GTRC009B	15.00	18.00	WHO1739	0.0069	0.0190	0.0100	0.250
23GTRC009B	18.00	21.00	WHO1741	0.0037	0.0220	0.0100	0.250
23GTRC009B	21.00	23.00	WHO1742	0.0392	0.0432	0.0100	0.250
23GTRC009B	23.00	24.00	GTM7171	0.0960	0.0214	0.0100	0.250
23GTRC009B	24.00	25.00	GTM7172	0.2400	0.0244	0.0100	0.250
23GTRC009B	25.00	26.00	GTM7173	0.3510	0.0210	0.0100	0.250
23GTRC009B	26.00	27.00	GTM7174	0.3010	0.0185	0.0100	0.500
23GTRC009B	27.00	28.00	GTM7175	0.0980	0.0055	0.0100	0.250
23GTRC009B	28.00	29.00	GTM7176	0.1005	0.0037	0.0100	0.700
23GTRC009B	29.00	32.00	WHO1743	0.0870	0.0010	0.0100	0.250
23GTRC009C	0.00	1.00	GTM7180	0.0407	0.0061	0.0400	0.700
23GTRC009C	1.00	2.00	GTM7181	0.1305	0.0084	1.3800	2.100
23GTRC009C	2.00	3.00	GTM7182	0.1315	0.1240	0.0900	1.600
23GTRC009C	3.00	4.00	GTM7183	0.4240	0.1465	0.1400	2.600
23GTRC009C	4.00	5.00	GTM7184	0.8830	0.3250	0.0200	2.100
23GTRC009C	5.00	6.00	GTM7185	0.9270	0.2860	0.0100	1.200
23GTRC009C	6.00	7.00	GTM7186	1.5050	0.3820	0.0100	1.100
23GTRC009C	7.00	8.00	GTM7187	1.6350	0.3170	0.0100	1.000
23GTRC009C	8.00	9.00	GTM7188	1.1150	0.1825	0.0100	0.900
23GTRC009C	9.00	10.00	GTM7189	0.7000	0.3190	0.0100	1.000
23GTRC009C	10.00	11.00	GTM7191	0.4230	0.4720	0.0100	0.600
23GTRC009C	11.00	12.00	GTM7192	0.0658	0.3710	0.0100	0.250
23GTRC009C	12.00	13.00	GTM7193	0.3170	0.3260	0.0200	0.600
23GTRC009C	13.00	14.00	GTM7194	0.2460	0.0508	0.0200	0.700
23GTRC009C	14.00	15.00	GTM7195	0.1120	0.0055	0.0800	0.250
23GTRC009C	15.00	16.00	GTM7196	0.0653	0.0050	0.0300	0.250
23GTRC009C	16.00	17.00	GTM7197	0.0436	0.0041	0.0300	0.700
23GTRC009C	17.00	18.00	GTM7198	0.0639	0.0016	0.0200	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC009C	18.00	19.00	GTM7199	0.0891	0.0028	0.0200	0.250
23GTRC009C	19.00	20.00	GTM7201	0.3180	0.0046	0.0600	1.100
23GTRC009C	20.00	21.00	GTM7202	0.2180	0.0053	0.0500	0.600
23GTRC009C	21.00	22.00	GTM7203	0.1535	0.0117	0.0200	0.250
23GTRC009C	22.00	23.00	GTM7204	0.1700	0.0231	0.0200	0.500
23GTRC009C	23.00	24.00	GTM7205	0.1525	0.0165	0.0200	0.250
23GTRC009C	24.00	25.00	GTM7206	0.1280	0.0316	0.0100	0.250
23GTRC009C	25.00	26.00	GTM7207	0.1065	0.0246	0.0100	0.250
23GTRC009C	26.00	27.00	GTM7208	0.0397	0.0100	0.0100	0.250
23GTRC009C	27.00	28.00	GTM7209	0.0957	0.0153	0.0100	0.250
23GTRC009C	28.00	29.00	GTM7211	0.1480	0.0113	0.0100	0.250
23GTRC009C	29.00	30.00	GTM7212	0.0725	0.0078	0.0100	0.250
23GTRC009C	30.00	31.00	GTM7213	0.0391	0.0089	0.0100	0.250
23GTRC009C	34.00	35.00	GTM7217	0.0229	0.0170	0.0100	0.250
23GTRC009C	35.00	36.00	GTM7218	0.0155	0.0141	0.0100	0.250
23GTRC009C	36.00	37.00	GTM7219	0.1025	0.0193	0.0100	0.250
23GTRC009C	37.00	38.00	GTM7221	0.0662	0.0290	0.0100	0.250
23GTRC009C	38.00	39.00	GTM7222	0.1370	0.0480	0.0100	0.250
23GTRC009C	39.00	40.00	GTM7223	0.0675	0.0316	0.0100	0.250
23GTRC009C	40.00	41.00	GTM7224	0.0896	0.0283	0.0100	0.250
23GTRC009C	41.00	42.00	GTM7225	0.1105	0.0209	0.0100	0.250
23GTRC009C	42.00	43.00	GTM7226	0.1165	0.0576	0.0100	0.250
23GTRC009C	43.00	44.00	GTM7227	0.0702	0.0650	0.0100	0.250
23GTRC009C	44.00	45.00	GTM7228	0.0244	0.0553	0.0100	0.250
23GTRC009C	45.00	47.00	WHO1744	0.0049	0.0312	0.0100	0.250
23GTRC009C	47.00	49.00	WHO1745	0.0050	0.0393	0.0100	0.250
23GTRC009C	49.00	50.00	GTM7234	0.0073	0.0228	0.0100	0.250
23GTRC009C	50.00	51.00	GTM7235	0.0061	0.0344	0.0100	0.250
23GTRC009C	51.00	52.00	GTM7236	0.0033	0.1075	0.0100	0.250
23GTRC009C	52.00	53.00	GTM7237	0.0140	0.1070	0.0100	0.250
23GTRC009C	53.00	54.00	GTM7238	0.0166	0.1260	0.0100	0.250
23GTRC009C	54.00	56.00	WHO1746	0.0176	0.0770	0.0100	0.250
23GTRC009C	56.00	59.00	WHO1747	0.0087	0.0712	0.0100	0.250
23GTRC009C	59.00	62.00	WHO1748	0.0111	0.0628	0.0100	0.250
23GTRC009C	62.00	65.00	WHO1749	0.0007	0.0454	0.0100	0.250
23GTRC009C	65.00	68.00	WHO1751	0.0092	0.0485	0.0100	0.250
23GTRC009C	68.00	71.00	WHO1752	0.0040	0.0703	0.0100	0.250
23GTRC009C	71.00	74.00	WHO1753	0.0056	0.0530	0.0100	0.250
23GTRC009C	74.00	77.00	WHO1754	0.0175	0.0663	0.0100	0.250
23GTRC009C	77.00	80.00	WHO1755	0.0088	0.0310	0.0100	0.250
23GTRC009C	80.00	83.00	WHO1756	0.0078	0.0185	0.0100	0.250
23GTRC009C	83.00	85.00	WHO1757	0.0174	0.0223	0.0100	0.250
23GTRC009C	85.00	88.00	WHO1758	0.0342	0.0235	0.0100	0.250
23GTRC009C	88.00	91.00	WHO1759	0.0150	0.0585	0.0100	0.250
23GTRC009C	91.00	93.00	WHO1761	0.0046	0.0310	0.0100	0.250
23GTRC009C	93.00	96.00	WHO1762	0.0006	0.0180	0.0100	0.250
23GTRC009C	96.00	99.00	WHO1763	0.0010	0.0250	0.0100	0.250
23GTRC009C	99.00	102.00	WHO1764	0.0007	0.0353	0.0100	0.250
23GTRC010	0.00	1.00	GTM6957	0.3290	0.1170	0.0800	0.250
23GTRC010	1.00	2.00	GTM6958	0.8690	0.1490	0.1600	0.250
23GTRC010	2.00	3.00	GTM6959	0.5440	0.0831	0.0600	0.600
23GTRC010	3.00	4.00	GTM6961	0.5810	0.1605	0.0100	1.400
23GTRC010	4.00	5.00	GTM6962	0.1095	0.0288	0.0100	0.250
23GTRC010	5.00	6.00	GTM6963	0.0268	0.0264	0.0100	0.250
23GTRC010	6.00	7.00	GTM6964	0.0593	0.0359	0.0100	0.250
23GTRC010	7.00	8.00	GTM6965	0.0780	0.0393	0.0100	0.250
23GTRC010	8.00	9.00	GTM6966	0.5120	0.0947	0.0600	0.250
23GTRC010	9.00	10.00	GTM6967	0.0642	0.0430	0.0100	0.250
23GTRC010	10.00	11.00	GTM6968	0.0245	0.0790	0.0100	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC010	11.00	12.00	GTM6969	0.0153	0.0224	0.0100	0.250
23GTRC010	12.00	13.00	GTM6971	0.0162	0.0436	0.0100	0.250
23GTRC010	13.00	16.00	WHO1674	0.0096	0.0173	0.0100	0.250
23GTRC010	16.00	19.00	WHO1675	0.0030	0.0141	0.0100	0.250
23GTRC010	19.00	22.00	WHO1676	0.0034	0.0174	0.0100	0.250
23GTRC010	22.00	25.00	WHO1677	0.0020	0.0265	0.0100	0.250
23GTRC010	25.00	28.00	WHO1678	0.0009	0.0196	0.0100	0.250
23GTRC010	28.00	31.00	WHO1679	0.0011	0.0159	0.0100	0.250
23GTRC010	31.00	34.00	WHO1681	0.0007	0.0158	0.0100	0.250
23GTRC010	34.00	37.00	WHO1682	0.0011	0.0213	0.0100	0.250
23GTRC010	37.00	39.00	WHO1683	0.0026	0.0102	0.0100	0.250
23GTRC010	39.00	42.00	WHO1684	0.0085	0.0133	0.0100	0.250
23GTRC010	42.00	45.00	WHO1685	0.0047	0.0075	0.0100	0.250
23GTRC010	45.00	48.00	WHO1686	0.0051	0.0050	0.0100	0.250
23GTRC010	48.00	51.00	WHO1687	0.0045	0.0042	0.0100	0.250
23GTRC010	51.00	54.00	WHO1688	0.0043	0.0034	0.0100	0.250
23GTRC010	54.00	57.00	WHO1689	0.0078	0.0034	0.0100	0.250
23GTRC010	57.00	60.00	WHO1691	0.0101	0.0061	0.0100	0.250
23GTRC010	60.00	63.00	WHO1692	0.0244	0.0138	0.0100	0.250
23GTRC010	63.00	66.00	WHO1693	0.0106	0.0086	0.0100	0.250
23GTRC010	66.00	69.00	WHO1694	0.0066	0.0083	0.0100	0.250
23GTRC010	69.00	72.00	WHO1695	0.0049	0.0089	0.0100	0.250
23GTRC010	72.00	75.00	WHO1696	0.0274	0.0099	0.0100	0.250
23GTRC010	75.00	78.00	WHO1697	0.0301	0.0088	0.0100	0.250
23GTRC010	78.00	81.00	WHO1698	0.0262	0.0091	0.0100	0.250
23GTRC010	81.00	84.00	WHO1699	0.0674	0.0075	0.0100	0.250
23GTRC010	84.00	87.00	WHO1701	0.0228	0.0075	0.0100	0.250
23GTRC010	87.00	90.00	WHO1702	0.0787	0.0078	0.0100	0.250
23GTRC010	90.00	93.00	WHO1703	0.0293	0.0087	0.0100	0.250
23GTRC010	93.00	96.00	WHO1704	0.0242	0.0121	0.0100	0.250
23GTRC010	96.00	99.00	WHO1705	0.0613	0.0150	0.0100	0.250
23GTRC010	99.00	102.00	WHO1706	0.0206	0.0100	0.0100	0.250
23GTRC010	102.00	105.00	WHO1707	0.0189	0.0090	0.0100	0.250
23GTRC010	105.00	108.00	WHO1708	0.0108	0.0084	0.0100	0.250
23GTRC010	108.00	111.00	WHO1709	0.0547	0.0119	0.0100	0.250
23GTRC010	111.00	114.00	WHO1711	0.0069	0.0142	0.0100	0.250
23GTRC010	114.00	117.00	WHO1712	0.0306	0.0184	0.0100	0.250
23GTRC010	117.00	120.00	WHO1713	0.0100	0.0212	0.0100	0.250
23GTRC010	120.00	123.00	WHO1714	0.0057	0.0128	0.0100	0.250
23GTRC010	123.00	126.00	WHO1715	0.0069	0.0481	0.0100	0.250
23GTRC010	126.00	129.00	WHO1716	0.0011	0.0349	0.0100	0.250
23GTRC010	129.00	132.00	WHO1717	0.0013	0.0442	0.0100	0.250
23GTRC010	132.00	135.00	WHO1718	0.0003	0.0356	0.0100	0.250
23GTRC011	0.00	1.00	GTM7111	0.0162	0.0217	0.0100	0.250
23GTRC011	1.00	2.00	GTM7112	0.0123	0.0141	0.0100	0.250
23GTRC011	2.00	3.00	GTM7113	0.0180	0.0180	0.0100	0.250
23GTRC011	3.00	4.00	GTM7114	0.0028	0.0241	0.0100	0.250
23GTRC011	4.00	5.00	GTM7115	0.0054	0.0166	0.0100	0.250
23GTRC011	5.00	8.00	WHO1719	0.0112	0.0203	0.0100	0.250
23GTRC011	8.00	10.00	WHO1721	0.0169	0.0200	0.0100	0.250
23GTRC011	10.00	12.00	WHO1722	0.0234	0.0470	0.0100	0.250
23GTRC011	12.00	13.00	GTM7124	0.0292	0.0259	0.0100	0.250
23GTRC011	13.00	14.00	GTM7125	0.0560	0.0444	0.0100	0.250
23GTRC011	14.00	15.00	GTM7126	0.5930	0.0450	0.0200	0.250
23GTRC011	16.00	17.00	GTM7128	0.1260	0.0473	0.0100	0.250
23GTRC011	17.00	18.00	GTM7129	0.0507	0.0525	0.0100	0.250
23GTRC011	18.00	19.00	GTM7131	0.0847	0.0618	0.0100	0.250
23GTRC011	19.00	20.00	GTM7132	0.0880	0.0615	0.0100	0.250
23GTRC011	20.00	21.00	GTM7133	0.2590	0.0290	0.0300	0.900

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC011	21.00	22.00	GTM7134	0.2890	0.0415	0.0400	0.250
23GTRC011	22.00	23.00	GTM7135	0.3880	0.0575	0.0100	0.250
23GTRC011	23.00	24.00	GTM7136	0.4540	0.0418	0.0100	0.250
23GTRC011	24.00	25.00	GTM7137	0.5540	0.0164	0.1100	1.300
23GTRC011	25.00	26.00	GTM7138	0.6890	0.0132	0.0900	3.300
23GTRC011	26.00	27.00	GTM7139	0.5890	0.0321	0.1200	0.900
23GTRC011	27.00	28.00	GTM7141	0.7040	0.0427	0.1500	3.900
23GTRC011	28.00	29.00	GTM7142	7.8700	0.0661	0.3100	3.000
23GTRC011	29.00	30.00	GTM7143	10.1500	0.0737	0.1200	3.400
23GTRC011	30.00	31.00	GTM7144	10.6000	0.0670	0.1300	4.100
23GTRC011A	0.00	3.00	WHO1765	0.0068	0.0184	0.0100	0.250
23GTRC011A	3.00	6.00	WHO1766	0.0110	0.0147	0.0100	0.250
23GTRC011A	6.00	7.00	GTM7297	0.0296	0.0334	0.0100	0.250
23GTRC011A	7.00	8.00	GTM7298	0.0072	0.0356	0.0100	0.250
23GTRC011A	8.00	9.00	GTM7299	0.0393	0.0351	0.0100	0.250
23GTRC011A	9.00	10.00	GTM7301	0.1795	0.0544	0.0100	0.250
23GTRC011A	10.00	11.00	GTM7302	0.3010	0.0834	0.0100	0.250
23GTRC011A	11.00	12.00	GTM7303	0.0723	0.0546	0.0100	0.250
23GTRC011A	12.00	13.00	GTM7304	0.0303	0.0388	0.0100	0.250
23GTRC011A	13.00	14.00	GTM7305	0.0186	0.0846	0.0100	0.250
23GTRC011A	14.00	15.00	GTM7306	0.0162	0.1295	0.0100	0.250
23GTRC011A	15.00	16.00	GTM7307	0.0297	0.1295	0.0100	0.250
23GTRC011A	16.00	17.00	GTM7308	0.0328	0.0728	0.0100	0.250
23GTRC011A	17.00	18.00	GTM7309	0.0453	0.0353	0.0100	0.250
23GTRC011A	18.00	19.00	GTM7311	0.0633	0.0312	0.0100	0.250
23GTRC011A	19.00	20.00	GTM7312	0.1155	0.0563	0.0100	0.500
23GTRC011A	20.00	21.00	GTM7313	0.6360	0.0701	0.0700	0.250
23GTRC011A	21.00	22.00	GTM7314	1.8650	0.0643	0.1800	0.800
23GTRC011A	22.00	23.00	GTM7315	0.5500	0.0435	0.0300	0.500
23GTRC011A	23.00	24.00	GTM7316	0.9780	0.0442	0.0300	0.600
23GTRC011A	24.00	25.00	GTM7317	0.1815	0.0404	0.0100	0.250
23GTRC011A	25.00	26.00	GTM7318	0.0322	0.0507	0.0100	0.250
23GTRC011A	26.00	27.00	GTM7319	0.0678	0.0649	0.0100	0.250
23GTRC011A	27.00	28.00	GTM7321	0.9590	0.0728	0.0100	0.600
23GTRC011A	28.00	29.00	GTM7322	0.8000	0.0472	0.0200	0.500
23GTRC011A	29.00	30.00	GTM7323	0.8010	0.0416	0.0500	0.250
23GTRC011A	30.00	31.00	GTM7324	0.4990	0.0808	0.0100	0.250
23GTRC011A	31.00	32.00	GTM7325	0.1665	0.0500	0.0400	0.250
23GTRC011A	32.00	33.00	GTM7326	0.1545	0.0497	0.0400	2.500
23GTRC011A	33.00	34.00	GTM7327	0.1685	0.0373	0.0400	4.900
23GTRC011A	34.00	35.00	GTM7328	0.1350	0.0513	0.2200	5.300
23GTRC011A	35.00	36.00	GTM7329	0.0934	0.0588	0.1200	4.400
23GTRC011A	36.00	37.00	GTM7331	0.1095	0.0740	0.0400	1.900
23GTRC011A	37.00	38.00	GTM7332	1.0050	0.1105	0.2700	4.800
23GTRC011A	38.00	39.00	GTM7333	1.5050	0.0790	0.5800	6.100
23GTRC011A	39.00	40.00	GTM7334	0.2270	0.0578	0.1500	2.100
23GTRC011A	40.00	41.00	GTM7335	0.4500	0.0786	0.2100	3.000
23GTRC011A	41.00	42.00	GTM7336	0.0858	0.0526	0.0600	0.900
23GTRC011A	42.00	43.00	GTM7337	0.1575	0.0506	0.0300	2.100
23GTRC011A	43.00	44.00	GTM7338	0.0879	0.0591	0.1300	2.000
23GTRC011A	44.00	45.00	GTM7339	0.1360	0.0463	0.0300	2.700
23GTRC011A	45.00	46.00	GTM7341	0.1485	0.0217	0.0100	2.500
23GTRC011A	46.00	47.00	GTM7342	0.1755	0.0145	0.0200	1.000
23GTRC011A	47.00	48.00	GTM7343	0.3360	0.0087	0.0100	7.300
23GTRC011A	48.00	49.00	GTM7344	0.9190	0.0118	0.0100	0.250
23GTRC011A	49.00	50.00	GTM7345	1.3350	0.0146	0.0100	0.250
23GTRC011A	50.00	51.00	GTM7346	1.0250	0.0161	0.0100	0.250
23GTRC011A	51.00	52.00	GTM7347	1.1850	0.0196	0.0100	0.250
23GTRC011A	52.00	53.00	GTM7348	0.6820	0.0176	0.0100	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
23GTRC011A	53.00	54.00	GTM7349	0.6700	0.0178	0.0100	0.250
23GTRC011A	54.00	55.00	GTM7351	1.1000	0.0261	0.0100	0.250
23GTRC011A	55.00	56.00	GTM7352	0.5590	0.0216	0.0100	0.250
23GTRC011A	56.00	57.00	GTM7353	0.5050	0.0210	0.0100	0.250
23GTRC011A	57.00	58.00	GTM7354	0.2160	0.0299	0.0100	0.250
23GTRC011A	58.00	59.00	GTM7355	0.1540	0.0259	0.0100	0.250
23GTRC011A	59.00	60.00	GTM7356	0.0355	0.0252	0.0100	0.250
23GTRC011A	60.00	61.00	GTM7357	0.0202	0.0150	0.0100	0.250
23GTRC011A	61.00	63.00	WHO1767	0.0555	0.0128	0.0100	0.250
23GTRC011A	63.00	64.00	GTM7361	0.0584	0.0081	0.0100	0.250
23GTRC011A	64.00	65.00	GTM7362	0.2700	0.0166	0.0100	0.250
23GTRC011A	65.00	66.00	GTM7363	0.3720	0.0121	0.0100	0.250
23GTRC011A	66.00	67.00	GTM7364	0.2120	0.0082	0.0100	0.250
23GTRC011A	67.00	68.00	GTM7365	0.0719	0.0079	0.0100	0.250
23GTRC011A	68.00	69.00	GTM7366	0.0241	0.0078	0.0100	0.250
23GTRC011A	69.00	70.00	GTM7367	0.0151	0.0066	0.0100	0.250
23GTRC011A	70.00	72.00	WHO1768	0.0080	0.0065	0.0100	0.250
23GTRC011A	72.00	75.00	WHO1769	0.0093	0.0051	0.0100	0.250
23GTRC011A	75.00	78.00	WHO1771	0.0077	0.0052	0.0100	0.250
23GTRC011A	78.00	81.00	WHO1772	0.0218	0.0048	0.0100	0.250
23GTRC011A	81.00	84.00	WHO1773	0.0665	0.0077	0.0100	0.250
23GTRC011A	84.00	87.00	WHO1774	0.1090	0.0128	0.0100	0.250
23GTRC011A	87.00	90.00	WHO1775	0.0370	0.0072	0.0100	0.250
23GTRC011A	90.00	93.00	WHO1776	0.0252	0.0074	0.0100	0.250
23GTRC011A	93.00	96.00	WHO1777	0.0066	0.0118	0.0100	0.250
24GTRC001	0.00	5.00	24GT18-001	0.0032	0.0154	0.0050	0.050
24GTRC001	5.00	10.00	24GT18-002	0.0030	0.0230	0.0050	0.020
24GTRC001	10.00	15.00	24GT18-003	0.0022	0.0181	0.0050	0.020
24GTRC001	15.00	20.00	24GT18-004	0.0002	0.0097	0.0100	0.050
24GTRC001	20.00	25.00	24GT18-005	0.0009	0.0145	0.0050	0.020
24GTRC001	25.00	30.00	24GT18-006	0.0007	0.0222	0.0100	0.040
24GTRC001	30.00	35.00	24GT18-007	0.0020	0.0365	0.0050	0.040
24GTRC001	35.00	40.00	24GT18-008	0.0041	0.0725	0.0050	0.030
24GTRC001	40.00	45.00	24GT18-009	0.0113	0.1330	0.0050	0.150
24GTRC001	45.00	50.00	24GT18-010	0.0016	0.0376	0.0050	0.050
24GTRC001	50.00	55.00	24GT18-011	0.0031	0.0583	0.0050	0.050
24GTRC001	55.00	60.00	24GT18-012	0.0013	0.0460	0.0050	0.005
24GTRC001	60.00	65.00	24GT18-013	0.0009	0.0172	0.0050	0.020
24GTRC001	65.00	70.00	24GT18-014	0.0007	0.0106	0.0050	0.030
24GTRC001	70.00	75.00	24GT18-015	0.0001	0.0081	0.0050	0.040
24GTRC001	75.00	80.00	24GT18-016	0.0001	0.0138	0.0050	0.040
24GTRC001	80.00	84.00	24GT18-017	0.0027	0.0325	0.0050	0.040
24GTRC001	84.00	85.00	24GT18-018	0.0043	0.0255	0.0050	0.040
24GTRC001	85.00	86.00	24GT18-019	0.0013	0.0276	0.0050	0.005
24GTRC001	86.00	87.00	24GT18-020	0.0018	0.0292	0.0050	0.005
24GTRC001	87.00	88.00	24GT18-021	0.0008	0.0277	0.0050	0.010
24GTRC001	88.00	89.00	24GT18-022	0.0028	0.0273	0.0050	0.130
24GTRC001	89.00	90.00	24GT18-023	0.0016	0.0246	0.0050	0.005
24GTRC001	90.00	91.00	24GT18-024	0.0021	0.0242	0.0050	0.005
24GTRC001	91.00	92.00	24GT18-025	0.0019	0.0217	0.0050	0.005
24GTRC001	92.00	93.00	24GT18-026	0.0040	0.0146	0.0050	0.230
24GTRC001	93.00	94.00	24GT18-027	0.0023	0.0117	0.0100	0.005
24GTRC001	94.00	95.00	24GT18-028	0.0079	0.0210	0.0050	0.040
24GTRC001	95.00	96.00	24GT18-029	0.0085	0.0203	0.0050	0.005
24GTRC001	96.00	97.00	24GT18-031	0.0036	0.0226	0.0050	0.680
24GTRC001	97.00	98.00	24GT18-032	0.0094	0.0197	0.0050	0.010
24GTRC001	98.00	99.00	24GT18-033	0.0104	0.0192	0.0050	0.005
24GTRC001	99.00	100.00	24GT18-034	0.0045	0.0186	0.0100	0.005
24GTRC001	100.00	101.00	24GT18-035	0.0035	0.0189	0.0050	0.005

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
24GTRC001	101.00	102.00	24GT18-036	0.0029	0.0196	0.0050	0.005
24GTRC001	102.00	103.00	24GT18-037	0.0049	0.0207	0.0050	0.005
24GTRC001	103.00	104.00	24GT18-038	0.0054	0.0234	0.0050	0.005
24GTRC001	104.00	105.00	24GT18-039	0.0067	0.0198	0.0050	0.010
24GTRC001	105.00	106.00	24GT18-040	0.0033	0.0189	0.0050	0.005
24GTRC001	106.00	107.00	24GT18-042	0.0076	0.0153	0.0100	0.010
24GTRC001	107.00	108.00	24GT18-043	0.0032	0.0106	0.0050	0.005
24GTRC001	108.00	109.00	24GT18-044	0.0004	0.0067	0.0050	0.005
24GTRC001	109.00	110.00	24GT18-045	0.0008	0.0073	0.0100	0.005
24GTRC001	110.00	111.00	24GT18-046	0.0022	0.0073	0.0050	0.005
24GTRC001	111.00	112.00	24GT18-047	0.0017	0.0128	0.0050	0.005
24GTRC001	112.00	113.00	24GT18-048	0.0041	0.0133	0.0050	0.005
24GTRC001	113.00	114.00	24GT18-049	0.0037	0.0116	0.0050	0.010
24GTRC001	114.00	115.00	24GT18-051	0.0023	0.0149	0.0050	0.040
24GTRC001	115.00	116.00	24GT18-052	0.0023	0.0140	0.0050	0.020
24GTRC001	116.00	117.00	24GT18-053	0.0004	0.0140	0.0050	0.050
24GTRC001	117.00	118.00	24GT18-054	0.0002	0.0135	0.0050	0.070
24GTRC001	118.00	119.00	24GT18-055	0.0003	0.0133	0.0050	0.150
24GTRC001	119.00	120.00	24GT18-056	0.0119	0.0181	0.0050	0.050
24GTRC001	120.00	121.00	24GT18-057	0.0029	0.0215	0.0050	0.040
24GTRC001	121.00	122.00	24GT18-058	0.0012	0.0206	0.0050	0.030
24GTRC001	122.00	123.00	24GT18-059	0.0020	0.0226	0.0050	0.030
24GTRC001	123.00	124.00	24GT18-061	0.0019	0.0246	0.0050	0.090
24GTRC001	124.00	125.00	24GT18-062	0.0017	0.0253	0.0050	0.020
24GTRC001	125.00	126.00	24GT18-063	0.0019	0.0248	0.0050	0.030
24GTRC001	126.00	127.00	24GT18-064	0.0016	0.0218	0.0050	0.020
24GTRC001	127.00	128.00	24GT18-065	0.0015	0.0207	0.0050	0.020
24GTRC001	128.00	129.00	24GT18-066	0.0108	0.0178	0.0050	0.070
24GTRC001	129.00	130.00	24GT18-067	0.0064	0.0232	0.0050	0.050
24GTRC001	130.00	135.00	24GT18-068	0.0020	0.0164	0.0050	0.030
24GTRC001	135.00	140.00	24GT18-069	0.0059	0.0164	0.0050	0.040
24GTRC001	140.00	145.00	24GT18-070	0.0033	0.0108	0.0050	0.060
24GTRC001	145.00	150.00	24GT18-071	0.0050	0.0144	0.0050	0.070
24GTRC001	150.00	155.00	24GT18-072	0.0029	0.0145	0.0100	0.050
24GTRC001	155.00	160.00	24GT18-073	0.0041	0.0157	0.0050	0.040
24GTRC001	160.00	165.00	24GT18-074	0.0045	0.0154	0.0050	0.040
24GTRC001	165.00	170.00	24GT18-075	0.0055	0.0139	0.0100	0.010
24GTRC001	170.00	175.00	24GT18-076	0.0070	0.0188	0.0050	0.070
24GTRC001	175.00	180.00	24GT18-077	0.0052	0.0414	0.0050	0.060
24GTRC001	180.00	185.00	24GT18-078	0.0270	0.0759	0.0100	0.240
24GTRC001	185.00	190.00	24GT18-079	0.0207	0.0236	0.0200	0.280
24GTRC001	190.00	195.00	24GT18-080	0.0030	0.0079	0.0050	0.020
24GTRC001	195.00	200.00	24GT18-082	0.0029	0.0128	0.0100	0.020
24GTRC001	200.00	205.00	24GT18-083	0.0026	0.0081	0.0050	0.040
24GTRC001	205.00	210.00	24GT18-084	0.0076	0.0071	0.0100	0.040
24GTRC001	210.00	215.00	24GT18-085	0.0074	0.0091	0.0100	0.030
24GTRC001	215.00	220.00	24GT18-086	0.0040	0.0213	0.0050	0.010
24GTRC001	220.00	225.00	24GT18-087	0.0024	0.0135	0.0100	0.010
24GTRC001	225.00	230.00	24GT18-088	0.0003	0.0308	0.0100	0.100
24GTRC001	230.00	231.00	24GT18-089	1.4450	0.4830	0.0600	2.750
24GTRC001	231.00	232.00	24GT18-091	1.5500	0.2670	0.0300	2.960
24GTRC001	232.00	233.00	24GT18-092	0.5800	0.0620	0.0400	1.540
24GTRC001	233.00	234.00	24GT18-093	1.0800	0.1800	0.0300	1.690
24GTRC001	234.00	235.00	24GT18-094	1.0150	0.0983	0.0300	1.550
24GTRC001	235.00	236.00	24GT18-095	3.3600	0.3420	0.0300	4.560
24GTRC001	236.00	237.00	24GT18-096	2.0100	0.1635	0.0500	3.820
24GTRC001	237.00	238.00	24GT18-097	1.0400	0.0686	0.0500	1.600
24GTRC001	238.00	239.00	24GT18-098	0.8190	0.0583	0.0300	1.150
24GTRC001	239.00	240.00	24GT18-099	0.0079	0.0036	0.0050	0.010

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
24GTRC001	240.00	241.00	24GT18-101	0.6060	0.0582	0.0200	0.850
24GTRC001	241.00	242.00	24GT18-102	1.8750	0.1060	0.0500	2.570
24GTRC001	242.00	243.00	24GT18-103	0.1235	0.0431	0.0050	0.170
24GTRC001	243.00	244.00	24GT18-104	0.9350	0.0457	0.0200	1.580
24GTRC001	244.00	245.00	24GT18-105	2.9300	0.0275	0.0900	6.770
24GTRC001	245.00	246.00	24GT18-106	0.1870	0.0175	0.0100	0.280
24GTRC001	246.00	247.00	24GT18-107	0.0321	0.0215	0.0100	0.070
24GTRC001	247.00	248.00	24GT18-108	0.0069	0.0116	0.0050	0.010
24GTRC001	248.00	249.00	24GT18-109	0.0051	0.0172	0.0100	0.020
24GTRC001	249.00	250.00	24GT18-110	0.0035	0.0109	0.0050	0.010
24GTRC001	250.00	251.00	24GT18-111	0.0037	0.0109	0.0100	0.005
24GTRC001	251.00	252.00	24GT18-112	0.0046	0.0100	0.0050	0.010
24GTRC001	252.00	253.00	24GT18-113	0.0037	0.0174	0.0050	0.020
24GTRC001	253.00	254.00	24GT18-114	0.0202	0.0123	0.0050	0.040
24GTRC001	254.00	255.00	24GT18-115	0.0638	0.0136	0.0100	0.110
24GTRC001	255.00	256.00	24GT18-116	0.0058	0.0143	0.0050	0.010
24GTRC001	256.00	257.00	24GT18-117	0.0023	0.0123	0.0100	0.030
24GTRC001	257.00	258.00	24GT18-118	0.0045	0.0048	0.0050	0.005
24GTRC001	258.00	259.00	24GT18-119	0.0142	0.0085	0.0100	0.040
24GTRC001	259.00	260.00	24GT18-121	0.0110	0.0070	0.0100	0.020
24GTRC001	260.00	265.00	24GT18-123	0.0097	0.0061	0.0050	0.030
24GTRC001	265.00	270.00	24GT18-124	0.0034	0.0067	0.0050	0.005
24GTRC001	270.00	275.00	24GT18-125	0.0022	0.0085	0.0050	0.040
24GTRC001	275.00	280.00	24GT18-126	0.0156	0.0110	0.0050	0.040
24GTRC001	280.00	285.00	24GT18-127	0.0035	0.0085	0.0050	0.040
24GTRC001	285.00	290.00	24GT18-128	0.2200	0.0255	0.0100	0.300
24GTRC001	290.00	295.00	24GT18-129	0.0029	0.0207	0.0050	0.010
24GTRC001	295.00	298.00	24GT18-130	0.0020	0.0371	0.0050	0.020
24GTRC001	298.00	299.00	24GT18-131	0.0129	0.0401	0.0050	0.130
24GTRC001	299.00	300.00	24GT18-132	0.0273	0.0391	0.0050	0.380
24GTRC001	300.00	301.00	24GT18-133	0.1445	0.0554	0.0400	2.140
24GTRC001	301.00	302.00	24GT18-134	0.0828	0.0460	0.0100	1.170
24GTRC001	302.00	303.00	24GT18-135	0.0343	0.0546	0.0050	0.690
24GTRC001	303.00	304.00	24GT18-136	0.0666	0.0511	0.0100	0.670
24GTRC001	304.00	305.00	24GT18-137	0.0430	0.0601	0.0050	0.310
24GTRC001	305.00	306.00	24GT18-138	0.0214	0.0655	0.0050	0.190
24GTRC001	306.00	307.00	24GT18-139	0.0211	0.0613	0.0050	0.190
24GTRC001	307.00	308.00	24GT18-140	0.0188	0.0594	0.0100	0.250
24GTRC001	308.00	313.00	24GT18-141	0.0057	0.0321	0.0050	0.060
24GTRC001	313.00	318.00	24GT18-142	0.0064	0.0175	0.0050	0.060
24GTRC001	318.00	319.00	24GT18-143	0.0040	0.0114	0.0050	0.050
24GTRC001	319.00	320.00	24GT18-144	0.0039	0.0109	0.0050	0.030
24GTRC001	320.00	325.00	24GT18-145	0.0055	0.0106	0.0050	0.070
24GTRC001	325.00	330.00	24GT18-146	0.0029	0.0113	0.0050	0.030
24GTRC001	330.00	335.00	24GT18-147	0.0064	0.0155	0.0050	0.070
24GTRC001	335.00	340.00	24GT18-148	0.0091	0.0283	0.0050	0.070
24GTRC001	340.00	341.00	24GT18-149	0.0413	0.0301	0.0100	0.360
24GTRC001	341.00	342.00	24GT18-152	0.0360	0.0259	0.0100	0.340
24GTRC001	342.00	343.00	24GT18-153	0.0185	0.0271	0.0050	0.190
24GTRC001	343.00	344.00	24GT18-154	0.0123	0.0298	0.0050	0.240
24GTRC001	344.00	345.00	24GT18-155	0.0063	0.0305	0.0050	0.100
24GTRC001	345.00	346.00	24GT18-156	0.0134	0.0324	0.0050	0.170
24GTRC001	346.00	347.00	24GT18-157	0.0094	0.0441	0.0050	0.150
24GTRC001	347.00	348.00	24GT18-158	0.0080	0.0881	0.0100	0.130
24GTRC001	348.00	349.00	24GT18-159	0.0067	0.0538	0.0050	0.120
24GTRC001	349.00	350.00	24GT18-160	0.0049	0.0443	0.0050	0.120
24GTRC001	350.00	351.00	24GT18-162	0.0033	0.0630	0.0050	0.090
24GTRC001	351.00	352.00	24GT18-163	0.0058	0.0580	0.0050	0.130
24GTRC001	352.00	353.00	24GT18-164	0.0077	0.0461	0.0050	0.110

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
24GTRC001	353.00	354.00	24GT18-165	0.0067	0.0477	0.0050	0.110
24GTRC001	354.00	355.00	24GT18-166	0.0075	0.0499	0.0050	0.120
24GTRC001	355.00	356.00	24GT18-167	0.0065	0.0416	0.0050	0.090
24GTRC001	356.00	357.00	24GT18-168	0.0026	0.0397	0.0050	0.030
24GTRC001	357.00	358.00	24GT18-169	0.0044	0.0348	0.0050	0.070
24GTRC001	358.00	363.00	24GT18-170	0.0054	0.0285	0.0050	0.040
24GTRC001	363.00	367.00	24GT18-171	0.0039	0.0183	0.0050	0.030
24GTRC001	367.00	368.00	24GT18-172	0.0059	0.0162	0.0050	0.040
24GTRC001	368.00	369.00	24GT18-173	0.0046	0.0138	0.0050	0.040
24GTRC001	369.00	370.00	24GT18-174	0.0043	0.0124	0.0050	0.040
24GTRC001	370.00	371.00	24GT18-175	0.0042	0.0112	0.0050	0.040
24GTRC001	371.00	372.00	24GT18-176	0.0027	0.0079	0.0050	0.020
24GTRC002	0.00	5.00	24GT18-427	0.0038	0.0052	0.0050	0.110
24GTRC002	5.00	10.00	24GT18-428	0.0055	0.0104	0.0050	0.210
24GTRC002	10.00	15.00	24GT18-429	0.0088	0.0122	0.0050	0.080
24GTRC002	15.00	20.00	24GT18-430	0.0046	0.0094	0.0050	0.050
24GTRC002	20.00	25.00	24GT18-431	0.0026	0.0087	0.0050	0.040
24GTRC002	25.00	30.00	24GT18-432	0.0004	0.0102	0.0050	0.010
24GTRC002	30.00	35.00	24GT18-433	0.0024	0.0153	0.0050	0.010
24GTRC002	35.00	40.00	24GT18-434	0.0055	0.0329	0.0050	0.030
24GTRC002	40.00	45.00	24GT18-435	0.0011	0.0109	0.0050	0.020
24GTRC002	45.00	50.00	24GT18-436	0.0009	0.0088	0.0100	0.005
24GTRC002	50.00	55.00	24GT18-437	0.0007	0.0099	0.0050	0.005
24GTRC002	55.00	60.00	24GT18-438	0.0021	0.0249	0.0050	0.020
24GTRC002	60.00	65.00	24GT18-439	0.0014	0.0284	0.0050	0.030
24GTRC002	65.00	70.00	24GT18-440	0.0008	0.0219	0.0050	0.030
24GTRC002	70.00	75.00	24GT18-442	0.0008	0.0116	0.0050	0.020
24GTRC002	75.00	80.00	24GT18-443	0.0013	0.0181	0.0050	0.005
24GTRC002	80.00	85.00	24GT18-444	0.0018	0.0105	0.0050	0.020
24GTRC002	85.00	90.00	24GT18-445	0.0017	0.0099	0.0050	0.010
24GTRC002	90.00	95.00	24GT18-446	0.0011	0.0084	0.0050	0.005
24GTRC002	95.00	100.00	24GT18-447	0.0024	0.0099	0.0050	0.020
24GTRC002	100.00	105.00	24GT18-448	0.0013	0.0116	0.0050	0.005
24GTRC002	105.00	110.00	24GT18-449	0.0013	0.0132	0.0050	0.010
24GTRC002	110.00	115.00	24GT18-452	0.0011	0.0123	0.0050	0.005
24GTRC002	115.00	120.00	24GT18-453	0.0015	0.0112	0.0050	0.010
24GTRC002	120.00	125.00	24GT18-454	0.0006	0.0072	0.0050	0.005
24GTRC002	125.00	130.00	24GT18-455	0.0012	0.0081	0.0050	0.005
24GTRC002	130.00	135.00	24GT18-456	0.0100	0.0152	0.0050	0.090
24GTRC002	135.00	140.00	24GT18-457	0.0057	0.0140	0.0050	0.050
24GTRC002	140.00	145.00	24GT18-458	0.0012	0.0114	0.0050	0.010
24GTRC002	145.00	150.00	24GT18-459	0.0016	0.0103	0.0050	0.040
24GTRC002	150.00	155.00	24GT18-460	0.0016	0.0112	0.0050	0.050
24GTRC002	155.00	156.00	24GT18-461	0.0035	0.0308	0.0050	0.030
24GTRC003	0.00	5.00	24GT18-462	0.0021	0.0062	0.0050	0.050
24GTRC003	5.00	10.00	24GT18-463	0.0032	0.0096	0.0050	0.030
24GTRC003	10.00	15.00	24GT18-464	0.0057	0.0131	0.0050	0.040
24GTRC003	15.00	20.00	24GT18-465	0.0069	0.0106	0.0050	0.070
24GTRC003	20.00	25.00	24GT18-466	0.0052	0.0104	0.0050	0.050
24GTRC003	25.00	30.00	24GT18-467	0.0009	0.0096	0.0050	0.050
24GTRC003	30.00	35.00	24GT18-468	0.0007	0.0143	0.0050	0.010
24GTRC003	35.00	40.00	24GT18-469	0.0035	0.0211	0.0050	0.020
24GTRC003	40.00	45.00	24GT18-470	0.0013	0.0132	0.0050	0.020
24GTRC003	45.00	50.00	24GT18-471	0.0026	0.0097	0.0050	0.010
24GTRC003	50.00	55.00	24GT18-472	0.0004	0.0082	0.0050	0.005
24GTRC003	55.00	60.00	24GT18-473	0.0016	0.0209	0.0050	0.030
24GTRC003	60.00	65.00	24GT18-474	0.0020	0.0295	0.0050	0.020
24GTRC003	65.00	70.00	24GT18-475	0.0012	0.0300	0.0050	0.030
24GTRC003	70.00	75.00	24GT18-476	0.0008	0.0114	0.0050	0.030

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
24GTRC003	75.00	80.00	24GT18-477	0.0048	0.0183	0.0050	0.010
24GTRC003	80.00	85.00	24GT18-478	0.0027	0.0118	0.0050	0.040
24GTRC003	85.00	90.00	24GT18-479	0.0016	0.0068	0.0050	0.020
24GTRC003	90.00	95.00	24GT18-481	0.0014	0.0084	0.0050	0.050
24GTRC003	95.00	100.00	24GT18-483	0.0016	0.0110	0.0050	0.010
24GTRC003	100.00	105.00	24GT18-484	0.0016	0.0143	0.0050	0.010
24GTRC003	105.00	110.00	24GT18-485	0.0010	0.0184	0.0050	0.010
24GTRC003	110.00	115.00	24GT18-486	0.0004	0.0077	0.0050	0.005
24GTRC003	115.00	120.00	24GT18-487	0.0015	0.0085	0.0100	0.030
24GTRC003	120.00	125.00	24GT18-488	0.0040	0.0176	0.0050	0.020
24GTRC003	125.00	130.00	24GT18-489	0.0013	0.0108	0.0100	0.010
24GTRC003	130.00	135.00	24GT18-490	0.0014	0.0111	0.0050	0.020
24GTRC003	135.00	140.00	24GT18-491	0.0013	0.0109	0.0050	0.010
24GTRC003	140.00	145.00	24GT18-492	0.0025	0.0085	0.0100	0.010
24GTRC003	145.00	150.00	24GT18-493	0.0008	0.0151	0.0050	0.050
24GTRC003	150.00	155.00	24GT18-494	0.0016	0.0139	0.0050	0.020
24GTRC003	155.00	160.00	24GT18-495	0.0040	0.0099	0.0100	0.040
24GTRC003	160.00	165.00	24GT18-496	0.0026	0.0133	0.0050	0.030
24GTRC003	165.00	170.00	24GT18-497	0.0039	0.0146	0.0050	0.040
24GTRC003	170.00	175.00	24GT18-498	0.0029	0.0164	0.0050	0.110
24GTRC003	175.00	180.00	24GT18-499	0.0025	0.0171	0.0050	0.050
24GTRC003	180.00	185.00	24GT18-501	0.0009	0.0159	0.0100	0.030
24GTRC003	185.00	190.00	24GT18-502	0.0015	0.0229	0.0050	0.050
24GTRC003	190.00	192.00	24GT18-503	0.0017	0.0196	0.0050	0.060
24GTRC004	0.00	5.00	24GT18-177	0.0032	0.0140	0.0050	0.010
24GTRC004	5.00	10.00	24GT18-178	0.0032	0.0091	0.0050	0.020
24GTRC004	10.00	15.00	24GT18-179	0.0014	0.0087	0.0050	0.010
24GTRC004	15.00	20.00	24GT18-181	0.0059	0.0118	0.0050	0.050
24GTRC004	20.00	25.00	24GT18-182	0.0131	0.0118	0.0050	0.100
24GTRC004	25.00	30.00	24GT18-183	0.0055	0.0073	0.0050	0.040
24GTRC004	30.00	35.00	24GT18-184	0.0030	0.0083	0.0050	0.020
24GTRC004	35.00	40.00	24GT18-185	0.0024	0.0115	0.0050	0.010
24GTRC004	40.00	45.00	24GT18-186	0.0016	0.0083	0.0050	0.010
24GTRC004	45.00	50.00	24GT18-187	0.0066	0.0132	0.0050	0.080
24GTRC004	50.00	55.00	24GT18-188	0.0082	0.0104	0.0050	0.090
24GTRC004	55.00	60.00	24GT18-189	0.0090	0.0104	0.0100	0.080
24GTRC004	60.00	65.00	24GT18-190	0.0037	0.0099	0.0100	0.060
24GTRC004	65.00	70.00	24GT18-191	0.0062	0.0143	0.0050	0.050
24GTRC004	70.00	75.00	24GT18-192	0.0050	0.0122	0.0100	0.060
24GTRC004	75.00	80.00	24GT18-193	0.0016	0.0122	0.0050	0.050
24GTRC004	80.00	85.00	24GT18-194	0.0014	0.0096	0.0050	0.050
24GTRC004	85.00	90.00	24GT18-195	0.0018	0.0202	0.0050	0.020
24GTRC004	90.00	95.00	24GT18-196	0.0043	0.0140	0.0050	0.050
24GTRC004	95.00	100.00	24GT18-197	0.0034	0.0250	0.0100	0.040
24GTRC004	100.00	105.00	24GT18-198	0.0013	0.0157	0.0050	0.030
24GTRC004	105.00	110.00	24GT18-199	0.0012	0.0087	0.0100	0.050
24GTRC004	110.00	115.00	24GT18-201	0.0011	0.0099	0.0050	0.010
24GTRC004	115.00	120.00	24GT18-203	0.0011	0.0074	0.0050	0.040
24GTRC004	120.00	125.00	24GT18-204	0.0107	0.0126	0.0050	0.110
24GTRC004	125.00	130.00	24GT18-205	0.0021	0.0141	0.0050	0.030
24GTRC004	130.00	135.00	24GT18-206	0.0061	0.0099	0.0050	0.050
24GTRC004	135.00	140.00	24GT18-207	0.0083	0.0092	0.0050	0.070
24GTRC004	140.00	145.00	24GT18-208	0.0081	0.0099	0.0050	0.070
24GTRC004	145.00	150.00	24GT18-209	0.0023	0.0112	0.0100	0.030
24GTRC004	150.00	155.00	24GT18-211	0.0038	0.0135	0.0050	0.060
24GTRC004	155.00	160.00	24GT18-212	0.0028	0.0097	0.0050	0.040
24GTRC004	160.00	165.00	24GT18-213	0.0063	0.0113	0.0100	0.070
24GTRC004	165.00	170.00	24GT18-214	0.0015	0.0162	0.0100	0.040
24GTRC004	170.00	175.00	24GT18-215	0.0072	0.0103	0.0100	0.130

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
24GTRC004	175.00	180.00	24GT18-216	0.0089	0.0136	0.0100	0.130
24GTRC004	180.00	185.00	24GT18-217	0.0068	0.0143	0.0100	0.090
24GTRC004	185.00	190.00	24GT18-218	0.0045	0.0088	0.0100	0.060
24GTRC004	190.00	195.00	24GT18-219	0.0031	0.0154	0.0100	0.040
24GTRC004	195.00	200.00	24GT18-220	0.0026	0.0156	0.0100	0.040
24GTRC004	200.00	205.00	24GT18-221	0.0016	0.0167	0.0100	0.090
24GTRC004	205.00	210.00	24GT18-222	0.0018	0.0126	0.0100	0.030
24GTRC004	210.00	215.00	24GT18-223	0.0011	0.0154	0.0050	0.060
24GTRC004	215.00	220.00	24GT18-224	0.0010	0.0112	0.0100	0.040
24GTRC004	220.00	225.00	24GT18-225	0.0017	0.0099	0.0100	0.030
24GTRC004	225.00	230.00	24GT18-226	0.0022	0.0131	0.0100	0.020
24GTRC004	230.00	235.00	24GT18-227	0.0028	0.0114	0.0050	0.040
24GTRC004	235.00	240.00	24GT18-228	0.0020	0.0127	0.0100	0.020
24GTRC004	240.00	245.00	24GT18-229	0.0021	0.0125	0.0100	0.040
24GTRC004	245.00	250.00	24GT18-230	0.0039	0.0201	0.0100	0.040
24GTRC004	250.00	255.00	24GT18-231	0.0028	0.1265	0.0100	0.150
24GTRC004	255.00	260.00	24GT18-232	0.0185	1.3950	0.2400	0.440
24GTRC004	260.00	261.00	24GT18-233	0.0142	0.6700	0.0300	0.410
24GTRC004	261.00	262.00	24GT18-234	1.3250	0.2630	0.0400	4.640
24GTRC004	262.00	263.00	24GT18-235	4.6100	2.6300	0.2500	15.950
24GTRC004	263.00	264.00	24GT18-236	3.2100	4.9600	0.4000	12.200
24GTRC004	264.00	265.00	24GT18-237	0.8830	1.2600	0.0700	3.300
24GTRC004	265.00	266.00	24GT18-238	0.8280	0.9160	0.0400	2.880
24GTRC004	266.00	267.00	24GT18-239	0.3340	0.5210	0.0200	1.210
24GTRC004	267.00	268.00	24GT18-241	0.2620	0.1435	0.0200	1.190
24GTRC004	268.00	269.00	24GT18-243	0.2390	0.2860	0.0200	0.890
24GTRC004	269.00	270.00	24GT18-244	0.1955	0.1435	0.0400	0.820
24GTRC004	270.00	271.00	24GT18-245	0.1135	0.0691	0.0100	0.570
24GTRC004	271.00	272.00	24GT18-246	0.0373	0.0422	0.0100	0.180
24GTRC004	272.00	273.00	24GT18-247	0.0503	0.0354	0.0100	1.170
24GTRC004	273.00	274.00	24GT18-248	0.1595	0.0389	0.0200	2.270
24GTRC004	274.00	275.00	24GT18-249	0.1965	0.0545	0.0100	1.960
24GTRC004	275.00	276.00	24GT18-251	0.0261	0.0476	0.0050	0.270
24GTRC004	276.00	277.00	24GT18-252	0.0107	0.0888	0.0050	0.130
24GTRC004	277.00	278.00	24GT18-253	0.0204	0.9820	0.0100	0.320
24GTRC004	278.00	279.00	24GT18-254	0.0272	0.4900	0.0200	0.450
24GTRC004	279.00	280.00	24GT18-255	0.0127	0.1940	0.0100	0.230
24GTRC004	280.00	285.00	24GT18-256	0.0141	0.0628	0.0050	0.170
24GTRC004	285.00	290.00	24GT18-257	0.0069	0.0669	0.0050	0.220
24GTRC004	290.00	295.00	24GT18-258	0.0095	0.0755	0.0100	0.430
24GTRC004	295.00	300.00	24GT18-259	0.0058	0.0237	0.0050	0.060
24GTRC004	300.00	305.00	24GT18-260	0.0051	0.0216	0.0050	0.020
24GTRC004	305.00	310.00	24GT18-261	0.0059	0.0140	0.0050	0.040
24GTRC004	310.00	315.00	24GT18-262	0.0092	0.0110	0.0050	0.060
24GTRC004	315.00	320.00	24GT18-263	0.0038	0.0106	0.0050	0.050
24GTRC004	320.00	325.00	24GT18-264	0.0024	0.0144	0.0050	0.030
24GTRC004	325.00	330.00	24GT18-265	0.0054	0.0137	0.0050	0.050
24GTRC004	330.00	335.00	24GT18-266	0.0030	0.0200	0.0050	0.040
24GTRC004	335.00	340.00	24GT18-267	0.0009	0.0089	0.0050	0.005
24GTRC004	340.00	345.00	24GT18-268	0.0020	0.0103	0.0050	0.020
24GTRC004	345.00	350.00	24GT18-269	0.0015	0.0097	0.0050	0.010
24GTRC004	350.00	355.00	24GT18-271	0.0011	0.0081	0.0100	0.005
24GTRC004	355.00	360.00	24GT18-272	0.0036	0.0109	0.0100	0.040
24GTRC004	360.00	365.00	24GT18-273	0.0065	0.0173	0.0050	0.040
24GTRC004	365.00	370.00	24GT18-274	0.0156	0.0210	0.0050	0.120
24GTRC004	370.00	373.00	24GT18-275	0.0125	0.0168	0.0050	0.090
24GTRC004	373.00	374.00	24GT18-276	0.0035	0.0114	0.0050	0.040
24GTRC004	374.00	375.00	24GT18-277	0.0018	0.0082	0.0050	0.010
24GTRC004	375.00	376.00	24GT18-278	0.0076	0.0179	0.0100	0.060

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
24GTRC004	376.00	377.00	24GT18-279	0.0024	0.0123	0.0050	0.010
24GTRC004	377.00	378.00	24GT18-280	0.0057	0.0250	0.0050	0.040
24GTRC005	0.00	5.00	24GT18-282	0.0162	0.0053	0.0050	0.080
24GTRC005	5.00	10.00	24GT18-283	0.0535	0.0094	0.0100	0.120
24GTRC005	10.00	15.00	24GT18-284	0.0199	0.0078	0.0050	0.050
24GTRC005	15.00	20.00	24GT18-285	0.0023	0.0076	0.0100	0.020
24GTRC005	20.00	25.00	24GT18-286	0.0006	0.0089	0.0050	0.020
24GTRC005	25.00	30.00	24GT18-287	0.0043	0.0104	0.0050	0.080
24GTRC005	30.00	35.00	24GT18-288	0.0046	0.0098	0.0050	0.070
24GTRC005	35.00	40.00	24GT18-289	0.0016	0.0125	0.0050	0.030
24GTRC005	40.00	45.00	24GT18-290	0.0069	0.0112	0.0050	0.120
24GTRC005	45.00	50.00	24GT18-291	0.0007	0.0117	0.0050	0.020
24GTRC005	50.00	55.00	24GT18-292	0.0027	0.0362	0.0050	0.030
24GTRC005	55.00	60.00	24GT18-293	0.0082	0.0556	0.0050	0.070
24GTRC005	60.00	65.00	24GT18-294	0.0028	0.0205	0.0050	0.030
24GTRC005	65.00	70.00	24GT18-295	0.0016	0.0330	0.0100	0.040
24GTRC005	70.00	75.00	24GT18-296	0.0024	0.0293	0.0050	0.020
24GTRC005	75.00	80.00	24GT18-297	0.0003	0.0160	0.0050	0.005
24GTRC005	80.00	85.00	24GT18-298	0.0034	0.0090	0.0050	0.010
24GTRC005	85.00	90.00	24GT18-299	0.0027	0.0072	0.0050	0.020
24GTRC005	90.00	95.00	24GT18-302	0.0006	0.0194	0.0050	0.030
24GTRC005	95.00	100.00	24GT18-303	0.0017	0.0157	0.0050	0.010
24GTRC005	100.00	105.00	24GT18-304	0.0020	0.0136	0.0100	0.010
24GTRC005	105.00	110.00	24GT18-305	0.0019	0.0107	0.0050	0.010
24GTRC005	110.00	115.00	24GT18-306	0.0017	0.0134	0.0050	0.005
24GTRC005	115.00	120.00	24GT18-307	0.0012	0.0096	0.0050	0.005
24GTRC005	120.00	125.00	24GT18-308	0.0026	0.0121	0.0050	0.030
24GTRC005	125.00	130.00	24GT18-309	0.0014	0.0105	0.0050	0.005
24GTRC005	130.00	135.00	24GT18-310	0.0017	0.0174	0.0050	0.010
24GTRC005	135.00	140.00	24GT18-311	0.0014	0.0080	0.0050	0.010
24GTRC005	140.00	145.00	24GT18-312	0.0012	0.0095	0.0050	0.010
24GTRC005	145.00	150.00	24GT18-313	0.0005	0.0081	0.0050	0.005
24GTRC005	150.00	155.00	24GT18-314	0.0016	0.0140	0.0050	0.020
24GTRC005	155.00	160.00	24GT18-315	0.0008	0.0083	0.0050	0.020
24GTRC005	160.00	165.00	24GT18-316	0.0015	0.0096	0.0050	0.020
24GTRC005	165.00	170.00	24GT18-317	0.0013	0.0204	0.0050	0.020
24GTRC005	170.00	175.00	24GT18-318	0.0012	0.0131	0.0050	0.010
24GTRC005	175.00	180.00	24GT18-319	0.0029	0.0059	0.0050	0.020
24GTRC005	180.00	185.00	24GT18-320	0.0055	0.0178	0.0200	0.040
24GTRC005	185.00	190.00	24GT18-322	0.0041	0.0173	0.0050	0.030
24GTRC005	190.00	195.00	24GT18-323	0.0077	0.0123	0.0100	0.060
24GTRC005	195.00	200.00	24GT18-324	0.0022	0.0154	0.0100	0.070
24GTRC005	200.00	205.00	24GT18-325	0.0019	0.0171	0.0100	0.040
24GTRC005	205.00	210.00	24GT18-326	0.0010	0.0162	0.0100	0.020
24GTRC005	210.00	215.00	24GT18-327	0.0057	0.0236	0.0100	0.040
24GTRC005	215.00	220.00	24GT18-328	0.0096	0.0202	0.0100	0.050
24GTRC005	220.00	225.00	24GT18-329	0.0025	0.0189	0.0100	0.020
24GTRC005	225.00	230.00	24GT18-331	0.0033	0.0163	0.0100	0.020
24GTRC005	230.00	235.00	24GT18-332	0.0029	0.0141	0.0100	0.020
24GTRC005	235.00	240.00	24GT18-333	0.0045	0.0134	0.0100	0.040
24GTRC005	240.00	245.00	24GT18-334	0.0017	0.0104	0.0100	0.005
24GTRC005	245.00	250.00	24GT18-335	0.0034	0.0192	0.0100	0.020
24GTRC005	250.00	255.00	24GT18-336	0.0057	0.0209	0.0100	0.050
24GTRC005	255.00	260.00	24GT18-337	0.0073	0.0208	0.0100	0.060
24GTRC005	260.00	265.00	24GT18-338	0.0044	0.0089	0.0100	0.040
24GTRC005	265.00	270.00	24GT18-339	0.0030	0.0096	0.0100	0.020
24GTRC005	270.00	275.00	24GT18-340	0.0024	0.0133	0.0100	0.030
24GTRC005	275.00	280.00	24GT18-341	0.0057	0.0179	0.0100	0.050
24GTRC005	280.00	285.00	24GT18-342	0.0023	0.0115	0.0050	0.020

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
24GTRC005	285.00	290.00	24GT18-343	0.0140	0.0135	0.0050	0.140
24GTRC005	290.00	295.00	24GT18-344	0.0069	0.0167	0.0100	0.050
24GTRC005	295.00	300.00	24GT18-345	0.0021	0.0131	0.0050	0.040
24GTRC005	300.00	305.00	24GT18-346	0.0077	0.0130	0.0100	0.060
24GTRC005	305.00	310.00	24GT18-347	0.0055	0.0168	0.0050	0.050
24GTRC005	310.00	315.00	24GT18-348	0.0038	0.0201	0.0100	0.040
24GTRC005	315.00	320.00	24GT18-349	0.0021	0.0158	0.0050	0.020
24GTRC005	320.00	325.00	24GT18-351	0.0059	0.0125	0.0050	0.060
24GTRC005	325.00	330.00	24GT18-352	0.0021	0.0136	0.0050	0.040
24GTRC005	330.00	335.00	24GT18-353	0.0067	0.0149	0.0050	0.080
24GTRC005	335.00	340.00	24GT18-354	0.0054	0.0174	0.0050	0.050
24GTRC005	340.00	345.00	24GT18-355	0.0150	0.0185	0.0100	0.100
24GTRC005	345.00	350.00	24GT18-356	0.0009	0.0211	0.0050	0.020
24GTRC005	350.00	355.00	24GT18-357	0.0035	0.0181	0.0050	0.020
24GTRC005	355.00	360.00	24GT18-358	0.0074	0.0129	0.0050	0.060
24GTRC005	360.00	365.00	24GT18-359	0.0156	0.0883	0.0050	0.210
24GTRC005	365.00	370.00	24GT18-361	0.0181	0.1240	0.0050	0.170
24GTRC005	370.00	375.00	24GT18-363	0.0045	0.0608	0.0100	0.060
24GTRC005	375.00	380.00	24GT18-364	0.0026	0.0168	0.0050	0.040
24GTRC005	380.00	385.00	24GT18-365	0.0049	0.0076	0.0100	0.060
24GTRC005	385.00	390.00	24GT18-366	0.0008	0.0063	0.0050	0.010
24GTRC005	390.00	395.00	24GT18-367	0.0017	0.0066	0.0050	0.020
24GTRC005	395.00	400.00	24GT18-368	0.0011	0.0100	0.0050	0.010
24GTRC005	400.00	405.00	24GT18-369	0.0002	0.0096	0.0050	0.020
24GTRC005	405.00	410.00	24GT18-370	0.0005	0.0103	0.0050	0.030
24GTRC005	410.00	415.00	24GT18-371	0.0010	0.0163	0.0100	0.030
24GTRC005	415.00	420.00	24GT18-372	0.0178	0.0185	0.0050	0.130
24GTRC005	420.00	425.00	24GT18-373	0.0108	0.0162	0.0100	0.050
24GTRC005	425.00	430.00	24GT18-374	0.0163	0.0166	0.0050	0.060
24GTRC005	430.00	435.00	24GT18-375	0.0015	0.0198	0.0100	0.020
24GTRC005	435.00	440.00	24GT18-376	0.0115	0.0846	0.0100	0.100
24GTRC005	440.00	445.00	24GT18-377	0.0166	0.1205	0.0050	0.130
24GTRC005	445.00	450.00	24GT18-378	0.0077	0.0345	0.0100	0.040
24GTRC005	450.00	455.00	24GT18-379	0.0082	0.0328	0.0050	0.050
24GTRC005	455.00	460.00	24GT18-380	0.0099	0.0152	0.0050	0.030
24GTRC005	460.00	465.00	24GT18-381	0.0048	0.0177	0.0050	0.040
24GTRC005	465.00	470.00	24GT18-382	0.0045	0.0144	0.0050	0.040
24GTRC005	470.00	475.00	24GT18-383	0.0065	0.0143	0.0050	0.040
24GTRC005	475.00	480.00	24GT18-384	0.0035	0.0125	0.0050	0.030
24GTRC005	480.00	485.00	24GT18-385	0.0015	0.0111	0.0050	0.010
24GTRC005	485.00	490.00	24GT18-386	0.0023	0.0150	0.0050	0.020
24GTRC005	490.00	495.00	24GT18-387	0.0036	0.0188	0.0050	0.030
24GTRC005	495.00	500.00	24GT18-388	0.0048	0.0142	0.0050	0.040
24GTRC005	500.00	505.00	24GT18-389	0.0022	0.0176	0.0050	0.010
24GTRC005	505.00	510.00	24GT18-391	0.0025	0.0240	0.0050	0.030
24GTRC005	510.00	515.00	24GT18-392	0.0073	0.0329	0.0050	0.050
24GTRC005	515.00	520.00	24GT18-393	0.0420	0.1510	0.0050	0.300
24GTRC005	520.00	525.00	24GT18-394	0.0040	0.0215	0.0050	0.050
24GTRC005	525.00	530.00	24GT18-395	0.0054	0.0158	0.0050	0.030
24GTRC005	530.00	535.00	24GT18-396	0.0056	0.0116	0.0050	0.020
24GTRC005	535.00	540.00	24GT18-397	0.0116	0.0118	0.0050	0.070
24GTRC005	540.00	545.00	24GT18-398	0.0068	0.0112	0.0050	0.040
24GTRC005	545.00	550.00	24GT18-399	0.0097	0.0106	0.0050	0.080
24GTRC005	550.00	555.00	24GT18-401	0.0231	0.0189	0.0100	0.210
24GTRC005	555.00	560.00	24GT18-403	0.0077	0.0223	0.0050	0.040
24GTRC005	560.00	565.00	24GT18-404	0.0060	0.0226	0.0050	0.020
24GTRC005	565.00	570.00	24GT18-405	0.0024	0.0172	0.0050	0.010
24GTRC005	570.00	575.00	24GT18-406	0.0037	0.0157	0.0100	0.020
24GTRC005	575.00	580.00	24GT18-407	0.0050	0.0165	0.0100	0.030

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
24GTRC005	580.00	585.00	24GT18-408	0.0018	0.0195	0.0100	0.020
24GTRC005	585.00	590.00	24GT18-409	0.0051	0.0264	0.0100	0.030
24GTRC005	590.00	595.00	24GT18-410	0.0662	0.0261	0.0100	0.240
24GTRC005	595.00	600.00	24GT18-411	0.0034	0.0146	0.0100	0.020
24GTRC005	600.00	605.00	24GT18-412	0.0075	0.0127	0.0100	0.070
24GTRC005	605.00	610.00	24GT18-413	0.0015	0.0116	0.0100	0.020
24GTRC005	610.00	615.00	24GT18-414	0.0062	0.0138	0.0100	0.030
24GTRC005	615.00	620.00	24GT18-415	0.0101	0.0176	0.0050	0.050
24GTRC005	620.00	625.00	24GT18-416	0.0092	0.0219	0.0100	0.080
24GTRC005	625.00	630.00	24GT18-417	0.0086	0.0257	0.0100	0.080
24GTRC005	630.00	635.00	24GT18-418	0.0069	0.0180	0.0100	0.040
24GTRC005	635.00	640.00	24GT18-419	0.0052	0.0149	0.0050	0.040
24GTRC005	640.00	643.00	24GT18-421	0.0054	0.0158	0.0100	0.080
24GTRC005	643.00	644.00	24GT18-422	0.0050	0.0154	0.0100	0.040
24GTRC005	644.00	645.00	24GT18-423	0.0087	0.0123	0.0050	0.060
24GTRC005	645.00	646.00	24GT18-424	0.0081	0.0120	0.0050	0.060
24GTRC005	646.00	647.00	24GT18-425	0.0063	0.0100	0.0100	0.050
24GTRC005	647.00	648.00	24GT18-426	0.0046	0.0121	0.0100	0.050
25GTDD001	488.00	489.00	25GT01-280	0.0744	0.5320	0.0300	0.740
25GTDD001	489.00	490.00	25GT01-281	0.2500	0.4720	0.0200	1.550
25GTDD001	490.00	491.00	25GT01-282	0.0628	0.0608	0.0050	0.440
25GTDD001	491.00	492.00	25GT01-283	0.0249	0.0542	0.0050	0.150
25GTDD001	492.00	493.00	25GT01-284	0.0602	0.0428	0.0050	0.280
25GTDD001	493.00	494.00	25GT01-285	0.1020	0.0961	0.0050	0.400
25GTDD001	494.00	495.00	25GT01-286	0.1190	0.4060	0.0050	0.400
25GTDD001	495.00	496.00	25GT01-287	0.0672	0.3920	0.0050	0.260
25GTDD001	496.00	497.00	25GT01-288	0.0206	0.1825	0.0050	0.080
25GTDD001	497.00	498.00	25GT01-289	0.0913	0.0693	0.0100	0.340
25GTDD001	498.00	499.00	25GT01-290	0.0658	0.2540	0.0050	0.230
25GTDD001	499.00	500.00	25GT01-291	0.1285	0.1835	0.0050	0.480
25GTDD001	500.00	501.00	25GT01-292	0.1030	0.2200	0.0100	0.650
25GTDD001	501.00	502.00	25GT01-293	0.0307	0.0886	0.0050	0.100
25GTDD001	502.00	503.00	25GT01-294	0.0324	0.0880	0.0050	0.150
25GTDD001	503.00	504.00	25GT01-295	0.0926	0.1810	0.0050	0.720
25GTDD001	504.00	504.50	25GT01-296	1.9800	0.3320	0.2600	17.250
25GTDD001	504.50	505.50	25GT01-297	0.0603	0.0602	0.0100	0.450
25GTDD001	505.50	506.50	25GT01-298	0.0046	0.0518	0.0050	0.040
25GTDD001	506.50	507.50	25GT01-299	0.0318	0.0476	0.0050	0.180
25GTDD001	507.50	508.50	25GT01-301	0.0017	0.0362	0.0050	0.020
25GTDD001	597.00	598.16	25GT01-307	0.0017	0.0361	0.0400	0.430
25GTDD001	598.16	599.10	25GT01-308	1.4650	0.0251	0.3100	2.070
25GTDD001	599.10	600.10	25GT01-309	2.2100	0.0359	0.3300	2.530
25GTDD001	600.10	601.00	25GT01-310	0.6130	0.0209	0.1200	0.850
25GTDD001	601.00	602.00	25GT01-311	0.9930	0.0327	0.0700	1.150
25GTDD001	602.00	602.50	25GT01-312	0.8850	0.0442	0.0400	1.060
25GTDD001	602.50	603.50	25GT01-313	3.8200	0.1990	0.0300	4.230
25GTDD001	603.50	604.50	25GT01-314	1.2500	0.1700	0.1400	1.890
25GTDD001	604.50	605.50	25GT01-315	0.7320	1.6750	0.0800	1.130
25GTDD001	605.50	606.50	25GT01-316	0.6450	0.4460	0.0700	1.060
25GTDD001	606.50	607.50	25GT01-317	0.5450	3.5800	0.2200	1.210
25GTDD001	607.50	608.10	25GT01-318	1.0400	0.1385	0.1100	1.930
25GTDD001	608.10	609.10	25GT01-319	0.0191	0.0769	0.0100	0.050
25GTDD001	625.31	626.31	25GT01-320	0.0058	0.0722	0.0900	2.090
25GTDD001	626.31	627.31	25GT01-321	2.0800	0.0483	0.6000	4.520
25GTDD001	627.31	628.00	25GT01-322	0.3340	0.0353	0.0900	0.630
25GTDD001	628.00	629.00	25GT01-323	0.4410	0.0264	0.3800	2.630
25GTDD001	629.00	630.00	25GT01-324	1.6100	0.0389	0.2600	3.010
25GTDD001	630.00	631.00	25GT01-326	0.0081	0.0190	0.0800	2.340
25GTDD001	765.50	766.50	25GT01-333	0.0340	0.0112	0.0100	0.540

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
25GTDD001	775.00	776.00	25GT01-335	0.0285	0.0119	0.0100	0.270
25GTDD001	776.00	777.00	25GT01-336	0.0160	0.0121	0.0050	0.360
25GTDD001	777.00	778.00	25GT01-337	0.0088	0.0111	0.0100	0.330
25GTDD001	784.50	785.50	25GT01-338	0.0120	0.0102	0.0100	0.260
25GTDD001	809.50	810.00	25GT01-343	0.0198	0.0149	0.0050	0.200
25GTDD001	810.00	811.00	25GT01-344	0.0184	0.0143	0.0050	0.230
25GTDD001	811.00	812.00	25GT01-345	0.0061	0.0101	0.0050	0.100
25GTDD001	812.00	813.00	25GT01-346	0.0042	0.0095	0.0050	0.090
25GTDD001	813.00	814.00	25GT01-347	0.0050	0.0122	0.0050	0.100
25GTDD001	814.00	815.00	25GT01-348	0.0041	0.0103	0.0050	0.080
25GTDD001	815.00	815.70	25GT01-349	0.0021	0.0109	0.0050	0.060
25GTDD002	277.16	278.00	25GT01-382	0.5150	0.0556	0.0800	1.640
25GTDD002	278.00	279.00	25GT01-383	1.1500	2.7400	0.0900	3.030
25GTDD002	279.00	279.50	25GT01-384	2.9100	8.9700	0.1000	6.090
25GTDD002	279.50	280.00	25GT01-385	3.3700	0.3580	0.0800	7.200
25GTDD002	280.00	280.95	25GT01-386	2.1600	0.0752	0.1100	4.260
25GTDD002	280.95	281.45	25GT01-387	4.0200	1.6750	0.1400	7.550
25GTDD002	281.45	282.65	25GT01-388	0.3230	0.1520	0.0100	0.570
25GTDD002	282.65	283.75	25GT01-389	1.2750	0.1470	0.0500	3.220
25GTDD002	283.75	284.30	25GT01-390	2.6800	0.1765	0.1700	8.200
25GTDD002	284.30	285.40	25GT01-391	0.0541	0.0834	0.0050	0.200
25GTDD002	285.40	286.40	25GT01-392	0.0263	0.0499	0.0050	0.070
25GTDD002	286.40	286.90	25GT01-393	0.1430	0.0329	0.0100	0.430
25GTDD002	286.90	287.40	25GT01-394	0.8530	0.0371	0.0200	2.470
25GTDD002	287.40	288.40	25GT01-395	0.0219	0.0311	0.0050	0.090
25GTDD002	338.44	339.14	25GT01-403	0.2690	0.0648	0.0500	4.130
25GTDD002	339.14	340.04	25GT01-404	0.0519	0.0676	0.0050	0.910
25GTDD002	340.04	341.04	25GT01-405	0.5120	0.0566	0.1300	12.700
25GTDD002	341.05	341.56	25GT01-406	0.1720	0.0557	0.0100	2.180
25GTDD002	342.00	342.50	25GT01-407	0.0788	0.0417	0.0300	2.690
25GTDD002	345.50	346.00	25GT01-409	0.0922	0.0389	0.0400	4.620
25GTDD002	346.00	346.50	25GT01-410	0.0480	0.0449	0.0050	0.660
25GTDD002	352.68	353.78	25GT01-413	0.3510	0.0502	0.0200	1.980
25GTDD002	366.42	367.42	25GT01-419	0.0028	0.0137	0.0100	0.050
25GTDD002	367.42	368.42	25GT01-420	0.0064	0.0112	0.0050	0.110
25GTDD002	368.42	369.42	25GT01-421	0.0042	0.0111	0.0050	0.050
25GTDD002	369.42	370.42	25GT01-422	0.0042	0.0103	0.0050	0.070
25GTDD002	370.42	371.42	25GT01-423	0.0049	0.0100	0.0050	0.040
98WDRC014	0.00	3.00	WC0001	0.0952	0.0287	0.0050	2.000
98WDRC014	3.00	6.00	WC0002	0.0268	0.0186	0.0050	2.000
98WDRC014	6.00	9.00	WC0003	0.0712	0.0182	0.0100	2.000
98WDRC014	9.00	12.00	WC0004	0.0222	0.0255	0.0100	2.000
98WDRC014	12.00	15.00	WC0005	0.0174	0.0282	0.0200	2.000
98WDRC014	15.00	18.00	WC0006	0.0069	0.0259	0.0100	1.000
98WDRC014	18.00	21.00	WC0007	0.0067	0.0271	0.0050	1.000
98WDRC014	21.00	24.00	WC0008	0.0086	0.0186	0.0050	1.000
98WDRC014	24.00	27.00	WC0009	0.0125	0.0138	0.0050	1.000
98WDRC014	27.00	30.00	WC0010	0.0080	0.0121	0.0100	1.000
98WDRC014	30.00	33.00	WC0011	0.0343	0.0109	0.0050	2.000
98WDRC014	33.00	36.00	WC0012	0.0810	0.0209	0.0100	2.000
98WDRC014	36.00	39.00	WC0013	0.0106	0.0359	0.0100	1.000
98WDRC014	39.00	42.00	WC0014	0.0049	0.0315	0.0050	1.000
98WDRC014	42.00	45.00	WC0015	0.0048	0.0446	0.0100	1.000
98WDRC014	45.00	48.00	WC0016	0.0115	0.0250	0.0050	1.000
98WDRC014	48.00	51.00	WC0017	0.0063	0.0257	0.0050	1.000
98WDRC014	51.00	54.00	WC0018	0.0072	0.0169	0.0050	1.000
98WDRC014	54.00	57.00	WC0019	0.0069	0.0098	0.0050	1.000
98WDRC014	57.00	60.00	WC0020	0.0085	0.0098	0.0050	2.000
98WDRC014	60.00	63.00	WC0021	0.0059	0.0065	0.0050	1.000

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
98WDRC014	63.00	66.00	WC0022	0.0055	0.0081	0.0050	2.000
98WDRC014	66.00	69.00	WC0023	0.0037	0.0091	0.0050	0.500
98WDRC014	69.00	72.00	WC0024	0.0029	0.0093	0.0050	1.000
98WDRC014	72.00	75.00	WC0025	0.0018	0.0073	0.0050	1.000
98WDRC014	75.00	78.00	WC0026	0.0012	0.0076	0.0050	0.500
98WDRC014	78.00	80.00	WC0027	0.0044	0.0085	0.0050	1.000
98WDRC015	0.00	3.00	WC0028	0.1130	0.0239	0.0100	1.000
98WDRC015	3.00	6.00	WC0029	0.0321	0.0238	0.0050	1.000
98WDRC015	6.00	9.00	WC0030	0.0095	0.0210	0.0050	0.500
98WDRC015	9.00	12.00	WC0031	0.0061	0.0188	0.0050	0.500
98WDRC015	12.00	15.00	WC0032	0.0072	0.0147	0.0050	0.500
98WDRC015	15.00	18.00	WC0033	0.0075	0.0240	0.0050	2.000
98WDRC015	18.00	21.00	WC0034	0.0069	0.0154	0.0050	1.000
98WDRC015	21.00	24.00	WC0035	0.0062	0.0152	0.0100	0.500
98WDRC015	24.00	27.00	WC0036	0.0038	0.0118	0.0050	1.000
98WDRC015	27.00	30.00	WC0037	0.0018	0.0098	0.0050	1.000
98WDRC015	30.00	33.00	WC0038	0.0081	0.0115	0.0050	1.000
98WDRC015	33.00	36.00	WC0039	0.0242	0.0157	0.0050	1.000
98WDRC015	36.00	39.00	WC0040	0.0239	0.0629	0.0100	1.000
98WDRC015	39.00	42.00	WC0041	0.0100	0.0453	0.0050	1.000
98WDRC015	42.00	45.00	WC0042	0.0191	0.0950	0.0100	1.000
98WDRC015	45.00	48.00	WC0043	0.0118	0.0534	0.0050	1.000
98WDRC015	48.00	51.00	WC0044	0.0087	0.0279	0.0050	2.000
98WDRC016	0.00	3.00	WC0045	0.2180	0.0156	0.0100	2.000
98WDRC016	3.00	6.00	WC0046	0.1140	0.0200	0.0050	2.000
98WDRC016	6.00	9.00	WC0047	0.3120	0.0544	0.0050	2.000
98WDRC016	9.00	12.00	WC0048	0.4090	0.0456	0.0050	2.000
98WDRC016	12.00	15.00	WC0049	0.3480	0.0427	0.0200	2.000
98WDRC016	15.00	18.00	WC0050	0.2910	0.0586	0.0050	2.000
98WDRC016	18.00	21.00	WC0051	0.1290	0.0524	0.0050	2.000
98WDRC016	21.00	24.00	WC0052	0.5680	0.0409	0.0100	4.000
98WDRC016	24.00	27.00	WC0053	0.7480	0.0430	0.0900	9.000
98WDRC016	27.00	30.00	WC0054	0.2510	0.0494	0.2400	10.000
98WDRC016	30.00	33.00	WC0055	0.2480	0.0331	0.1100	3.000
98WDRC016	33.00	36.00	WC0056	0.0889	0.0330	0.0050	1.000
98WDRC016	36.00	39.00	WC0057	0.0528	0.0471	0.0050	2.000
98WDRC016	39.00	42.00	WC0058	0.0850	0.0499	0.0050	1.000
98WDRC016	42.00	45.00	WC0059	0.1350	0.0366	0.0050	1.000
98WDRC016	45.00	48.00	WC0060	0.0165	0.0067	0.0050	0.500
98WDRC016	48.00	51.00	WC0061	0.0183	0.0069	0.0050	0.500
98WDRC017	0.00	3.00	WC0062	0.9500	0.0390	1.2600	9.000
98WDRC017	3.00	6.00	WC0063	1.3300	0.0266	0.4900	11.000
98WDRC017	6.00	9.00	WC0064	0.3820	0.0089	0.1500	3.000
98WDRC017	9.00	12.00	WC0065	0.1790	0.0016	0.0900	1.000
98WDRC017	12.00	15.00	WC0066	0.1210	0.0009	0.0900	0.500
98WDRC017	15.00	18.00	WC0067	0.6510	0.0089	0.0700	6.000
98WDRC017	18.00	21.00	WC0068	0.6890	0.0146	0.0400	4.000
98WDRC017	21.00	24.00	WC0069	0.4240	0.0096	0.0100	1.000
98WDRC017	24.00	27.00	WC0070	0.2320	0.0231	0.0100	2.000
98WDRC017	27.00	30.00	WC0071	0.2110	0.0521	0.0100	2.000
98WDRC017	30.00	33.00	WC0072	0.0597	0.0374	0.0050	2.000
98WDRC017	33.00	36.00	WC0073	0.0329	0.0232	0.0100	2.000
98WDRC017	36.00	39.00	WC0074	0.0459	0.0234	0.0050	2.000
98WDRC017	39.00	42.00	WC0075	0.0614	0.0148	0.0050	2.000
98WDRC017	42.00	45.00	WC0076	0.1360	0.0237	0.0050	2.000
98WDRC017	45.00	48.00	WC0077	1.1500	0.0246	0.0050	2.000
98WDRC017	48.00	51.00	WC0078	1.4800	0.0256	0.0100	3.000
98WDRC017	51.00	54.00	WC0079	1.3500	0.0314	0.0050	2.000
98WDRC017	54.00	57.00	WC0080	0.4220	0.0199	0.0050	2.000

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
98WDRC017	57.00	60.00	WC0081	0.1550	0.0396	0.0100	2.000
98WDRC017	60.00	63.00	WC0082	0.0757	0.0226	0.0100	2.000
98WDRC017	63.00	66.00	WC0083	0.0116	0.0075	0.0050	0.500
98WDRC017	66.00	69.00	WC0084	0.1050	0.0081	0.0050	1.000
98WDRC017	69.00	72.00	WC0085	0.1190	0.0189	0.0050	2.000
98WDRC017	72.00	75.00	WC0086	0.1550	0.0347	0.0050	2.000
98WDRC017	75.00	78.00	WC0087	0.0065	0.0070	0.0050	2.000
98WDRC017	78.00	80.00	WC0088	0.0036	0.0052	0.0050	1.000
98WDRC018	0.00	3.00	WC0089	0.0143	0.0006	0.0200	0.500
98WDRC018	3.00	6.00	WC0090	0.0089	0.0012	0.0100	0.500
98WDRC018	6.00	9.00	WC0091	0.0275	0.0024	0.0050	2.000
98WDRC018	9.00	12.00	WC0092	0.0680	0.0062	0.0050	1.000
98WDRC018	12.00	15.00	WC0093	0.0740	0.0145	0.0050	1.000
98WDRC018	15.00	18.00	WC0094	0.1900	0.0915	0.0050	2.000
98WDRC018	18.00	21.00	WC0095	0.1810	0.1360	0.0050	2.000
98WDRC018	21.00	24.00	WC0096	0.0747	0.0014	0.0100	1.000
98WDRC018	24.00	27.00	WC0097	0.2590	0.0129	0.0100	2.000
98WDRC018	27.00	30.00	WC0098	0.1370	0.0159	0.0050	2.000
98WDRC018	30.00	33.00	WC0099	0.0548	0.0073	0.0050	1.000
98WDRC018	33.00	36.00	WC0100	0.1620	0.0209	0.0100	1.000
98WDRC018	36.00	39.00	WC0101	0.0701	0.0103	0.0050	1.000
98WDRC018	39.00	42.00	WC0102	0.1400	0.0264	0.0050	2.000
98WDRC018	42.00	45.00	WC0103	0.0335	0.0424	0.0050	2.000
98WDRC018	45.00	48.00	WC0104	0.0065	0.0192	0.0050	1.000
98WDRC018	48.00	51.00	WC0105	0.0038	0.0416	0.0050	1.000
98WDRC018	51.00	54.00	WC0106	0.0043	0.0274	0.0050	2.000
98WDRC018	54.00	57.00	WC0107	0.0012	0.0682	0.0100	2.000
98WDRC018	57.00	60.00	WC0108	0.0043	0.0664	0.0050	2.000
98WDRC018	60.00	63.00	WC0109	0.0038	0.0341	0.0050	0.500
98WDRC018	63.00	66.00	WC0110	0.0003	0.0205	0.0050	2.000
98WDRC018	66.00	69.00	WC0111	0.0009	0.0154	0.0050	1.000
98WDRC018	69.00	72.00	WC0112	0.0055	0.0426	0.0050	2.000
98WDRC018	72.00	75.00	WC0113	0.0089	0.0275	0.0050	2.000
98WDRC018	75.00	78.00	WC0114	0.0126	0.0418	0.0050	2.000
98WDRC018	78.00	80.00	WC0115	0.0074	0.0398	0.0100	1.000
98WDRC018	80.00	83.00	WC0116	0.0014	0.0101	0.0050	1.000
98WDRC018	83.00	86.00	WC0117	0.0003	0.0074	0.0050	1.000
AWRC075	0.00	1.00	ARV010867	0.0039	0.0156	0.0050	0.250
AWRC075	1.00	2.00	ARV010868	0.0062	0.0209	0.0050	0.250
AWRC075	2.00	3.00	ARV010869	0.0055	0.0253	0.0050	0.250
AWRC075	3.00	4.00	ARV010870	0.0053	0.0211	0.0050	0.250
AWRC075	4.00	5.00	ARV010871	0.0077	0.0268	0.0050	0.250
AWRC075	5.00	6.00	ARV010872	0.0037	0.0280	0.0100	0.250
AWRC075	6.00	7.00	ARV010873	0.0557	0.0394	0.0050	0.250
AWRC075	7.00	8.00	ARV010874	0.0469	0.0204	0.0050	0.250
AWRC075	8.00	9.00	ARV010875	0.0085	0.0174	0.0050	0.250
AWRC075	9.00	10.00	ARV010876	0.0047	0.0331	0.0050	0.250
AWRC075	10.00	11.00	ARV010877	0.0062	0.0213	0.0050	0.250
AWRC075	11.00	12.00	ARV010878	0.0049	0.0186	0.0050	0.250
AWRC075	12.00	13.00	ARV010879	0.0080	0.0143	0.0050	0.250
AWRC075	13.00	14.00	ARV010880	0.0072	0.0168	0.0050	0.250
AWRC075	14.00	15.00	ARV010883	0.0110	0.0207	0.0050	0.250
AWRC075	15.00	16.00	ARV010884	0.0041	0.0166	0.0050	0.250
AWRC075	16.00	17.00	ARV010885	0.0198	0.0178	0.0050	0.250
AWRC075	17.00	18.00	ARV010886	0.0253	0.0117	0.0050	0.250
AWRC075	18.00	19.00	ARV010887	0.0052	0.0148	0.0050	0.250
AWRC075	19.00	20.00	ARV010888	0.0050	0.0180	0.0050	0.250
AWRC075	20.00	21.00	ARV010889	0.0010	0.0250	0.0050	0.250
AWRC075	21.00	22.00	ARV010890	0.0043	0.0169	0.0050	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
AWRC075	22.00	23.00	ARV010891	0.0069	0.0278	0.0050	0.250
AWRC075	23.00	24.00	ARV010892	0.0043	0.0192	0.0050	0.250
AWRC075	24.00	25.00	ARV010893	0.0020	0.0347	0.0050	0.250
AWRC075	25.00	26.00	ARV010894	0.0039	0.0489	0.0050	0.250
AWRC075	26.00	27.00	ARV010895	0.0036	0.0351	0.0050	0.250
AWRC075	27.00	28.00	ARV010896	0.0018	0.0447	0.0050	0.250
AWRC075	28.00	29.00	ARV010897	0.0086	0.0195	0.0050	0.250
AWRC075	29.00	30.00	ARV010898	0.0109	0.0341	0.0050	0.250
AWRC075	30.00	31.00	ARV010899	0.0031	0.0291	0.0050	0.250
AWRC075	31.00	32.00	ARV010900	0.0056	0.0420	0.0050	0.250
AWRC075	32.00	33.00	ARV010903	0.0199	0.0395	0.0050	0.250
AWRC075	33.00	34.00	ARV010904	0.0058	0.0161	0.0050	0.250
AWRC075	34.00	35.00	ARV010905	0.0043	0.0119	0.0050	0.250
AWRC075	35.00	36.00	ARV010906	0.0010	0.0091	0.0050	0.250
AWRC075	36.00	37.00	ARV010907	0.0011	0.0202	0.0050	0.250
AWRC075	37.00	38.00	ARV010908	0.0004	0.0182	0.0050	0.250
AWRC075	38.00	39.00	ARV010909	0.0008	0.0108	0.0050	0.250
AWRC075	39.00	40.00	ARV010910	0.0007	0.0064	0.0050	0.250
AWRC075	40.00	41.00	ARV010911	0.0004	0.0110	0.0050	0.250
AWRC075	41.00	42.00	ARV010912	0.0001	0.0072	0.0050	0.250
AWRC075	42.00	43.00	ARV010913	0.0002	0.0050	0.0050	0.250
AWRC075	43.00	44.00	ARV010914	0.0005	0.0072	0.0050	0.250
AWRC075	44.00	45.00	ARV010915	0.0014	0.0114	0.0050	0.250
AWRC075	45.00	46.00	ARV010916	0.0008	0.0165	0.0050	0.250
AWRC075	46.00	47.00	ARV010917	0.0015	0.0134	0.0050	0.250
AWRC075	47.00	48.00	ARV010918	0.0023	0.0101	0.0050	0.250
AWRC075	48.00	49.00	ARV010919	0.0036	0.0100	0.0050	0.250
AWRC075	49.00	50.00	ARV010920	0.0023	0.0046	0.0050	0.250
AWRC075	50.00	51.00	ARV010923	0.0011	0.0059	0.0050	0.250
AWRC075	51.00	52.00	ARV010924	0.0008	0.0112	0.0050	0.250
AWRC075	52.00	53.00	ARV010925	0.0005	0.0043	0.0050	0.250
AWRC075	53.00	54.00	ARV010926	0.0004	0.0045	0.0050	0.250
AWRC075	54.00	55.00	ARV010927	0.0027	0.0127	0.0050	0.250
AWRC075	55.00	56.00	ARV010928	0.0030	0.0140	0.0050	0.250
AWRC075	56.00	57.00	ARV010929	0.0012	0.0124	0.0050	0.250
AWRC075	57.00	58.00	ARV010930	0.0008	0.0117	0.0050	0.250
AWRC075	58.00	59.00	ARV010931	0.0035	0.0149	0.0050	0.250
AWRC075	59.00	60.00	ARV010932	0.0170	0.0126	0.0050	0.250
AWRC075	60.00	61.00	ARV010933	0.0119	0.0164	0.0050	0.250
AWRC075	61.00	62.00	ARV010934	0.0079	0.0182	0.0050	0.250
AWRC075	62.00	63.00	ARV010935	0.0047	0.0106	0.0050	0.250
AWRC075	63.00	64.00	ARV010936	0.0062	0.0126	0.0050	0.250
AWRC075	64.00	65.00	ARV010937	0.0021	0.0110	0.0050	0.250
AWRC075	65.00	66.00	ARV010938	0.0034	0.0102	0.0050	0.250
AWRC075	66.00	67.00	ARV010939	0.0064	0.0154	0.0050	0.250
AWRC075	67.00	68.00	ARV010940	0.0169	0.0195	0.0050	0.250
AWRC075	68.00	69.00	ARV010943	0.0101	0.0241	0.0050	0.250
AWRC075	69.00	70.00	ARV010944	0.0025	0.0068	0.0050	0.250
AWRC075	70.00	71.00	ARV010945	0.0065	0.0078	0.0050	0.250
AWRC075	71.00	72.00	ARV010946	0.0073	0.0084	0.0050	0.250
AWRC075	72.00	73.00	ARV010947	0.0023	0.0052	0.0050	0.250
AWRC075	73.00	74.00	ARV010948	0.0029	0.0057	0.0050	0.250
AWRC075	74.00	75.00	ARV010949	0.0022	0.0064	0.0050	0.250
AWRC075	75.00	76.00	ARV010950	0.0020	0.0064	0.0050	0.250
AWRC075	76.00	77.00	ARV010951	0.0021	0.0072	0.0050	0.250
AWRC075	77.00	78.00	ARV010952	0.0012	0.0055	0.0050	0.250
AWRC075	78.00	79.00	ARV010953	0.0004	0.0052	0.0050	0.250
AWRC075	79.00	80.00	ARV010954	0.0003	0.0044	0.0050	0.250
AWRC075	80.00	81.00	ARV010955	0.0002	0.0042	0.0050	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
AWRC075	81.00	82.00	ARV010956	0.0003	0.0052	0.0050	0.250
AWRC075	82.00	83.00	ARV010957	0.0003	0.0034	0.0050	0.250
AWRC075	83.00	84.00	ARV010958	0.0002	0.0055	0.0050	0.250
AWRC075	84.00	85.00	ARV010959	0.0001	0.0073	0.0050	0.250
AWRC075	85.00	86.00	ARV010960	0.0001	0.0099	0.0050	0.250
AWRC075	86.00	87.00	ARV010963	0.0003	0.0107	0.0050	0.250
AWRC075	87.00	88.00	ARV010964	0.0002	0.0101	0.0050	0.250
AWRC075	88.00	89.00	ARV010965	0.0010	0.0129	0.0050	0.250
AWRC075	89.00	90.00	ARV010966	0.1310	0.0550	0.0050	0.250
AWRC075	90.00	91.00	ARV010967	0.0020	0.0106	0.0050	0.250
AWRC075	91.00	92.00	ARV010968	0.0004	0.0094	0.0050	0.250
AWRC075	92.00	93.00	ARV010969	0.0002	0.0102	0.0050	0.250
AWRC075	93.00	94.00	ARV010970	0.0006	0.0111	0.0050	0.250
AWRC075	94.00	95.00	ARV010971	0.0075	0.0168	0.0050	0.250
AWRC075	95.00	96.00	ARV010972	0.0490	0.0209	0.0050	0.250
AWRC075	96.00	97.00	ARV010973	0.0668	0.0195	0.0050	0.250
AWRC075	97.00	98.00	ARV010974	0.0032	0.0901	0.0050	0.250
AWRC075	98.00	99.00	ARV010975	0.0259	0.1350	0.0050	0.250
AWRC075	99.00	100.00	ARV010976	0.6640	2.3600	0.0400	1.800
AWRC075	100.00	101.00	ARV010977	0.4710	1.1700	0.0050	1.100
AWRC075	101.00	102.00	ARV010978	0.4790	1.4150	0.0100	1.100
AWRC075	102.00	103.00	ARV010979	1.0150	0.2210	0.0500	2.000
AWRC075	103.00	104.00	ARV010980	0.0402	0.0965	0.0050	0.250
AWRC075	104.00	105.00	ARV010983	0.0318	0.0824	0.0050	0.250
AWRC075	105.00	106.00	ARV010984	0.0215	0.0621	0.0050	0.250
AWRC075	106.00	107.00	ARV010985	0.0165	0.0717	0.0050	0.250
AWRC075	107.00	108.00	ARV010986	0.0115	0.0618	0.0050	0.250
AWRC075	108.00	109.00	ARV010987	0.0075	0.0397	0.0050	0.250
AWRC075	109.00	110.00	ARV010988	0.0059	0.0328	0.0050	0.250
AWRC075	110.00	111.00	ARV010989	0.0029	0.0387	0.0050	0.250
AWRC075	111.00	112.00	ARV010990	0.0021	0.0163	0.0050	0.250
AWRC075	112.00	113.00	ARV010991	0.0049	0.0235	0.0050	0.250
AWRC075	113.00	114.00	ARV010992	0.0230	0.0309	0.0050	0.250
AWRC077	0.00	1.00	ARV012119	0.0064	0.0106	0.0050	0.250
AWRC077	1.00	2.00	ARV012120	0.0014	0.0063	0.0050	0.250
AWRC077	2.00	3.00	ARV012123	0.0005	0.0067	0.0050	0.250
AWRC077	3.00	4.00	ARV012124	0.0003	0.0136	0.0050	0.250
AWRC077	4.00	5.00	ARV012125	0.0008	0.0134	0.0050	0.250
AWRC077	5.00	6.00	ARV012126	0.0007	0.0122	0.0050	0.250
AWRC077	6.00	7.00	ARV012127	0.0025	0.0129	0.0050	0.250
AWRC077	7.00	8.00	ARV012128	0.0025	0.0151	0.0050	0.250
AWRC077	8.00	9.00	ARV012129	0.0023	0.0157	0.0050	0.250
AWRC077	9.00	10.00	ARV012130	0.0128	0.0121	0.0050	0.250
AWRC077	10.00	11.00	ARV012131	0.0056	0.0143	0.0050	0.250
AWRC077	11.00	12.00	ARV012132	0.0070	0.0125	0.0050	0.250
AWRC077	12.00	13.00	ARV012133	0.0106	0.0118	0.0050	0.250
AWRC077	13.00	14.00	ARV012134	0.0020	0.0132	0.0050	0.250
AWRC077	14.00	15.00	ARV012135	0.0016	0.0123	0.0050	0.250
AWRC077	15.00	16.00	ARV012136	0.0026	0.0161	0.0050	0.250
AWRC077	16.00	17.00	ARV012137	0.0005	0.0147	0.0050	0.250
AWRC077	17.00	18.00	ARV012138	0.0010	0.0167	0.0050	0.250
AWRC077	18.00	19.00	ARV012139	0.0014	0.0136	0.0050	0.250
AWRC077	19.00	20.00	ARV012140	0.0005	0.0183	0.0050	0.250
AWRC077	20.00	21.00	ARV012143	0.0024	0.0200	0.0050	0.250
AWRC077	21.00	22.00	ARV012144	0.0129	0.0265	0.0050	0.250
AWRC077	22.00	23.00	ARV012145	0.0024	0.0364	0.0050	0.250
AWRC077	23.00	24.00	ARV012146	0.0046	0.0421	0.0050	0.250
AWRC077	24.00	25.00	ARV012147	0.0104	0.0322	0.0050	0.250
AWRC077	25.00	26.00	ARV012148	0.0045	0.0338	0.0050	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
AWRC077	26.00	27.00	ARV012149	0.0146	0.0550	0.0050	0.250
AWRC077	27.00	28.00	ARV012150	0.0040	0.0213	0.0050	0.250
AWRC077	28.00	29.00	ARV012151	0.0019	0.0118	0.0050	0.250
AWRC077	29.00	30.00	ARV012152	0.0033	0.0145	0.0050	0.250
AWRC077	30.00	31.00	ARV012153	0.0048	0.0168	0.0050	0.250
AWRC077	31.00	32.00	ARV012154	0.0026	0.0121	0.0050	0.250
AWRC077	32.00	33.00	ARV012155	0.0043	0.0128	0.0050	0.250
AWRC077	33.00	34.00	ARV012156	0.0026	0.0102	0.0050	0.250
AWRC077	34.00	35.00	ARV012157	0.0025	0.0108	0.0050	0.250
AWRC077	35.00	36.00	ARV012158	0.0024	0.0094	0.0050	0.250
AWRC077	36.00	37.00	ARV012159	0.0033	0.0074	0.0050	0.250
AWRC077	37.00	38.00	ARV012160	0.0026	0.0040	0.0050	0.250
AWRC077	38.00	39.00	ARV012163	0.0014	0.0043	0.0050	0.250
AWRC077	39.00	40.00	ARV012164	0.0017	0.0053	0.0050	0.250
AWRC077	40.00	41.00	ARV012165	0.0003	0.0064	0.0050	0.250
AWRC077	41.00	42.00	ARV012166	0.0040	0.0109	0.0050	0.250
AWRC077	42.00	43.00	ARV012167	0.0018	0.0136	0.0050	0.250
AWRC077	43.00	44.00	ARV012168	0.0071	0.0084	0.0050	0.250
AWRC077	44.00	45.00	ARV012169	0.0024	0.0190	0.0050	0.250
AWRC077	45.00	46.00	ARV012170	0.0121	0.0191	0.0050	0.250
AWRC077	46.00	47.00	ARV012171	0.0130	0.0575	0.0050	0.250
AWRC077	47.00	48.00	ARV012172	0.0120	0.0670	0.0050	0.250
AWRC077	48.00	49.00	ARV012173	0.0007	0.0361	0.0050	0.250
AWRC077	49.00	50.00	ARV012174	0.0248	0.0224	0.0050	0.250
AWRC077	50.00	51.00	ARV012175	0.1960	0.0393	0.0050	1.100
AWRC077	51.00	52.00	ARV012176	0.0128	0.0217	0.0050	0.250
AWRC077	52.00	53.00	ARV012177	0.0048	0.0165	0.0050	0.250
AWRC077	53.00	54.00	ARV012178	0.6410	0.0253	0.0200	3.600
AWRC077	54.00	55.00	ARV012179	1.5050	0.0489	0.0100	3.700
AWRC077	55.00	56.00	ARV012180	1.2400	0.0306	0.0050	4.400
AWRC077	56.00	57.00	ARV012183	1.1050	0.0215	0.0100	3.900
AWRC077	57.00	58.00	ARV012184	0.7770	0.0089	0.0100	3.300
AWRC077	58.00	59.00	ARV012185	0.5580	0.0146	0.0300	3.100
AWRC077	59.00	60.00	ARV012186	2.0500	0.0956	0.0300	6.900
AWRC077	60.00	61.00	ARV012187	1.3750	0.1200	0.0300	4.600
AWRC077	61.00	62.00	ARV012188	1.6600	0.1130	0.0300	5.500
AWRC077	62.00	63.00	ARV012189	1.0750	0.0322	0.0300	3.200
AWRC077	63.00	64.00	ARV012190	0.6420	0.0273	0.0300	2.300
AWRC077	64.00	65.00	ARV012191	0.5750	0.0314	0.0400	1.800
AWRC077	65.00	66.00	ARV012192	0.4960	0.0244	0.0400	1.500
AWRC077	66.00	67.00	ARV012193	0.5410	0.0343	0.0200	1.700
AWRC077	67.00	68.00	ARV012194	0.3070	0.0250	0.0300	1.100
AWRC077	68.00	69.00	ARV012195	0.3650	0.0223	0.0200	1.200
AWRC077	69.00	70.00	ARV012196	0.4620	0.0312	0.0600	1.300
AWRC077	70.00	71.00	ARV012197	0.2200	0.0476	0.0050	0.900
AWRC077	71.00	72.00	ARV012198	0.0542	0.0194	0.0050	0.250
AWRC077	72.00	73.00	ARV012199	0.0207	0.0124	0.0050	0.250
AWRC077	73.00	74.00	ARV012200	0.0166	0.0103	0.0050	0.250
AWRC077	74.00	75.00	ARV012203	0.0180	0.0113	0.0050	0.250
AWRC077	75.00	76.00	ARV012204	0.0113	0.0137	0.0050	0.250
AWRC077	76.00	77.00	ARV012205	0.0198	0.0080	0.0050	0.250
AWRC077	77.00	78.00	ARV012206	0.0066	0.0068	0.0100	0.250
AWRC077	78.00	79.00	ARV012207	0.0013	0.0101	0.0400	0.250
AWRC077	79.00	80.00	ARV012208	0.0009	0.0113	0.0050	0.250
AWRC077	80.00	81.00	ARV012209	0.0023	0.0083	0.0050	0.250
AWRC077	81.00	82.00	ARV012210	0.0055	0.0075	0.1000	0.250
AWRC077	82.00	83.00	ARV012211	0.0501	0.0077	0.0050	0.250
AWRC077	83.00	84.00	ARV012212	0.0052	0.0085	0.0050	0.250
AWRC077	84.00	85.00	ARV012213	0.0042	0.0107	0.0050	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
AWRC077	85.00	86.00	ARV012214	0.0006	0.0095	0.0050	0.250
AWRC077	86.00	87.00	ARV012215	0.0008	0.0086	0.0050	0.250
AWRC077	87.00	88.00	ARV012216	0.0007	0.0087	0.0050	0.250
AWRC077	88.00	89.00	ARV012217	0.0007	0.0093	0.0050	0.250
AWRC077	89.00	90.00	ARV012218	0.0015	0.0111	0.0050	0.250
AWRC077	90.00	91.00	ARV012219	0.0006	0.0100	0.0050	0.250
AWRC077	91.00	92.00	ARV012220	0.0006	0.0094	0.0050	0.250
AWRC077	92.00	93.00	ARV012223	0.0006	0.0114	0.0050	0.250
AWRC077	93.00	94.00	ARV012224	0.0005	0.0137	0.0200	0.250
AWRC077	94.00	95.00	ARV012225	0.0006	0.0148	0.0050	0.250
AWRC077	95.00	96.00	ARV012226	0.0028	0.0166	0.0050	0.250
AWRC077	96.00	97.00	ARV012227	0.0008	0.0232	0.0050	0.250
AWRC077	97.00	98.00	ARV012228	0.0015	0.0156	0.0050	0.250
AWRC077	98.00	99.00	ARV012229	0.0061	0.0158	0.0050	0.250
AWRC077	99.00	100.00	ARV012230	0.0124	0.0163	0.0050	0.250
AWRC087	0.00	1.00	ARV013363	0.0031	0.0091	0.0050	0.250
AWRC087	1.00	2.00	ARV013364	0.0018	0.0054	0.0050	0.250
AWRC087	2.00	3.00	ARV013365	0.0044	0.0071	0.0050	0.250
AWRC087	3.00	4.00	ARV013366	0.0014	0.0061	0.0050	0.250
AWRC087	4.00	5.00	ARV013367	0.0025	0.0051	0.0050	0.250
AWRC087	5.00	6.00	ARV013368	0.0055	0.0048	0.0050	0.250
AWRC087	6.00	7.00	ARV013369	0.0017	0.0089	0.0050	0.250
AWRC087	7.00	8.00	ARV013370	0.0030	0.0073	0.0050	0.250
AWRC087	8.00	9.00	ARV013371	0.0044	0.0110	0.0050	0.250
AWRC087	9.00	10.00	ARV013372	0.0080	0.0091	0.0050	0.250
AWRC087	10.00	11.00	ARV013373	0.0024	0.0070	0.0050	0.250
AWRC087	11.00	12.00	ARV013374	0.0030	0.0220	0.0050	0.250
AWRC087	12.00	13.00	ARV013375	0.0111	0.0151	0.0050	0.250
AWRC087	13.00	14.00	ARV013376	0.0054	0.0108	0.0050	0.250
AWRC087	14.00	15.00	ARV013377	0.0019	0.0106	0.0100	0.250
AWRC087	15.00	16.00	ARV013378	0.0013	0.0148	0.0050	0.250
AWRC087	16.00	17.00	ARV013379	0.0032	0.0120	0.0050	0.250
AWRC087	17.00	18.00	ARV013380	0.0143	0.0190	0.0050	0.250
AWRC087	18.00	19.00	ARV013383	0.0020	0.0085	0.0050	0.250
AWRC087	19.00	20.00	ARV013384	0.0040	0.0085	0.0050	0.250
AWRC087	20.00	21.00	ARV013385	0.0037	0.0097	0.0050	0.250
AWRC087	21.00	22.00	ARV013386	0.0005	0.0124	0.0050	0.250
AWRC087	22.00	23.00	ARV013387	0.0055	0.0105	0.0050	0.250
AWRC087	23.00	24.00	ARV013388	0.0078	0.0122	0.0050	0.250
AWRC087	24.00	25.00	ARV013389	0.0012	0.0119	0.0050	0.250
AWRC087	25.00	26.00	ARV013390	0.0014	0.0126	0.0050	0.250
AWRC087	26.00	27.00	ARV013391	0.0070	0.0123	0.0050	0.250
AWRC087	27.00	28.00	ARV013392	0.0079	0.0138	0.0050	0.250
AWRC087	28.00	29.00	ARV013393	0.0064	0.0127	0.0050	0.250
AWRC087	29.00	30.00	ARV013394	0.0168	0.0136	0.0050	0.250
AWRC087	30.00	31.00	ARV013395	0.0059	0.0168	0.0100	0.250
AWRC087	31.00	32.00	ARV013396	0.0008	0.0119	0.0050	0.250
AWRC087	32.00	33.00	ARV013397	0.0050	0.0093	0.0050	0.250
AWRC087	33.00	34.00	ARV013398	0.0006	0.0129	0.0050	0.250
AWRC087	34.00	35.00	ARV013399	0.0011	0.0128	0.0050	0.250
AWRC087	35.00	36.00	ARV013400	0.0001	0.0138	0.0050	0.250
AWRC087	36.00	37.00	ARV013403	0.0007	0.0139	0.0050	0.250
AWRC087	37.00	38.00	ARV013404	0.0003	0.0142	0.0050	0.250
AWRC087	38.00	39.00	ARV013405	0.0008	0.0119	0.0050	0.250
AWRC087	39.00	40.00	ARV013406	0.0002	0.0119	0.0050	0.250
AWRC087	40.00	41.00	ARV013407	0.0009	0.0139	0.0100	0.250
AWRC087	41.00	42.00	ARV013408	0.0047	0.0084	0.0050	0.250
AWRC087	42.00	43.00	ARV013409	0.0053	0.0058	0.0050	0.250
AWRC087	43.00	44.00	ARV013410	0.0014	0.0062	0.0050	0.250

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
AWRC087	44.00	45.00	ARV013411	0.0028	0.0070	0.0050	0.250
AWRC087	45.00	46.00	ARV013412	0.0076	0.0099	0.0050	0.250
AWRC087	46.00	47.00	ARV013413	0.0017	0.0133	0.0050	0.250
AWRC087	47.00	48.00	ARV013414	0.0017	0.0124	0.0050	0.250
AWRC087	48.00	49.00	ARV013415	0.0005	0.0051	0.0050	0.250
AWRC087	49.00	50.00	ARV013416	0.0054	0.0108	0.0050	0.250
AWRC087	50.00	51.00	ARV013417	0.0014	0.0042	0.0050	0.250
AWRC087	51.00	52.00	ARV013418	0.0012	0.0043	0.0050	0.250
AWRC087	52.00	53.00	ARV013419	0.0002	0.0050	0.0050	0.250
AWRC087	53.00	54.00	ARV013420	0.0001	0.0070	0.0050	0.250
AWRC087	54.00	55.00	ARV013423	0.0001	0.0070	0.0050	0.250
AWRC087	55.00	56.00	ARV013424	0.0001	0.0051	0.0100	0.250
AWRC087	56.00	57.00	ARV013425	0.0002	0.0044	0.0050	0.250
AWRC087	57.00	58.00	ARV013426	0.0014	0.0051	0.0050	0.250
AWRC087	58.00	59.00	ARV013427	0.0020	0.0059	0.0050	0.250
AWRC087	59.00	60.00	ARV013428	0.0019	0.0079	0.0050	0.250
AWRC087	60.00	61.00	ARV013429	0.0043	0.0125	0.0100	0.250
AWRC087	61.00	62.00	ARV013430	0.0030	0.0129	0.0050	0.250
AWRC087	62.00	63.00	ARV013431	0.0255	0.0126	0.0050	0.250
AWRC087	63.00	64.00	ARV013432	0.0007	0.0114	0.0050	0.250
AWRC087	64.00	65.00	ARV013433	0.0016	0.0106	0.0050	0.250
AWRC087	65.00	66.00	ARV013434	0.0055	0.0111	0.0050	0.250
AWRC087	66.00	67.00	ARV013435	0.0056	0.0148	0.0050	0.250
AWRC087	67.00	68.00	ARV013436	0.0158	0.0416	0.0050	0.250
AWRC087	68.00	69.00	ARV013437	0.0197	0.0380	0.0050	0.250
AWRC087	69.00	70.00	ARV013438	0.0215	0.0357	0.0050	0.250
AWRC087	70.00	71.00	ARV013439	0.0051	0.0133	0.0050	0.250
AWRC087	71.00	72.00	ARV013440	0.0028	0.0123	0.0050	0.250
AWRC087	72.00	73.00	ARV013443	0.0031	0.0124	0.0050	0.250
AWRC087	73.00	74.00	ARV013444	0.0025	0.0115	0.0050	0.250
AWRC087	74.00	75.00	ARV013445	0.0080	0.0096	0.0050	0.250
AWRC087	75.00	76.00	ARV013446	0.0023	0.0129	0.0050	0.250
AWRC087	76.00	77.00	ARV013447	0.0007	0.0134	0.0050	0.250
AWRC087	77.00	78.00	ARV013448	0.0039	0.0140	0.0050	0.250
AWRC087	78.00	79.00	ARV013449	0.0083	0.0131	0.0050	0.250
AWRC087	79.00	80.00	ARV013450	0.0005	0.0141	0.0050	0.250
AWRC087	80.00	81.00	ARV013451	0.0003	0.0141	0.0050	0.250
AWRC087	81.00	82.00	ARV013452	0.0091	0.0178	0.0050	0.250
AWRC087	82.00	83.00	ARV013453	0.1510	0.0461	0.0050	0.600
AWRC087	83.00	84.00	ARV013454	0.0898	0.0438	0.0050	0.250
AWRC087	84.00	85.00	ARV013455	0.7520	0.0120	0.0050	3.000
AWRC087	85.00	86.00	ARV013456	0.0901	0.0190	0.0050	0.250
AWRC087	86.00	87.00	ARV013457	0.0220	0.0122	0.0050	0.250
AWRC087	87.00	88.00	ARV013458	0.0333	0.0091	0.0050	0.250
AWRC087	88.00	89.00	ARV013459	0.0282	0.0104	0.0050	0.250
AWRC087	89.00	90.00	ARV013460	0.0825	0.0128	0.0050	0.250
AWRC087	90.00	91.00	ARV013463	0.0068	0.0209	0.0050	0.250
AWRC087	91.00	92.00	ARV013464	0.0050	0.0200	0.0050	0.250
AWRC087	92.00	93.00	ARV013465	0.0008	0.0300	0.0050	0.250
AWRC087	93.00	94.00	ARV013466	0.0071	0.0176	0.0050	0.250
AWRC087	94.00	95.00	ARV013467	0.0078	0.0159	0.0100	0.250
AWRC087	95.00	96.00	ARV013468	0.0046	0.0145	0.0050	0.250
AWRC087	96.00	97.00	ARV013469	0.0050	0.0184	0.0050	0.250
AWRC087	97.00	98.00	ARV013470	0.0167	0.0140	0.0050	0.250
AWRC087	98.00	99.00	ARV013471	0.0070	0.0195	0.0050	0.250
AWRC087	99.00	100.00	ARV013472	0.0186	0.0106	0.0050	0.250
P6	0.00	1.52	100	0.0100	0.0600		0.005
P6	1.52	3.05	101	0.9300	0.0500		0.005
P6	3.05	4.57	102	0.3100	0.0100		0.005

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
P6	4.57	6.10	103	0.1200	0.0100		0.005
P6	6.10	7.62	104	0.1700	0.0100		0.005
P6	7.62	9.14	105	0.0600	0.0100		1.000
P6	9.14	10.67	106	0.2700	0.0200		0.005
P6	10.67	12.19	107	0.2600	0.0100		0.005
P6	12.19	13.72	108	0.2900	0.0100		0.005
P6	13.72	15.24	109	0.0700	0.0200		1.000
P6	15.24	16.76	110	0.0400	0.0200		1.000
P6	16.76	18.29	111	0.0200	0.0300		0.005
P6	18.29	19.81	112	0.0100	0.0700		0.005
P6	19.81	21.34	113	0.0300	0.0800		0.005
P6	21.34	22.86	114	0.0100	0.0600		0.005
P6	22.86	24.38	115	0.0100	0.0400		0.005
P6	24.38	25.91	116	0.0100	0.0300		0.005
P6	25.91	27.43	117	0.0100	0.0200		0.005
P6	27.43	28.96	118	0.0100	0.0200		0.005
P6	28.96	30.48	119	0.0011	0.0200		0.005
P7	0.00	1.52	120	0.0100	0.0200		0.005
P7	1.52	3.05	121	0.0100	0.0300		0.005
P7	3.05	4.57	122	0.0100	0.0200		0.005
P7	4.57	6.10	123	0.0100	0.0300		0.005
P7	6.10	7.62	124	0.0100	0.0400		0.005
P7	7.62	9.14	125	0.4100	0.0400		0.005
P7	9.14	10.67	126	0.3500	0.1300		0.005
P7	10.67	12.19	127	0.3800	0.1600		0.005
P7	12.19	13.72	128	2.3500	0.1000		0.005
P7	13.72	15.24	129	1.1300	0.0400		0.005
P7	15.24	16.76	130	0.9800	0.0400		1.000
P7	16.76	18.29	131	0.0011	0.0100		0.005
P7	18.29	19.81	132	0.0011	0.0100		0.005
P7	19.81	21.34	133	0.0011	0.0100		0.005
P7	21.34	22.86	134	0.0011	0.0200		0.005
P7	22.86	24.38	135	0.0011	0.0100		0.005
P7	24.38	25.91	136	0.0011	0.0200		0.005
P7	25.91	27.43	137	0.0100	0.0200		0.005
P7	27.43	28.96	138	0.0100	0.0200		0.005
P74	0.00	1.52	459	0.0011	0.0200		0.005
P74	1.52	3.05	460	0.0011	0.0400		0.005
P74	3.05	4.57	461	0.0100	0.0400		0.005
P74	4.57	6.10	462	0.0100	0.0200		0.005
P74	6.10	7.62	463	0.0011	0.0100		0.005
P74	7.62	9.14	464	0.0011	0.0500		0.005
P74	9.14	10.67	465	0.0011	0.0400		0.005
P74	10.67	12.19	466	0.0100	0.0200		0.005
P74	12.19	13.72	467	0.0100	0.0200		0.005
P74	13.72	15.24	468	0.0011	0.0100		0.005
P74	15.24	16.76	469	0.0100	0.0100		0.005
P74	16.76	18.29	470	0.0200	0.0100		0.005
P74	18.29	19.81	471	0.0700	0.0200		0.005
P74	19.81	21.34	472	0.0900	0.0200		0.005
P74	21.34	22.86	473	2.2600	0.0900		0.005
P74	22.86	24.38	474	0.0500	0.0400		0.005
P74	24.38	25.91	475	0.0700	0.0400		0.005
P74	25.91	27.43	476	0.2100	0.2000		0.005
P74	27.43	28.96	477	0.0200	0.0700		0.005
P74	28.96	30.48	478	0.0200	0.0700		0.005
P74	30.48	32.00	479	0.0200	0.0400		0.005
P74	32.00	33.53	480	0.0300	0.0400		0.005
P74	33.53	35.05	481	0.0200	0.0400		0.005

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
P74	35.05	36.58	482	0.0500	0.0500		0.005
P75	0.00	1.52	484	0.0100	0.0300		0.005
P75	1.52	3.05	485	0.0011	0.0200		0.005
P75	3.05	4.57	486	0.0011	0.0100		0.005
P75	4.57	6.10	487	0.0011	0.0100		0.005
P75	6.10	7.62	488	0.0100	0.0200		0.005
P75	7.62	9.14	489	0.0100	0.0100		0.005
P75	9.14	10.67	490	0.0200	0.0300		0.005
P75	10.67	12.19	491	0.1000	0.0800		0.005
P75	12.19	13.72	492	0.0200	0.0300		0.005
P75	13.72	15.24	493	0.0300	0.0200		0.005
P75	15.24	16.76	494	0.0900	0.0200		0.005
P75	16.76	18.29	495	0.0200	0.0200		0.005
P75	18.29	19.81	496	0.0200	0.0200		0.005
P75	19.81	21.34	497	0.1800	0.1100		0.005
P75	21.34	22.86	498	0.0700	0.0600		0.005
P75	22.86	24.38	499	0.1300	0.1300		0.005
P75	24.38	25.91	500	0.2500	0.1000		0.005
P75	25.91	27.43	501	0.0400	0.0300		0.005
P75	27.43	28.96	502	0.0500	0.0400		0.005
P75	28.96	30.48	503	0.0400	0.0700		0.005
P75	30.48	32.00	504	0.0200	0.0300		0.005
P75	32.00	33.53	505	0.0600	0.1000		0.005
P75	33.53	35.05	506	0.0300	0.0600		0.005
P76	0.00	1.52	508	0.0100	0.0200		0.005
P76	1.52	3.05	509	0.0100	0.0200		0.005
P76	3.05	4.57	510	0.0100	0.0300		0.005
P76	4.57	6.10	511	0.0100	0.0400		0.005
P76	6.10	7.62	512	0.0100	0.0600		0.005
P76	7.62	9.14	513	0.0100	0.1300		0.005
P76	9.14	10.67	514	0.0100	0.1100		0.005
P76	10.67	12.19	515	0.0100	0.0700		0.005
P76	12.19	13.72	516	0.0011	0.0900		0.005
P76	13.72	15.24	517	0.0100	0.0500		0.005
P76	15.24	16.76	518	0.0011	0.0500		0.005
P76	16.76	18.29	519	0.0100	0.0600		0.005
P76	18.29	19.81	520	0.0100	0.0700		0.005
P76	19.81	21.34	521	0.0200	0.0600		0.005
P76	21.34	22.86	522	0.0100	0.0300		0.005
P76	22.86	24.38	523	0.0100	0.0300		0.005
P76	24.38	25.91	524	0.0011	0.0400		0.005
P76	25.91	27.43	525	0.0100	0.0300		0.005
P76	27.43	28.96	526	0.0100	0.0300		0.005
P76	28.96	30.48	527	0.0100	0.0400		0.005
P76	30.48	32.00	528	0.0100	0.0500		0.005
P76	32.00	33.53	529	0.0200	0.1500		0.005
P76	33.53	35.05	530	0.0200	0.0800		0.005
P8	0.00	1.52	139	0.0300	0.0400		0.005
P8	1.52	3.05	140	0.0200	0.0500		0.005
P8	3.05	4.57	141	0.0100	0.0400		0.005
P8	4.57	6.10	142	0.0200	0.0600		0.005
P8	6.10	7.62	143	0.0200	0.0700		0.005
P8	7.62	9.14	144	0.0200	0.0500		0.005
P8	9.14	10.67	145	0.0200	0.0600		0.005
P8	10.67	12.19	146	0.0100	0.0400		0.005
P8	12.19	13.72	147	0.0011	0.0500		0.005
P8	13.72	15.24	148	0.0011	0.0400		0.005
P8	15.24	16.76	149	0.0100	0.0800		0.005
P8	16.76	18.29	150	0.0100	0.0400		0.005

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
P8	18.29	19.81	151	0.0011	0.0300		0.005
P8	19.81	21.34	152	0.0011	0.0200		0.005
P8	21.34	22.86	153	0.0100	0.0200		0.005
P8	22.86	24.38	154	0.0100	0.0300		0.005
P8	24.38	25.91	155	0.0011	0.0200		0.005
P8	25.91	27.43	156	0.0100	0.0400		0.005
P8	27.43	28.96	157	0.0100	0.0300		0.005
P8	28.96	30.48	158	0.0100	0.0300		0.005
P80	0.00	1.52	613	0.0011	0.0500		0.005
P80	1.52	3.05	614	0.0300	0.0400		0.005
P80	3.05	4.57	615	0.0100	0.0200		0.005
P80	4.57	6.10	616	0.0100	0.0200		0.005
P80	6.10	7.62	617	0.0100	0.0200		0.005
P80	7.62	9.14	618	0.0011	0.0300		0.005
P80	9.14	10.67	619	0.0011	0.0400		0.005
P80	10.67	12.19	620	0.0100	0.0300		0.005
P80	12.19	13.72	621	0.0100	0.0300		0.005
P80	13.72	15.24	622	0.0100	0.0500		0.005
P80	15.24	16.76	623	0.0011	0.0800		0.005
P80	16.76	18.29	624	0.0100	0.0700		0.005
P80	18.29	19.81	625	0.0100	0.2200		0.005
P80	19.81	21.34	626	0.0100	0.0800		0.005
P80	21.34	22.86	627	0.0100	0.0600		0.005
P80	22.86	24.38	628	0.0200	0.1800		0.005
P80	24.38	25.91	629	0.0100	0.1200		0.005
P80	25.91	27.43	630	0.0100	0.0800		0.005
P80	27.43	28.96	631	0.0100	0.0900		0.005
P80	28.96	30.48	632	0.0100	0.3000		0.005
P80	30.48	32.00	633	0.0500	0.4400		0.005
P80	32.00	33.53	634	0.0400	0.2100		0.005
P80	33.53	35.05	635	0.0200	0.0700		0.005
P80	35.05	36.58	636	0.0200	0.2200		0.005
P80	36.58	38.10	637	0.0600	0.2300		0.005
P80	38.10	39.62	638	0.0300	0.3800		0.005
P80	39.62	41.15	639	0.0100	0.3500		0.005
P80	41.15	42.67	640	0.0100	0.2200		0.005
P80	42.67	44.20	641	0.0200	0.3400		0.005
P80	44.20	45.72	642	0.0200	0.3000		0.005
P80	45.72	47.24	643	0.0300	0.2500		0.005
P80	47.24	48.77	644	0.0100	0.0700		0.005
P80	48.77	50.29	645	0.0011	0.0500		0.005
P80	50.29	51.82	646	0.0011	0.0500		0.005
P80	51.82	53.34	647	0.0011	0.0400		0.005
P80	53.34	54.86	648	0.0011	0.0500		0.005
P80	54.86	56.39	649	0.0011	0.0500		0.005
P80	56.39	57.91	650	0.0100	0.0500		0.005
P80	57.91	59.44	651	0.0100	0.0400		0.005
P81	0.00	1.52	652	0.0700	0.0200		0.005
P81	1.52	3.05	653	0.0600	0.0100		0.005
P81	3.05	4.57	654	0.0400	0.0100		0.005
P81	4.57	6.10	655	0.0500	0.0100		0.005
P81	6.10	7.62	656	0.1600	0.0300		0.005
P81	7.62	9.14	657	0.4100	0.0900		0.005
P81	9.14	10.67	658	0.4400	0.0700		0.005
P81	10.67	12.19	659	0.2900	0.0400		0.005
P81	12.19	13.72	660	0.1800	0.0200		0.005
P81	13.72	15.24	661	0.2900	0.1000		0.005
P81	15.24	16.76	662	0.4000	0.0300		0.005
P81	16.76	18.29	663	0.1900	0.0200		0.005

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
P81	18.29	19.81	664	0.1800	0.0100		0.005
P81	19.81	21.34	665	0.1900	0.0100		0.005
P81	21.34	22.86	666	0.2400	0.0100		0.005
P81	22.86	24.38	667	0.1700	0.0100		0.005
P81	24.38	25.91	668	0.1700	0.0100		0.005
P81	25.91	27.43	669	0.2300	0.0100		0.005
P81	27.43	28.96	670	0.6600	0.0100		0.005
P81	28.96	30.48	671	0.2600	0.0100		0.005
P81	30.48	32.00	672	0.1300	0.0100		0.005
P81	32.00	33.53	673	0.0400	0.0100		0.005
P81	33.53	35.05	674	0.0100	0.0100		0.005
P81	35.05	36.58	675	0.0100	0.0100		0.005
P81	36.58	38.10	676	0.0400	0.0200		0.005
P81	38.10	39.62	677	0.4800	0.1600		0.005
P81	39.62	41.15	678	0.3100	0.0700		0.005
P81	41.15	42.67	679	0.4300	0.0200		0.005
P81	42.67	44.20	680	0.1000	0.0400		0.005
P81	44.20	45.72	681	0.0300	0.0200		0.005
P81	45.72	47.24	682	0.0300	0.0200		0.005
P81	47.24	48.77	683	0.0800	0.0300		0.005
P81	48.77	50.29	684	0.2000	0.0200		0.005
P81	50.29	51.82	685	0.3600	0.0400		0.005
P81	51.82	53.34	686	0.1100	0.0300		0.005
P81	53.34	54.86	687	0.0700	0.0300		0.005
P81	54.86	56.39	688	0.0300	0.0200		0.005
P81	56.39	57.91	689	0.0200	0.0400		0.005
P81	57.91	59.44	690	0.0500	0.0200		0.005
P81	59.44	60.96	691	0.0200	0.0100		0.005
P81	60.96	62.48	692	0.0200	0.0200		0.005
P81	62.48	64.01	693	0.0100	0.0300		0.005
P81	64.01	65.53	694	0.0011	0.0200		0.005
P81	65.53	67.06	695	0.0200	0.0300		0.005
P81	67.06	68.58	696	0.0100	0.0100		0.005
P81	68.58	70.10	697	0.0100	0.0100		0.005
P81	70.10	71.63	698	0.0100	0.0100		0.005
P81	71.63	73.15	699	0.0011	0.0100		0.005
P81	73.15	74.68	700	0.0100	0.0100		0.005
P81	74.68	76.20	701	0.0100	0.0100		0.005
P82	0.00	1.52	702	0.0010	0.0100		0.005
P82	1.52	3.05	703	0.0010	0.0100		0.005
P82	3.05	4.57	704	0.0010	0.0100		0.005
P82	4.57	6.10	705	0.0010	0.0100		0.005
P82	6.10	7.62	706	0.0300	0.0800		0.005
P82	7.62	9.14	707	0.0100	0.0100		0.005
P82	9.14	10.67	708	0.0400	0.0100		0.005
P82	10.67	12.19	709	0.0200	0.0100		0.005
P82	12.19	13.72	710	0.0010	0.0100		0.005
P82	13.72	15.24	711	0.0010	0.0100		0.005
P82	15.24	16.76	712	0.0010	0.0100		0.005
P82	16.76	18.29	713	0.0100	0.0100		0.005
P82	18.29	19.81	714	0.0010	0.0100		0.005
P82	19.81	21.34	715	0.0010	0.0100		0.005
P82	21.34	22.86	716	0.0010	0.0100		0.005
P82	22.86	24.38	717	0.0010	0.0100		0.005
P82	24.38	25.91	718	0.0010	0.0100		0.005
P82	25.91	27.43	719	0.0010	0.0100		0.005
P82	27.43	28.96	720	0.0100	0.0200		0.005
P82	28.96	30.48	721	0.0010	0.0100		0.005
P82	30.48	32.00	722	0.0010	0.0100		0.005

Hole_ID	From_m	To_m	Sample_ID	Cu_pct	Zn_pct	Au_ppm	Ag_ppm
P82	32.00	33.53	723	0.0010	0.0100		0.005
P82	33.53	35.05	724	0.0010	0.0100		0.005
P82	35.05	36.58	725	0.0200	0.0300		0.005
P82	36.58	38.10	726	0.0010	0.0100		0.005
P82	38.10	39.62	727	0.0010	0.0100		0.005
P82	39.62	41.15	728	0.0010	0.0100		0.005
P82	41.15	42.67	729	0.0010	0.0100		0.005
P82	42.67	44.20	730	0.0011	0.0400		0.005
P82	44.20	45.72	731	0.0010	0.0100		0.005
P82	45.72	47.24	732	0.0010	0.0100		0.005
P82	47.24	48.77	733	0.0010	0.0100		0.005
P82	48.77	50.29	734	0.0010	0.0100		0.005
P82	50.29	51.82	735	0.0010	0.0100		0.005
P82	51.82	53.34	736	0.0010	0.0100		0.005
P82	53.34	54.86	737	0.0011	0.0100		0.005
P82	54.86	56.39	738	0.0100	0.0300		0.005
P82	56.39	57.91	739	0.1800	1.2500		0.005
P82	57.91	59.44	740	0.0100	0.0700		0.005
P82	59.44	60.96	741	0.0011	0.0500		0.005
P83	0.00	1.52	743	0.0010	0.0100		0.005
P83	1.52	3.05	744	0.0010	0.0100		0.005
P83	3.05	4.57	745	0.0010	0.0100		0.005
P83	4.57	6.10	746	0.0010	0.0100		0.005
P83	6.10	7.62	747	0.0010	0.0100		0.005
P83	7.62	9.14	748	0.0010	0.0100		0.005
P83	9.14	10.67	749	0.0200	0.0600		0.005
P83	10.67	12.19	750	0.0200	0.0600		0.005
P83	12.19	13.72	751	0.0010	0.0100		0.005
P83	13.72	15.24	752	0.0010	0.0100		0.005
P83	15.24	16.76	753	0.0010	0.0100		0.005
P83	16.76	18.29	754	0.0010	0.0100		0.005
P83	18.29	19.81	755	0.0100	0.0200		0.005
P83	19.81	21.34	756	0.0010	0.0100		0.005
P83	21.34	22.86	757	0.0010	0.0100		0.005
P83	22.86	24.38	758	0.0010	0.0100		0.005
P83	24.38	25.91	759	0.0010	0.0100		0.005
P83	25.91	27.43	760	0.0300	0.0400		0.005
P83	27.43	28.96	761	0.0010	0.0100		0.005
P83	28.96	30.48	762	0.0010	0.0100		0.005
P83	30.48	32.00	763	0.0010	0.0100		0.005
P83	32.00	33.53	764	0.0010	0.0100		0.005
P83	33.53	35.05	765	0.1500	0.4000		0.005
P83	35.05	36.58	766	0.0010	0.0100		0.005
P83	36.58	38.10	767	0.0010	0.0100		0.005
P83	38.10	39.62	768	0.0010	0.0100		0.005
P83	39.62	41.15	769	0.0010	0.0100		0.005
P83	41.15	42.67	770	0.0800	0.0700		0.005
P83	42.67	44.20	771	0.0010	0.0100		0.005
P83	44.20	45.72	772	0.0010	0.0100		0.005
P83	45.72	47.24	773	0.0010	0.0100		0.005
P83	47.24	48.77	774	0.0010	0.0100		0.005
P83	48.77	50.29	775	0.0100	0.0200		0.005
P83	50.29	51.82	776	0.0100	0.0200		0.005
P83	51.82	53.34	777	0.0100	0.0200		0.005
P83	53.34	54.86	778	0.0011	0.0100		0.005

JORC Code, 2012 Edition – Table 1 report template

Section 1 Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections.)

Criteria	JORC Code explanation	Commentary
Sampling techniques	<p><i>Nature and quality of sampling (e.g., cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc.). These examples should not be taken as limiting the broad meaning of sampling.</i></p> <p><i>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</i></p> <p><i>Aspects of the determination of mineralisation that are Material to the Public Report.</i></p> <p><i>In cases where 'industry standard' work has been done this would be relatively simple (e.g., 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases, more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g., submarine nodules) may warrant disclosure of detailed information.</i></p>	<p><u>RC Drilling</u> RC drilling was designed to obtain drill chip samples predominantly at 1 and 3metre intervals, from which a 2-4 kilogram sub-sample was collected for laboratory multi-element analysis Samples from each metre were collected through a rig-mounted cyclone and</p> <ul style="list-style-type: none"> • split using a rig-mounted static cone splitter. • Field duplicates were taken as well as blanks and Certified Reference Samples inserted at regular intervals and submitted for analysis to monitor QAQC. <p><u>Diamond Drilling</u> Drill core samples were taken at variable intervals from split (halved) HQ/NQ core based on lithology and visible mineralisation. Zones of mineralisation often were samples at 1m intervals and a section of 4-5m composite in areas with no visual mineralisation.</p> <p><u>RC & Diamond Drilling</u> Sample interval summary:</p> <ul style="list-style-type: none"> • 43 intervals were less than 0.75 m, • 559 ranged from 0.76m to 1.20 m, • 45 from 1.21m to 2.00 m, • 253 from 2.01m to 3.00 m, • and 539 intervals ranged from 3.01m to 5.00 m (99.8% are 5m lengths). <p>The individual samples were bagged and dispatched to the ALS Perth laboratory for analysis – 50g charge for FA and multi-element by 4 acid Digest and Aqua regia digest. These were exploratory drill holes with the primary aim to identify or not mineralisation associated with geophysical anomalies. The results were not used to establish a resource estimate.</p>
Drilling techniques	<p><i>Drill type (e.g., core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc.) and details (e.g., core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc.).</i></p>	<p>Mutplie drilling techniques utilized including diamond core and RC drilling. Refer to table for summary relating to exploration target.</p> <p><u>Diamond drilling</u> All diamond core included PQ, HQ and NQ sizes. Drilling collar set up and directions commonly test mineralisation and or targets close to perpendicular of the interpretive trend. All diamond drill core is orientated using reflex or OMNlx42 DH gyro.</p>

		<p><u>RC Drilling</u> Reverse Circulation drilling by Greentech Metals was carried out using a truck-mounted Schramm 685 RC rig equipped with a 5¼-inch diameter face-sampling hammer; fewer details are available for the historic holes included in the Exploration Target review.</p>
<p>Drill sample recovery</p>	<p><i>Method of recording and assessing core and chip sample recoveries and results assessed. Measures taken to maximise sample recovery and ensure representative nature of the samples. Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i></p>	<p><u>Diamond and RC Drilling</u> The geologist visually assesses and records drill core and RC drill sample recoveries. Recoveries are considered appropriate often greater than 95%.</p> <p><u>Diamond Drilling</u> The core was recovered from the drill rig using a standard core barrel and the core was placed into core trays Selected mineralised intervals of core were selected for analysis. Furthermore, a 1 to 5m zone was also sampled adjacent to observed zones of mineralisation.</p> <p><u>RC Drilling</u> A cyclone and static cone splitter were used to ensure representative sampling and were routinely inspected and cleaned. Sample recoveries during drilling were high, and almost all samples were dry. There is not expected to be a systematic bias caused by variable sample recovery.</p>
<p>Logging</p>	<p><i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc.) photography. The total length and percentage of the relevant intersections logged.</i></p>	<p><u>Diamond & RC Drilling</u> All drill holes included in the Exploration Target were geologically logged for lithology, weathering, and other relevant features. The level of geological detail is limited for historic drillholes, while for more recent drilling, it is consistent with the nature and limitations of the exploratory RC drilling technique. Greentech drilling was supervised by an employee of Greentech Metals and using experienced geological contractors provided by APEX Geoscience. These are exploratory drill holes which renders the assay results unsuitable for Resource Estimation. Although data acquired from this program would complement future drilling and assist with Resource Estimation. Data relating to the geological observations and the sampling intervals was entered in a database and the reference drill core & RC chip trays stored at the core shed located at Karratha.</p>
<p>Sub-sampling techniques and sample preparation</p>	<p><i>If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled.</i></p>	<p><u>Diamond Drilling</u> The mineralised sections of the HQ core were sawn in half and then quartered and with quarter core samples taken for analysis. The mineralised sections of the NQ core were sawn in half and with half core samples taken for analysis. There was no core loss associated with the intervals that were sampled. Samples of split core were taken from variable but continuous intervals The samples were then sent to ALS Global Laboratory in Perth for sample preparation and analysis. The sample sizes were appropriate for the style of mineralisation being investigated.</p> <p><u>RC Drilling</u> Recent RC drilling rig was equipped with a rig-mounted cyclone and static cone splitter, which provided one bulk sample of approximately 20-30 kg, and a representative sub-sample of approximately 2-4 kg for</p>

		<p>every metre drilled.</p> <p>The sample size of 2-4 kg is considered to be appropriate and representative of the grain size and mineralisation style of the deposit.</p> <ul style="list-style-type: none"> • Most of the samples were dry. • Duplicate samples were collected and submitted for analysis. <p>In contrast, limited information is available regarding sampling methods for historic drillholes included in the Exploration Target. Details such as sample size, collection technique, moisture content, and whether duplicates were collected are generally not recorded or are poorly documented.</p>
<p>Quality of assay data and laboratory tests</p>	<p><i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i></p> <p><i>For geophysical tools, spectrometers, handheld XRF instruments, etc., the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i></p> <p><i>Nature of quality control procedures adopted (e.g., standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e., lack of bias) and precision have been established.</i></p>	<p><u>Diamond & RC Drilling - Greentech Metals</u></p> <p>ALS Global (Perth) were used for all analysis of drill and RC samples submitted by Greentech. The laboratory techniques below are for all samples submitted to ALS and are considered appropriate for the style of mineralisation defined within the Whundo area:</p> <ul style="list-style-type: none"> • 50-gram Fire Assay (Au-AA26) with ICP finish - Au. • 4 Acid Digest with CP-AES & ICP-MS instrumentation (ME-MS61) –48 elements • 4 Acid Digest ICP-AES Finish (ME-ICP61) – 34 elements • Ore Grade 4 Acid Digest ICP-AES Finish (ME-OG62) <p>Laboratory Certified Reference Materials, blanks and duplicates are inserted at regular intervals analysed with each batch of samples by the laboratory. These quality control results are reported along with the sample values in their final report. Selected samples are also re-analysed to confirm anomalous results.</p> <p><u>Diamond, RC & PER Drilling - Historic</u></p> <p>All reported historic diamond, RC, and percussion (PER) assay data has been entered into the in-house managed database. The quality of some of the historic data has been verified against available laboratory data files or extracts of such to ensure accuracy and consistency. This validation process is ongoing. The laboratory techniques and QAQC are not generally available. Confirmed historic techniques:</p> <ul style="list-style-type: none"> • 50-gram Fire Assay (Au-PM209) with AAS finish – Au • Cu, Zn, Pb and Ag assay by Aqua Regia Digestion with AAS finish (ALS Perth procedure G102) <p>Assay results from the samples taken are reported in Table 2.</p>
<p>Verification of sampling and assaying</p>	<p><i>The verification of significant intersections by either independent or alternative company personnel.</i></p> <p><i>The use of twinned holes.</i></p> <p><i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i></p> <p><i>Discuss any adjustment to assay data.</i></p>	<p><u>Diamond and RC Drilling</u></p> <p>Drill collar data, sample information, logging data and assay results are completed, compiled, and validated by a site geologists and GIS/Administration Geologist.</p> <p>An Access-based data management platform is used by Greentech Metals to electronically enter and store all exploration data.</p>
<p>Location of data points</p>	<p><i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i></p> <p><i>Specification of the grid system used.</i></p> <p><i>Quality and adequacy of topographic control.</i></p>	<p>A handheld GPS is used initially to record the collar location and RL of the drill hole with approximate error of ±5m. Majority of holes resurveyed using DGPS with approximate error ±10cm</p> <p>Down hole orientation surveys were completed on the drill holes at various intervals – 5, 10 and 30m</p> <p>The grid system used is GDA94, MGA zone 50.</p>

Data spacing and distribution	<i>Data spacing for reporting of Exploration Results. Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied. Whether sample compositing has been applied.</i>	The samples have been collected from exploratory drill holes which were designed to test and identify the cause of a deep geophysical anomalies and mineralisation trends projected/modelled from historic drill holes. These are exploratory drill holes which renders the assay results unsuitable for Resource Estimation. Although data acquired from these programs would complement future drilling and assist with Resource Estimation
Orientation of data in relation to geological structure	<i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type. If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i>	The regional stratigraphy and the contained mineralisation comprising the Whundo & Ayshia Resource has a northerly down dip trend approximately between 30-40 deg. The orientation of the stratigraphy in the vicinity of drill holes appears broadly conformable with mineralisation. The work to further understand relationship of stratigraphic and structural controls with mineralisation continues. Sampling bias is not considered an issue with respect to the sampling of these exploratory drill holes. The true orientation of mineralised bodies in this area is generally known, so an assessment of the effect of drill orientation on sample bias can be made if further drilling is undertaken.
Sample security	<i>The measures taken to ensure sample security.</i>	All drill samples from the recent drilling programs were transported by Greentech Metals directly to ALS Global laboratory in Perth for analysis. Sample security was not considered a significant risk to the project, as only Greentech Metals personnel were involved in sample collection, short-term storage at the company's secure operations centre and work compound, and delivery to the laboratory. However, limited information is available regarding sample security procedures for historic drillholes included in the Exploration Target review.
Audits or reviews	<i>The results of any audits or reviews of sampling techniques and data.</i>	No formal audits or reviews have been conducted on sampling technique and data to date.

Section 2 Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section.)

Criteria	JORC Code explanation	Commentary
Mineral tenement and land tenure status	<i>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</i>	The drilling programs being entirely conducted on mining licenses M47/007 (935.1ha) and M47/009 (4.85ha). The tenement is held by Fox Radio Hill Pty Ltd which is a 100% owned subsidiary of Greentech Metals Pty Ltd. The tenement lies within the Ngarluma Native Title claim, with Heritage clearances having been completed. There is no heritage issues associated with the drill hole sites. The tenement is in good standing with no known impediments.
Exploration done by other parties	<i>Acknowledgment and appraisal of exploration by other parties.</i>	The Whundo copper-zinc-cobalt deposit has a long history of prospecting, exploration and small-scale mining dating back to early 1970s. In 2018 Artemis Resources was able to complete an Indicated Mineral Resource Estimate totalling 2.7Mt @1.14%Cu and 1.14%Zn. In addition, geophysical surveys completed by Fox Resources and Artemis Resources led to the identification of numerous conductor targets in proximity to Whundo.
Geology	<i>Deposit type, geological setting and style of mineralisation.</i>	The target for drilling is VMS style copper-zinc-cobalt deposits in proximity to the known Whundo VMS

		deposits. The geological setting of the area is Archaean greenstones consisting of steeply dipping and folded basalts, felsic volcanics, komatiites, and sediments, intruded by voluminous gabbro, dolerite dykes, and granitic intrusions.
Drill hole Information	<i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: easting and northing of the drill hole collar elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar dip and azimuth of the hole down hole length and interception depth hole length. If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</i>	The drill hole collar locations are listed in Table 1 in the body of the release. Drilling was conducted at the natural land surface. Elevation of the drill hole to be determined from a handheld DGPS instrument with an accuracy of +/- 0.1m.
Data aggregation methods	<i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g., cutting of high grades) and cut-off grades are usually Material and should be stated. Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. The assumptions used for any reporting of metal equivalent values should be clearly stated.</i>	Data aggregation methods were used to report on a portion of the mineralised intersections. The standard weighted average method was used to report the composite grade in hole.
Relationship between mineralisation widths and intercept lengths	<i>These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g., ‘down hole length, true width not known’).</i>	The holes drilled were reconnaissance in nature and the relationship between the reported mineralisation and the angle of the drill hole is not known precisely. Hence down hole intercepts of mineralisation have been reported.
Diagrams	<i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i>	The drilling data has been tabulated in summary tables 5 & 6. Illustrations supporting the exploration target estimate model are presented in body of report
Balanced reporting	<i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced avoiding misleading reporting of Exploration Results.</i>	All sample intercept assays for reported drill holes presented in table 2.
Other substantive exploration data	<i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i>	The drill holes were designed to test geophysical targets and projection mineralisation from historic drilling.
Further work	<i>The nature and scale of planned further work (e.g., tests for lateral extensions or depth extensions or large-scale step-out drilling).</i>	<u>Drilling</u> Planning of the forward stage 2 drill program is underway which will focus on testing; <ul style="list-style-type: none"> • For continuity of mineralisation between Austin and Shelby (EIS Co-funded)

Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.

- Down plunge extent of the Ashyia shoot
- Shallow high grade oxide mineralisation at Yannery
- Core holes at Whundo and Ayshia to provide material for metallurgical test work

Conceptual Mine Study

- Completion of Mineral Resource Estimates for Whundo, Ayshia and Yannery incorporating gold
- Completion of Whittle optimisation for Whundo, Ayshia and Yannery
- Evaluating the economics of near-term production opportunities
- Further evaluation of the Radio Hill Processing site as a processing option for Whundo

Mining Compliance

- Commence the application process for a mining permit